



Bulk Density: 2.81 gm/cc

BH.No.	Section Line	Sectional Area (m ²)	Strike Influence (m)	Volume (m ³)	Geological Gross In-situ Resources (tonnes)	Average Quality									
						CaO %	MgO %	Al ₂ O ₃ %	SiO ₂ %	Fe ₂ O ₃ %	SO ₃ %	P ₂ O ₅ %	K ₂ O %	Na ₂ O %	LOI %
MDK-02	S3-S3'	34573.46	800	27658767.84	77721137.63	33.31	16.36	0.89	4.22	0.41	0.06	0.02	0.16	0.04	44.35
MDK-03	S2-S2'	20099.40	800	16079516.48	45183441.31	34.85	16.93	0.41	2.31	0.29	0.04	0.06	0.07	0.04	44.84
MDK-04	S1-S1'	6000.00	800	4800000.00	13488000.00	29.66	17.13	1.76	8.10	0.48	0.07	0.03	0.29	0.16	42.09
MDK-04	S1-S1'	6400.00	800	5120000.00	14387200.00	30.27	16.59	1.89	7.39	0.46	0.15	0.06	0.32	0.13	42.50
MDK-04	S1-S1'	3959.80	800	3167842.88	8901638.49	33.34	16.71	1.07	3.96	0.68	0.13	0.02	0.18	0.13	43.30
MDK-05	S2-S2'	3200.01	800	2560006.00	7193616.86	30.06	17.18	1.85	6.62	0.39	0.55	0.07	0.29	0.15	42.63
MDK-05	S2-S2'	15589.37	800	12471495.60	35044902.64	31.77	16.93	1.47	5.12	0.34	0.54	0.03	0.25	0.14	43.19
Total Geological Gross In-situ Resources of Beneficial Grade Dolomite in Tonnes					201919936.93	32.81	16.70	1.05	4.51	0.39	0.17	0.04	0.18	0.08	43.87
Total Geological Gross In-situ Resources of Beneficial Grade Dolomite in Million Tonnes (MT)					201.92										