



**Bulk density determination of glauconitic mineralisation for  
Deulha (G-3 stage) block, Satna, Madhya Pradesh**

Sl. No.	SampleNo.	Borehole No.	From (m)	To (m)	Bulk Density (gm/cm <sup>3</sup> )
1	MDLH/BD01	MDLH-01	30.90	31.00	2.67
2	MDLH/BD02	MDLH-04	23.88	24.00	2.67
3	MDLH/BD03	MDLH-07	36.00	36.10	2.62
4	MDLH/BD04	MDLH-08	13.89	14.00	2.71
<b>Average Bulk Density</b>					<b>2.67</b>