



**Statement Showing Primary Analysis for 5 Trace Elements Ni, Co, Cd, Cr & Ti) of
borehole core samples of Amoch Chhapra (G-3) Block for Iron and Bauxite,
Dist.- Jabalpur & Katni, Madhya Pradesh**

Sr No	BH No.	Sample No.	From (m)	To (m)	Thick. (m)	Ni (ppm)	Co (ppm)	Cd (ppm)	Cr (ppm)	Ti (%)
1	MBAC-2	MACTR-1	9.00	10.00	1.00	37.14	43.27	12.78	160.69	2.15
2	MBAC-2	MACTR-2	15.00	16.00	1.00	40.36	45.26	11.66	141.96	2.27
3	MBAC-2	MACTR-3	17.00	18.00	1.00	51.15	77.49	10.29	194.93	3.79
4	MBAC-4	MACTR-4	9.00	10.00	1.00	27.20	93.12	9.82	92.68	4.14
5	MBAC-4	MACTR-5	10.00	11.00	1.00	84.36	112.05	5.61	102.52	3.39
6	MBAC-4	MACTR-6	11.00	12.00	1.00	135.44	128.37	6.10	88.98	2.77
7	MBAC-4	MACTR-7	13.00	14.00	1.00	182.52	149.34	9.77	84.17	2.83
8	MBAC-7	MACTR-8	8.00	9.00	1.00	49.57	43.78	14.35	318.91	1.92
9	MBAC-12	MACTR-9	12.00	13.00	1.00	34.20	37.81	11.65	183.31	2.17
10	MBAC-12	MACTR-10	13.00	14.00	1.00	42.58	66.56	10.17	348.10	2.94