

**Statement Showing Zone details with respect to $Al_2O_3 \geq 20\%$,
 $Ti \geq 2\%$ and $V \geq 500$ ppm, Majhauri (G-3) Block for Iron and Bauxite,
Distt.- Jabalpur, Madhya Pradesh**

Zone details with $Al_2O_3 \geq 20\%$ Cut off

Sl. No.	BH No.	From (m)	To (m)	Thickness (m)	$Al_2O_3\%$
1	MBAC-1	0.00	11.00	11.00	25.78
2	MBAC-2	0.00	19.00	19.00	27.82
3	MBAC-3	1.00	20.00	19.00	29.62
4	MBAC-4	0.00	12.00	12.00	28.73
5	MBAC-7	0.00	15.00	15.00	25.27
6	MBAC-10	0.00	10.00	10.00	23.08
7	MBAC-12	0.00	15.00	15.00	27.73
8	MBAC-13	0.00	20.00	20.00	29.80
9	MBAC-14	0.00	20.00	20.00	31.72
10	MBAC-15	0.00	20.00	20.00	28.30
11	MBAC-16	0.00	20.00	20.00	27.90
12	MBAC-17	0.00	20.00	20.00	28.96
13	MBAC-18	0.00	20.00	20.00	28.97

Zone details with $Ti \geq 2\%$ Cut off

Sl. No.	BH No.	From (m)	To (m)	Thickness (m)	Ti%
1	MBAC-2	6.00	18.00	12.00	2.38
2	MBAC-3	1.00	4.00	3.00	2.47
3	MBAC-3	8.00	18.00	10.00	2.24
4	MBAC-4	0.00	20.00	20.00	2.62
5	MBAC-7	7.00	15.00	8.00	2.11
6	MBAC-12	2.00	5.00	3.00	2.35
7	MBAC-12	12.00	15.00	3.00	2.66
8	MBAC-13	12.00	17.00	5.00	2.32
9	MBAC-14	6.00	20.00	14.00	2.44
10	MBAC-15	8.00	14.00	6.00	2.06
11	MBAC-16	4.00	12.00	8.00	2.26
12	MBAC-17	4.00	14.00	10.00	2.28
13	MBAC-18	8.00	18.00	10.00	2.99

Zone details with $V \geq 500$ ppm Cut off

Sl. No.	BH No.	From (m)	To (m)	Thickness (m)	V (ppm)
1	MBAC-2	0.00	18.00	18.00	522.52
2	MBAC-3	1.00	5.00	4.00	815.84
3	MBAC-4	2.00	14.00	12.00	622.08
4	MBAC-7	0.00	17.00	17.00	653.82
5	MBAC-11	0.00	6.00	6.00	868.98
6	MBAC-12	0.00	15.00	15.00	632.35
7	MBAC-13	0.00	20.00	20.00	583.59
8	MBAC-14	0.00	20.00	20.00	680.20
9	MBAC-15	0.00	8.00	8.00	666.54
10	MBAC-15	16.00	20.00	4.00	701.97
11	MBAC-16	2.00	20.00	18.00	551.54
12	MBAC-17	0.00	20.00	20.00	579.08
13	MBAC-18	0.00	10.00	10.00	648.22
14	MBAC-18	14.00	20.00	6.00	661.31