

**Bulk density determination of glauconitic mineralisation for Ambara West G-4 Block,
District-Kachchh, Gujarat**

Sl. No.	Sample no.	Borehole no.	From (m)	To (m)	Bulk Density (gm/cm ³)
1	MKA W-01BD1	MKA W-01	11.45	11.66	1.82
2	MKA W-03BD1	MKA W-03	22.85	23.00	2.17
3	MKA W-04BD1	MKA W-04	13.10	13.27	1.93
4	MKA W-09BD1	MKA W-09	13.70	13.85	1.93
5	MKA W-10BD1	MKA W-10	21.38	21.55	1.87
Average Bulk Density					1.94