



{at IBM cut off for Aluminous Laterite Al₂O₃ - 20%(min)}

									Bulk Density: 2.32					
Sl. No.	BH No.	Polygon Area (m ²)	Thickness (m)	Volume (m ³)	Gross Geological Resources (tonnes)	Net Geological Resources (tonnes)	Average Quality							
							Al ₂ O ₃ %	Fe ₂ O ₃ %	SiO ₂ %	TiO ₂ %	LOI %	Sc (ppm)	Ga (ppm)	V (ppm)
1	MBD-01	81183.98	6.00	487103.86	1130080.95	1017072.86	35.80	30.01	9.42	4.63	19.25	47.36	78.21	884.98
2	MBD-02	49605.81	5.50	272831.93	567490.42	510741.38	37.68	29.35	8.19	3.28	20.74	36.66	65.64	705.71
3	MBD-03	22489.61	2.00	44979.22	93556.77	84201.10	39.19	23.26	11.01	5.90	20.05	51.72	102.71	1031.00
4	MBD-04	38449.87	3.30	126884.57	263919.91	237527.92	30.76	35.65	11.56	4.91	16.61	71.55	57.67	792.33
Total Geological resources of Aluminous Laterite with grade in tonnes					2055048.06	1849543.25	35.83	30.25	9.43	4.35	19.36	47.71	73.22	830.22
Total Geological resources for Aluminous Laterite with grade in million tonnes					2.06	1.85								