



**Statement showing the Composite Sample Analysis for Mn%, SiO₂%, P₂O₅%, Fe₂O₃%,
MnO₂% & Acid Insoluble% in Katori Jhiriya Block,
District: Balaghat, Madhya Pradesh**

Sr. No.	Sample Id	Mn%	SiO ₂ %	P ₂ O ₅ %	Fe ₂ O ₃ %	MnO ₂ %	Acid Insoluble%
1	MKJ/C01	14.99	44.54	1.33	11.79	3.04	79.62
2	MKJ/C02	4.53	58.66	0.40	8.47	0.38	88.61
3	MKJ/C03	11.79	57.71	1.79	9.47	<0.10	88.53