



**Comparison of Bedrock/Channel Sample Analysis Vs External Check Sample  
Analysis for Au by fire assay in Bargur Block,  
District-Krishnagiri, Tamil Nadu**

S.No.	Primary Sample	Check Sample	Primary Au (PPM)	Check Sample Au (PPM)
			(DL= 0.01 PPM)	(DL= 0.01 PPM)
1	MBBR-091	MBBR/EAU-01	0.19	0.14
2	MBBR-004	MBBR/EAU-02	0.03	<0.01
3	MBBR-014	MBBR/EAU-03	0.01	<0.01
4	MBBR-013	MBBR/EAU-04	0.09	0.07
5	MBBR-117	MBBR/EAU-05	0.08	0.04
6	MBBR-119	MBBR/EAU-06	<0.01	<0.01
7	MBBR-128	MBBR/EAU-07	0.01	<0.01
8	MBBR-134	MBBR/EAU-08	0.01	<0.01
9	MBBR-147	MBBR/EAU-09	<0.01	<0.01
10	MBBR-086	MBBR/EAU-10	0.07	0.04
11	MBBR-183	MBBR/EAU-11	0.03	<0.01
12	MBBR-046	MBBR/EAU-12	<0.01	<0.01
13	MBBR-060	MBBR/EAU-13	<0.01	<0.01
14	MBBR-063	MBBR/EAU-14	0.03	<0.01
15	MBBR-097	MBBR/EAU-15	<0.01	<0.01
16	MBBR-098	MBBR/EAU-16	<0.01	<0.01
17	MBBR-102	MBBR/EAU-17	0.01	<0.01
18	MBBR-149	MBBR/EAU-18	<0.01	<0.01
19	MBBR-165	MBBR/EAU-19	<0.01	<0.01
20	MBBR-180	MBBR/EAU-20	0.09	0.08

DL= Detection limit