

Details of chemical analysis of Primary samples for W, Sn, Cu, Pb & Zn of the boreholes drilled in Murara-Devendrapura Block (G-3), District - Niwari, Madhya Pradesh

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To		Primary Analysis PPM (DL = 1 PPM)				
1	MMDB-01/01	63.00	63.81	0.81	89.42	6.64	8.78	7.48	97.94
2	MMDB-01/02	63.81	64.60	0.79	219.83	<1.0	24.08	<1.0	45.46
3	MMDB-01/03	64.60	65.26	0.66	210.48	6.82	11.74	<1.0	46.01
4	MMDB-01/04	65.26	66.00	0.74	306.08	1.89	23.58	<1.0	24.23
5	MMDB-01/05	66.00	67.02	1.02	286.58	18.02	8.64	<1.0	15.30
6	MMDB-01/06	67.02	68.02	1.00	225.90	21.26	12.36	2.53	26.79
7	MMDB-01/07	68.02	69.00	0.98	289.88	<1.0	22.90	2.80	2.87
8	MMDB-01/08	69.00	69.82	0.82	310.80	14.02	31.06	1.00	23.14
9	MMDB-01/09	69.82	70.54	0.72	354.23	7.15	61.21	<1.0	12.05
10	MMDB-01/10	70.54	71.49	0.95	271.98	<1.0	6.38	<1.0	20.60
11	MMDB-01/11	71.49	72.44	0.95	224.82	<1.0	4.53	<1.0	20.99
12	MMDB-01/12	72.44	73.40	0.96	254.23	<1.0	13.49	16.84	18.59
13	MMDB-01/13	73.40	74.70	1.30	320.00	<1.0	7.24	1.70	35.40
14	MMDB-01/14	74.70	75.73	1.03	226.92	<1.0	31.25	12.19	20.99
15	MMDB-01/15	75.73	76.80	1.07	232.36	<1.0	7.79	14.51	22.78
16	MMDB-01/16	76.80	78.00	1.20	199.90	<1.0	4.68	15.36	26.37
17	MMDB-01/17	78.00	85.78	7.78	151.90	7.08	2.84	13.34	31.50
18	MMDB-01/18	85.78	87.00	1.22	2.77	8.44	2.14	17.07	40.59
19	MMDB-01/19	87.00	87.98	0.98	2.42	<1.0	1.38	14.39	16.67
20	MMDB-01/20	87.98	88.96	0.98	39.36	13.63	3.91	20.21	18.75
21	MMDB-01/21	88.96	90.00	1.04	4.38	11.12	28.84	14.24	5.64
22	MMDB-01/22	90.00	90.91	0.91	3.64	6.78	42.18	29.04	1.48
23	MMDB-01/23	90.91	91.64	0.73	5.08	11.98	3.16	12.40	18.57
24	MMDB-01/24	91.64	92.45	0.81	2.42	20.37	2.84	15.21	19.29
25	MMDB-01/25	92.45	93.00	0.55	3.88	13.72	4.57	7.94	6.75
26	MMDB-02/01	60.32	61.42	1.10	261.11	<1.0	6.16	1.00	19.68
27	MMDB-02/02	61.42	62.39	0.97	494.30	4.63	23.52	2.91	9.23
28	MMDB-02/03	62.39	63.32	0.93	267.92	<1.0	54.76	7.23	43.72
29	MMDB-02/04	63.32	64.26	0.94	172.60	<1.0	15.00	8.26	96.66
30	MMDB-02/05	64.26	65.22	0.96	121.73	<1.0	7.38	8.41	71.64
31	MMDB-02/06	65.22	66.15	0.93	174.87	9.82	21.59	24.46	49.77
32	MMDB-02/07	66.15	67.13	0.98	365.47	15.14	9.30	9.04	7.46

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To		Primary Analysis PPM (DL = 1 PPM)				
33	MMDB-02/08	67.13	68.09	0.96	341.84	<1.0	5.42	1.81	27.28
34	MMDB-02/09	68.09	69.00	0.91	294.59	1.01	3.56	1.37	7.18
35	MMDB-02/10	69.00	69.99	0.99	217.13	<1.0	3.38	1.60	9.29
36	MMDB-02/11	69.99	70.98	0.99	306.00	<1.0	34.73	13.18	34.85
37	MMDB-02/12	70.98	72.00	1.02	343.06	2.56	19.64	10.07	27.66
38	MMDB-02/13	72.00	72.96	0.96	297.70	1.00	2.96	<1.0	10.18
39	MMDB-02/14	72.96	73.93	0.97	395.96	3.16	5.99	2.47	7.52
40	MMDB-02/15	73.93	74.87	0.94	380.29	<1.0	5.31	4.20	19.07
41	MMDB-02/16	74.87	75.81	0.94	327.75	15.25	5.90	1.81	8.49
42	MMDB-02/17	75.81	76.79	0.98	273.82	1.81	6.09	5.40	19.34
43	MMDB-02/18	76.79	77.74	0.95	194.87	19.68	12.08	4.46	9.37
44	MMDB-02/19	77.74	78.68	0.94	210.45	24.67	6.89	5.01	8.46
45	MMDB-02/20	78.68	79.62	0.94	283.41	<1.0	7.70	10.44	22.58
46	MMDB-02/21	79.62	80.58	0.96	455.43	<1.0	8.60	6.79	11.17
47	MMDB-02/22	80.58	81.53	0.95	463.56	63.81	10.54	4.70	7.44
48	MMDB-02/23	81.53	82.51	0.98	232.28	50.88	8.99	4.19	5.32
49	MMDB-02/24	82.51	83.44	0.93	466.30	46.57	23.24	1.00	1.24
50	MMDB-02/25	83.44	84.34	0.90	561.26	53.21	9.52	2.56	31.17
51	MMDB-02/26	84.34	85.27	0.93	537.00	77.47	11.21	3.82	1.93
52	MMDB-02/27	85.27	86.23	0.96	559.51	50.41	29.24	2.36	2.15
53	MMDB-02/28	86.23	87.00	0.77	500.63	56.72	12.48	1.88	<1.0
54	MMDB-02/29	87.00	88.10	1.10	407.69	39.79	25.72	<1.0	<1.0
55	MMDB-02/30	88.10	89.05	0.95	402.08	61.08	30.06	<1.0	<1.0
56	MMDB-02/31	89.05	90.00	0.95	459.86	51.32	21.17	2.02	<1.0
57	MMDB-02/32	90.00	90.90	0.90	555.92	<1.0	12.89	7.90	4.92
58	MMDB-02/33	90.90	91.80	0.90	13.74	<1.0	9.90	10.92	13.12
59	MMDB-02/34	91.80	92.70	0.90	15.29	<1.0	16.67	11.94	16.29
60	MMDB-02/35	92.70	93.61	0.91	30.49	<1.0	37.28	6.73	10.77
61	MMDB-02/36	93.61	94.59	0.98	22.86	<1.0	5.88	1.97	<1.0
62	MMDB-02/37	94.59	95.53	0.94	41.67	<1.0	11.23	2.94	<1.0
63	MMDB-02/38	95.53	96.43	0.90	42.66	<1.0	11.74	11.27	2.94
64	MMDB-02/39	96.43	97.37	0.94	275.40	<1.0	11.08	4.42	3.76
65	MMDB-02/40	97.37	98.30	0.93	32.62	<1.0	6.21	5.68	19.12
66	MMDB-02/41	98.30	99.20	0.90	192.07	<1.0	7.45	7.88	17.07
67	MMDB-02/42	99.20	100.13	0.93	312.88	<1.0	5.47	8.71	<1.0
68	MMDB-02/43	100.13	101.06	0.93	329.72	<1.0	10.50	4.00	<1.0
69	MMDB-02/44	101.06	102.00	0.94	335.60	<1.0	25.95	11.28	2.77
70	MMDB-02/45	102.00	102.93	0.93	529.36	<1.0	12.82	39.07	<1.0
71	MMDB-02/46	102.93	103.83	0.90	440.12	<1.0	10.06	4.46	<1.0
72	MMDB-02/47	103.83	104.75	0.92	307.13	<1.0	9.36	13.29	<1.0
73	MMDB-02/48	104.75	105.65	0.90	561.28	<1.0	9.55	5.58	2.44

ANNEXURE- II

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To						
74	MMDB-02/49	105.65	106.61	0.96	428.72	<1.0	2.96	7.61	<1.0
75	MMDB-02/50	106.61	107.52	0.91	393.36	<1.0	1.16	1.30	<1.0
76	MMDB-02/51	107.52	108.39	0.87	378.09	<1.0	1.00	1.67	<1.0
77	MMDB-02/52	108.39	109.34	0.95	315.19	<1.0	2.53	<1.0	5.47
78	MMDB-02/53	109.34	110.24	0.90	244.54	<1.0	2.39	1.02	<1.0
79	MMDB-02/54	110.24	111.00	0.76	256.90	<1.0	4.11	2.37	<1.0
80	MMDB-02/55	111.00	111.69	0.69	478.73	<1.0	10.87	6.94	5.08
81	MMDB-03/01	42.00	42.70	0.70	371.34	<1.0	11.85	2.47	6.82
82	MMDB-03/02	42.70	43.40	0.70	293.08	<1.0	17.73	1.43	<1.0
83	MMDB-03/03	43.40	44.10	0.70	299.05	<1.0	18.88	1.55	<1.0
84	MMDB-03/04	44.10	45.00	0.90	310.64	<1.0	9.17	<1.0	10.22
85	MMDB-03/05	45.00	46.02	1.02	428.11	<1.0	11.83	<1.0	1.73
86	MMDB-03/06	46.02	46.97	0.95	298.08	<1.0	9.77	<1.0	14.14
87	MMDB-03/07	46.97	48.00	1.03	291.61	<1.0	1.94	<1.0	17.88
88	MMDB-03/08	48.00	49.00	1.00	235.21	<1.0	2.51	1.26	51.13
89	MMDB-03/09	49.00	49.98	0.98	54.20	<1.0	5.09	3.21	64.61
90	MMDB-03/10	49.98	51.00	1.02	88.23	<1.0	14.27	5.16	6.16
91	MMDB-03/11	51.00	52.00	1.00	321.99	<1.0	4.43	2.43	6.26
92	MMDB-03/12	52.00	52.69	0.69	107.33	<1.0	2.59	2.36	8.98
93	MMDB-03/13	52.69	53.66	0.97	31.35	<1.0	33.74	7.28	20.60
94	MMDB-03/14	53.66	54.57	0.91	375.73	<1.0	2.40	4.44	<1.0
95	MMDB-03/15	54.57	55.83	1.26	50.48	<1.0	3.41	13.24	12.79
96	MMDB-03/16	55.83	56.91	1.08	134.45	<1.0	4.78	17.29	14.45
97	MMDB-03/17	56.91	58.00	1.09	170.97	<1.0	10.94	22.28	19.90
98	MMDB-03/18	58.00	59.27	1.27	165.46	<1.0	31.23	19.70	21.43
99	MMDB-03/19	59.27	59.90	0.63	447.43	<1.0	2.19	1.75	<1.0
100	MMDB-03/20	59.90	61.00	1.10	389.85	<1.0	2.01	5.76	7.26
101	MMDB-03/21	61.00	61.86	0.86	319.16	<1.0	3.16	6.88	5.56
102	MMDB-03/22	61.86	62.94	1.08	461.12	<1.0	1.60	2.02	<1.0
103	MMDB-03/23	62.94	63.75	0.81	398.37	<1.0	4.49	2.63	<1.0
104	MMDB-03/24	63.75	64.48	0.73	380.08	<1.0	2.35	1.70	<1.0
105	MMDB-03/25	64.48	65.05	0.57	438.70	<1.0	10.59	8.88	9.50
106	MMDB-03/26	65.05	66.08	1.03	384.87	<1.0	4.66	3.01	<1.0
107	MMDB-03/27	66.08	67.00	0.92	337.04	<1.0	3.33	2.52	<1.0
108	MMDB-03/28	67.00	67.89	0.89	448.53	<1.0	83.83	249.23	<1.0
109	MMDB-03/29	67.89	68.67	0.78	477.36	<1.0	11.70	15.72	<1.0
110	MMDB-03/30	68.67	69.31	0.65	169.17	<1.0	6.42	4.65	<1.0
111	MMDB-03/31	69.31	70.30	0.99	360.34	<1.0	7.26	8.16	<1.0
112	MMDB-03/32	70.30	71.22	0.92	377.69	<1.0	7.46	9.17	6.02
113	MMDB-03/33	71.22	71.72	0.50	229.02	<1.0	2.61	6.57	8.38
114	MMDB-03/34	71.72	72.40	0.68	253.32	<1.0	4.30	14.22	<1.0

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To		Primary Analysis PPM (DL = 1 PPM)				
115	MMDB-03/35	72.40	73.20	0.80	232.11	<1.0	4.00	5.43	4.97
116	MMDB-03/36	73.20	74.05	0.85	243.58	<1.0	5.63	10.84	24.97
117	MMDB-03/37	74.05	75.02	0.97	412.53	<1.0	8.48	10.21	16.72
118	MMDB-03/38	75.02	76.25	1.23	442.59	<1.0	7.97	6.39	6.36
119	MMDB-03/39	81.55	82.00	0.45	521.40	<1.0	12.12	5.52	4.41
120	MMDB-03/40	86.00	86.83	0.83	344.36	<1.0	6.39	3.25	5.00
121	MMDB-03/41	86.83	87.77	0.94	531.71	<1.0	27.35	6.47	<1.0
122	MMDB-03/42	87.77	88.49	0.72	437.19	<1.0	11.61	7.57	<1.0
123	MMDB-03/43	88.49	89.40	0.91	456.89	<1.0	5.65	4.31	<1.0
124	MMDB-03/44	89.40	90.35	0.95	12.72	<1.0	20.78	16.07	4.76
125	MMDB-03/45	90.35	91.31	0.96	11.60	<1.0	4.17	4.42	<1.0
126	MMDB-03/46	91.31	92.19	0.88	8.85	<1.0	6.40	4.44	<1.0
127	MMDB-03/47	92.19	93.16	0.97	6.90	<1.0	7.78	6.16	<1.0
128	MMDB-03/48	93.16	94.07	0.91	4.31	<1.0	23.01	80.90	<1.0
129	MMDB-03/49	94.07	95.00	0.93	6.04	<1.0	28.52	7.37	<1.0
130	MMDB-03/50	95.00	95.97	0.97	1.96	<1.0	9.84	2.25	<1.0
131	MMDB-03/51	95.97	96.96	0.99	185.61	<1.0	27.02	3.63	<1.0
132	MMDB-03/52	96.96	98.00	1.04	207.22	<1.0	27.70	3.69	<1.0
133	MMDB-03/53	98.00	98.98	0.98	176.25	<1.0	18.20	4.28	<1.0
134	MMDB-03/54	98.98	99.94	0.96	357.13	<1.0	6.10	1.79	<1.0
135	MMDB-03/55	99.94	101.00	1.06	397.24	<1.0	37.01	2.93	<1.0
136	MMDB-03/56	101.00	102.00	1.00	403.48	<1.0	12.61	1.74	<1.0
137	MMDB-03/57	102.00	102.99	1.00	350.17	<1.0	6.41	2.08	10.63
138	MMDB-03/58	102.99	104.00	1.01	411.29	<1.0	7.14	3.13	9.40
139	MMDB-03/59	104.00	105.02	1.02	447.80	<1.0	7.59	2.16	<1.0
140	MMDB-03/60	105.02	105.91	0.90	251.97	<1.0	9.50	5.92	12.64
141	MMDB-03/61	105.91	107.00	1.09	339.67	<1.0	27.39	23.71	27.64
142	MMDB-03/62	107.00	108.03	1.03	465.35	<1.0	27.08	6.20	<1.0
143	MMDB-03/63	108.03	109.01	0.98	281.43	<1.0	6.50	1.38	<1.0
144	MMDB-03/64	109.01	110.00	0.99	424.12	<1.0	47.57	7.58	<1.0
145	MMDB-03/65	110.00	110.93	0.93	456.75	<1.0	10.50	3.47	<1.0
146	MMDB-03/66	110.93	111.92	0.99	492.86	<1.0	14.45	1.27	<1.0
147	MMDB-03/67	111.92	113.00	1.08	465.57	<1.0	14.31	3.88	<1.0
148	MMDB-03/68	113.00	113.93	0.93	558.04	<1.0	15.53	5.55	8.96
149	MMDB-03/69	113.93	114.84	0.92	449.08	<1.0	8.23	1.81	<1.0
150	MMDB-03/70	114.84	116.00	1.16	383.22	<1.0	5.45	5.44	26.00
151	MMDB-03/71	116.00	116.97	0.97	23.15	<1.0	9.21	29.90	2.07
152	MMDB-03/72	116.97	117.91	0.94	559.66	<1.0	17.55	23.17	1.23
153	MMDB-03/73	117.91	119.00	1.09	420.08	<1.0	4.55	8.71	9.12
154	MMDB-03/74	119.00	119.83	0.83	347.09	<1.0	4.44	9.22	14.36
155	MMDB-04/01	29.56	30.48	0.92	272.08	<1.0	11.08	2.48	12.43

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To		Primary Analysis PPM (DL = 1 PPM)				
156	MMDB-04/02	30.48	31.40	0.92	394.62	<1.0	33.28	1.00	10.04
157	MMDB-04/03	54.03	54.92	0.89	350.22	<1.0	5.11	4.77	2.05
158	MMDB-04/04	54.92	56.00	1.08	514.33	<1.0	4.60	2.51	<1.0
159	MMDB-04/05	56.00	57.00	1.00	449.13	<1.0	2.33	<1.0	<1.0
160	MMDB-04/06	57.00	58.12	1.12	445.77	<1.0	5.01	1.40	<1.0
161	MMDB-04/07	58.12	59.00	0.88	407.38	<1.0	3.91	4.32	5.06
162	MMDB-04/08	59.00	60.00	1.00	439.90	<1.0	2.80	2.55	<1.0
163	MMDB-04/09	60.00	61.01	1.02	541.05	<1.0	6.79	<1.0	<1.0
164	MMDB-04/10	61.01	62.00	0.99	175.40	<1.0	5.33	<1.0	<1.0
165	MMDB-04/11	62.00	63.01	1.01	163.39	<1.0	2.64	<1.0	1.00
166	MMDB-04/12	63.01	64.02	1.02	284.53	<1.0	5.62	<1.0	<1.0
167	MMDB-04/13	64.02	65.00	0.98	204.87	<1.0	1.54	<1.0	6.79
168	MMDB-04/14	65.00	65.99	0.99	338.27	<1.0	7.51	8.60	<1.0
169	MMDB-04/15	65.99	66.99	1.00	460.76	<1.0	5.19	2.96	<1.0
170	MMDB-04/16	66.99	68.00	1.01	489.46	<1.0	29.83	87.82	<1.0
171	MMDB-04/17	68.00	68.95	0.95	9.93	<1.0	16.99	15.08	<1.0
172	MMDB-04/18	68.95	70.00	1.05	394.77	<1.0	9.43	15.69	<1.0
173	MMDB-04/19	70.00	71.00	1.00	418.03	<1.0	11.72	11.75	<1.0
174	MMDB-04/20	71.00	71.97	0.97	475.02	<1.0	7.77	3.80	<1.0
175	MMDB-04/21	71.97	72.97	1.00	388.30	<1.0	12.65	1.12	<1.0
176	MMDB-04/22	72.97	74.00	1.03	526.75	<1.0	4.34	12.91	<1.0
177	MMDB-04/23	74.00	75.02	1.02	405.15	<1.0	24.64	5.89	30.56
178	MMDB-04/24	75.02	75.98	0.96	<1.0	<1.0	<1.0	<1.0	<1.0
179	MMDB-04/25	75.98	77.00	1.02	188.72	<1.0	2.11	<1.0	<1.0
180	MMDB-04/26	77.00	78.00	1.00	102.10	<1.0	<1.0	<1.0	<1.0
181	MMDB-04/27	78.00	79.00	1.00	370.59	<1.0	17.90	2.07	3.63
182	MMDB-04/28	79.00	80.00	1.00	11.43	<1.0	<1.0	<1.0	<1.0
183	MMDB-04/29	80.00	80.98	0.98	166.20	<1.0	2.49	1.69	<1.0
184	MMDB-04/30	80.98	81.98	1.00	452.25	<1.0	3.61	3.18	5.03
185	MMDB-04/31	81.98	83.00	1.02	43.75	<1.0	<1.0	<1.0	<1.0
186	MMDB-04/32	83.00	84.00	1.00	163.82	<1.0	1.47	<1.0	<1.0
187	MMDB-04/33	84.00	85.00	1.00	<1.0	<1.0	<1.0	<1.0	<1.0
188	MMDB-04/34	85.00	86.00	1.00	367.95	<1.0	12.06	1.21	<1.0
189	MMDB-04/35	86.00	86.93	0.93	227.10	<1.0	16.48	1.56	31.60
190	MMDB-04/36	86.93	87.91	0.98	182.09	<1.0	15.14	<1.0	8.32
191	MMDB-04/37	87.91	88.87	0.96	104.19	<1.0	12.04	<1.0	9.09
192	MMDB-04/38	88.87	89.79	0.92	123.53	<1.0	7.58	1.34	<1.0
193	MMDB-04/39	89.79	90.74	0.95	121.37	<1.0	10.80	3.36	<1.0
194	MMDB-04/40	90.74	91.70	0.96	136.44	<1.0	20.41	2.88	1.16
195	MMDB-04/41	91.70	92.61	0.91	97.66	<1.0	9.75	7.53	<1.0
196	MMDB-04/42	92.61	93.57	0.96	61.12	<1.0	31.03	14.11	8.67

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To		Primary Analysis PPM (DL = 1 PPM)				
197	MMDB-04/43	93.57	94.52	0.95	203.13	<1.0	12.47	9.77	17.53
198	MMDB-04/44	94.52	95.18	0.66	215.10	<1.0	5.56	3.24	7.27
199	MMDB-04/45	95.18	96.20	1.02	153.45	<1.0	21.19	69.02	5.89
200	MMDB-05/01	66.42	67.46	1.04	273.37	<1.0	78.82	8.07	21.96
201	MMDB-05/02	67.46	68.17	0.71	333.82	<1.00	2.72	<1.00	19.11
202	MMDB-05/03	68.17	69.00	0.83	212.89	<1.00	25.95	5.13	29.89
203	MMDB-05/04	69.00	69.85	0.85	250.54	<1.00	8.20	2.98	20.20
204	MMDB-05/05	69.85	71.32	1.47	287.05	<1.00	2.96	2.32	13.41
205	MMDB-06/01	63.58	64.13	0.55	228.03	<1.00	6.28	23.74	37.01
206	MMDB-06/02	64.13	64.70	0.57	217.03	<1.00	16.07	25.91	26.92
207	MMDB-06/03	64.70	65.20	0.50	224.90	<1.00	9.39	24.11	62.93
208	MMDB-06/04	93.64	94.64	1.00	212.96	<1.00	34.60	15.68	49.96
209	MMDB-06/05	99.40	100.18	0.78	290.27	<1.00	20.12	6.83	16.71
210	MMDB-06/06	100.18	100.92	0.74	281.33	<1.00	3.22	2.70	31.65
211	MMDB-06/07	100.92	101.90	0.98	289.77	<1.00	18.10	28.98	96.22
212	MMDB-06/08	101.90	102.87	0.97	267.32	<1.00	7.64	1.19	40.81
213	MMDB-06/09	102.87	103.87	1.00	312.76	<1.00	84.42	4.16	35.17
214	MMDB-06/10	107.24	108.22	0.98	188.37	<1.00	4.06	16.03	41.75
215	MMDB-06/11	108.22	109.19	0.97	298.97	<1.00	36.47	18.85	2.27
216	MMDB-06/12	109.19	110.00	0.81	154.79	<1.00	14.44	8.53	35.70
217	MMDB-06/13	110.00	111.84	1.84	207.84	<1.00	13.64	18.61	52.77
218	MMDB-06/14	111.84	113.00	1.16	9.56	<1.00	43.74	15.55	<1.00
219	MMDB-06/15	113.00	113.93	0.93	5.11	<1.00	20.99	15.70	28.82
220	MMDB-06/16	113.93	114.73	0.80	8.19	<1.00	9.78	8.61	55.38
221	MMDB-07/01	89.23	90.16	0.93	2.72	<1.00	22.00	3.69	17.44
222	MMDB-07/02	90.16	91.11	0.95	2.67	<1.00	52.63	5.00	9.79
223	MMDB-07/03	91.11	92.15	1.04	3.20	<1.00	23.46	5.43	<1.00
224	MMDB-07/04	92.15	93.32	1.17	7.68	<1.00	31.37	11.55	7.07
225	MMDB-07/05	93.32	94.27	0.95	4.49	<1.00	14.27	7.32	<1.00
226	MMDB-07/06	94.27	95.22	0.95	5.34	<1.00	6.65	4.10	1.34
227	MMDB-07/07	95.22	96.17	0.95	5.28	<1.00	15.78	3.24	<1.00
228	MMDB-07/08	96.17	97.11	0.94	4.77	<1.00	32.30	<1.00	5.26
229	MMDB-07/09	97.11	98.09	0.98	6.14	<1.00	59.22	3.29	<1.00
230	MMDB-07/10	98.09	99.00	0.91	5.58	<1.00	8.76	1.86	2.96
231	MMDB-07/11	99.00	99.95	0.95	3.23	<1.00	71.67	3.93	<1.00
232	MMDB-07/12	99.95	100.87	0.92	8.01	<1.00	16.13	2.03	1.20
233	MMDB-07/13	100.87	101.80	0.93	5.13	<1.00	12.97	3.39	<1.00
234	MMDB-07/14	101.80	102.79	0.99	354.20	<1.00	13.40	1.68	12.72
235	MMDB-07/15	102.79	103.81	1.02	386.04	<1.00	4.26	2.36	14.45
236	MMDB-07/16	103.81	104.84	1.03	302.22	<1.00	2.00	2.38	15.45
237	MMDB-07/17	104.84	105.80	0.96	352.35	<1.00	4.12	5.85	7.27

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To		Primary Analysis PPM (DL = 1 PPM)				
238	MMDB-07/18	105.80	106.78	0.98	383.66	<1.00	3.76	4.78	16.09
239	MMDB-07/19	106.78	107.75	0.97	311.04	<1.00	3.18	7.26	8.46
240	MMDB-07/20	107.75	108.67	0.92	299.67	<1.00	13.33	6.54	15.84
241	MMDB-07/21	108.67	109.60	0.93	264.77	<1.00	17.34	7.73	20.17
242	MMDB-07/22	109.60	110.52	0.92	249.96	<1.00	27.50	3.01	18.69
243	MMDB-07/23	110.52	111.42	0.90	309.43	<1.00	8.02	5.46	15.48
244	MMDB-07/24	111.42	112.32	0.90	307.32	<1.00	12.05	8.68	25.92
245	MMDB-07/25	112.32	113.22	0.90	305.68	<1.00	4.80	9.62	39.78
246	MMDB-07/26	113.22	114.15	0.93	293.27	<1.00	5.48	5.77	36.96
247	MMDB-07/27	114.15	115.08	0.93	255.63	<1.00	2.86	7.24	17.60
248	MMDB-07/28	115.08	116.03	0.95	362.79	<1.00	7.52	5.83	26.07
249	MMDB-07/29	116.03	117.00	0.97	221.66	<1.00	2.31	1.04	40.95
250	MMDB-07/30	117.00	117.98	0.98	183.45	<1.00	1.92	<1.00	37.76
251	MMDB-07/31	117.98	118.90	0.92	194.20	<1.00	3.00	<1.00	32.64
252	MMDB-07/32	118.90	119.86	0.96	139.62	<1.00	10.13	1.61	44.14
253	MMDB-07/33	119.86	120.80	0.94	159.46	<1.00	4.38	3.71	40.25
254	MMDB-07/34	120.80	121.71	0.91	10.78	<1.00	3.72	4.50	31.31
255	MMDB-07/35	121.71	122.70	0.99	144.43	<1.00	4.11	6.95	36.21
256	MMDB-07/36	122.70	123.70	1.00	149.66	<1.00	8.17	6.57	21.86
257	MMDB-07/37	123.70	124.45	0.75	130.06	<1.00	21.43	10.66	25.74
258	MMDB-07/38	124.45	125.00	0.55	315.47	<1.00	7.45	6.65	<1.00
259	MMDB-08/01	67.00	68.00	1.00	254.80	<1.00	34.56	6.35	16.40
260	MMDB-08/02	68.00	69.00	1.00	346.48	<1.00	20.26	7.64	15.19
261	MMDB-08/03	69.00	70.00	1.00	366.09	<1.00	16.87	8.57	10.75
262	MMDB-08/04	70.00	71.00	1.00	366.30	<1.00	14.48	10.94	7.98
263	MMDB-08/05	71.00	72.06	1.06	362.28	<1.00	13.00	5.66	4.62
264	MMDB-08/06	72.06	73.00	0.94	327.92	<1.00	7.45	3.44	4.71
265	MMDB-08/07	73.00	74.01	1.01	232.60	<1.00	13.37	13.13	1.11
266	MMDB-08/08	74.01	75.00	0.99	227.30	<1.00	8.05	8.44	<1.00
267	MMDB-08/09	75.00	76.00	1.00	15.08	<1.00	8.91	16.62	<1.00
268	MMDB-08/10	76.00	77.00	1.00	10.64	<1.00	10.71	7.65	<1.00
269	MMDB-08/11	77.00	78.00	1.00	4.84	<1.00	19.32	10.15	13.74
270	MMDB-08/12	78.00	79.00	1.00	7.93	<1.00	12.55	39.80	<1.00
271	MMDB-08/13	79.00	80.00	1.00	10.22	<1.00	13.00	38.79	<1.00
272	MMDB-08/14	80.00	81.00	1.00	9.43	<1.00	4.98	9.80	7.78
273	MMDB-08/15	81.00	81.91	0.91	4.57	<1.00	4.46	37.91	14.58
274	MMDB-08/16	81.91	82.88	0.97	435.30	<1.00	1.95	28.49	<1.00
275	MMDB-08/17	82.88	83.79	0.91	298.47	<1.00	1.43	15.12	6.08
276	MMDB-08/18	83.79	84.73	0.94	455.39	<1.00	4.39	18.55	9.91
277	MMDB-08/19	84.73	85.72	0.99	378.67	<1.00	3.66	9.32	<1.00
278	MMDB-08/20	85.72	86.76	1.04	290.42	<1.00	16.13	13.24	<1.00

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To		Primary Analysis PPM (DL = 1 PPM)				
279	MMDB-08/21	86.76	87.76	1.00	302.42	<1.00	14.48	27.73	7.06
280	MMDB-08/22	87.76	88.82	1.06	327.32	<1.00	4.30	13.61	<1.00
281	MMDB-08/23	88.82	89.65	0.83	19.87	<1.00	9.13	22.22	3.23
282	MMDB-08/24	89.65	90.55	0.90	1.09	4.62	46.90	82.07	51.42
283	MMDB-08/25	90.55	91.47	0.92	3.42	4.85	15.39	10.55	11.72
284	MMDB-08/26	91.47	92.20	0.73	309.37	6.95	13.45	8.41	8.16
285	MMDB-08/27	92.20	93.11	0.91	155.37	2.17	4.09	4.59	42.32
286	MMDB-08/28	93.11	94.42	1.31	6.01	7.50	5.61	4.55	<1.00
287	MMDB-08/29	94.42	95.25	0.83	9.17	4.50	26.83	16.23	<1.00
288	MMDB-08/30	95.25	96.00	0.75	262.28	7.54	16.14	6.18	<1.00
289	MMDB-08/31	96.00	96.92	0.92	130.35	4.05	40.67	<1.00	<1.00
290	MMDB-08/32	96.92	97.89	0.97	226.86	5.24	28.54	5.36	<1.00
291	MMDB-08/33	97.89	99.00	1.11	315.63	5.41	11.18	7.77	<1.00
292	MMDB-08/34	99.00	100.07	1.07	236.32	5.08	19.43	11.51	<1.00
293	MMDB-08/35	100.07	101.05	0.98	303.45	3.01	5.57	<1.00	<1.00
294	MMDB-08/36	101.05	102.00	0.95	239.92	3.62	3.16	5.36	23.00
295	MMDB-08/37	102.00	102.93	0.93	216.02	1.67	1.02	4.36	<1.00
296	MMDB-08/38	111.72	112.75	1.03	318.16	1.09	4.26	12.13	33.42
297	MMDB-08/39	112.75	114.00	1.25	322.91	3.49	20.81	27.89	<1.00
298	MMDB-08/40	114.00	115.00	1.00	374.14	4.81	9.49	34.71	<1.00
299	MMDB-08/41	115.00	118.00	3.00	122.63	<1.00	21.13	13.05	6.03
300	MMDB-08/42	118.00	119.00	1.00	221.17	<1.00	14.41	6.36	29.17
301	MMDB-08/43	119.00	120.00	1.00	266.24	1.41	10.25	7.16	21.47
302	MMDB-08/44	120.00	120.96	0.96	<1.0	2.67	5.11	<1.00	20.40
303	MMDB-08/45	120.96	121.90	0.94	<1.0	<1.00	24.18	5.88	13.88
304	MMDB-08/46	121.90	122.80	0.90	1.66	1.17	17.48	3.33	13.25
305	MMDB-08/47	122.80	123.68	0.88	1.02	1.88	17.68	21.00	<1.00
306	MMDB-08/48	123.68	124.67	0.99	<1.0	1.01	9.58	11.08	33.49
307	MMDB-08/49	124.67	125.58	0.91	<1.0	1.45	12.63	5.14	29.06
308	MMDB-08/50	125.58	126.39	0.81	8.59	2.99	11.56	2.70	14.64
309	MMDB-08/51	126.39	127.29	0.90	232.65	2.84	3.24	<1.00	27.14
310	MMDB-08/52	127.29	128.00	0.71	256.59	1.23	5.30	5.40	59.86
311	MMDB-08/53	128.00	128.90	0.90	256.62	2.37	5.18	10.57	38.89
312	MMDB-08/54	128.90	129.85	0.95	271.40	1.94	1.19	6.77	44.76
313	MMDB-08/55	129.85	130.80	0.95	250.32	1.47	9.68	13.74	44.97
314	MMDB-08/56	130.80	131.69	0.89	232.30	3.87	5.02	10.37	31.48
315	MMDB-08/57	131.69	132.70	1.01	245.71	4.87	15.15	5.84	47.15
316	MMDB-08/58	132.70	133.60	0.90	260.90	4.41	3.79	2.55	34.27
317	MMDB-08/59	133.60	134.55	0.95	61.97	2.29	2.93	<1.00	15.30
318	MMDB-08/60	134.55	135.50	0.95	70.79	4.18	15.11	2.86	<1.00
319	MMDB-08/61	135.50	136.46	0.96	52.37	4.36	8.10	21.08	<1.00

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To		Primary Analysis PPM (DL = 1 PPM)				
320	MMDB-08/62	136.46	137.40	0.94	5.03	4.47	20.46	<1.00	<1.00
321	MMDB-08/63	137.40	138.33	0.93	411.60	2.97	20.60	10.40	73.76
322	MMDB-08/64	138.33	139.30	0.97	317.80	3.63	7.27	<1.00	<1.00
323	MMDB-08/65	139.30	140.25	0.95	8.68	4.25	5.42	1.68	<1.00
324	MMDB-08/66	140.25	141.22	0.97	4.25	4.33	6.46	3.30	<1.00
325	MMDB-08/67	141.22	142.15	0.93	5.34	4.65	2.95	<1.00	<1.00
326	MMDB-08/68	142.15	143.10	0.95	440.66	4.82	1.72	2.76	<1.00
327	MMDB-08/69	143.10	144.03	0.93	323.27	3.16	2.48	<1.00	<1.00
328	MMDB-08/70	144.03	144.97	0.94	264.64	5.00	2.42	<1.00	<1.00
329	MMDB-08/71	144.97	145.90	0.93	333.35	<1.0	9.00	1.08	16.96
330	MMDB-08/72	145.90	146.85	0.95	258.96	<1.0	18.62	4.30	39.18
331	MMDB-08/73	146.85	148.00	1.15	212.76	<1.0	24.31	6.32	61.49
332	MMDB-08/74	148.00	149.00	1.00	234.59	<1.0	15.10	9.10	49.13
333	MMDB-09/01	13.69	14.42	0.73	3.57	4.57	20.69	22.54	76.35
334	MMDB-09/02	15.53	16.28	0.75	42.18	1.12	127.22	169.19	81.09
335	MMDB-09/03	16.28	17.03	0.75	23.23	2.43	79.53	34.56	82.11
336	MMDB-09/04	17.03	18.00	0.97	4.34	1.52	41.81	16.47	77.26
337	MMDB-09/05	18.00	18.98	0.98	1.19	2.39	51.13	13.61	74.97
338	MMDB-09/06	18.98	19.51	0.53	4.82	2.92	49.90	10.38	69.37
339	MMDB-09/07	19.51	19.99	0.48	30.30	3.67	60.03	13.18	70.50
340	MMDB-09/08	19.99	20.50	0.51	4.58	5.58	59.66	17.52	82.13
341	MMDB-09/09	20.50	21.00	0.50	134.67	6.44	96.08	22.56	78.86
342	MMDB-09/10	21.00	21.47	0.47	285.52	5.02	250.96	20.20	73.28
343	MMDB-09/11	21.47	21.95	0.48	107.43	6.84	141.00	22.03	66.71
344	MMDB-09/12	21.95	22.48	0.53	141.02	8.15	84.87	22.98	62.33
345	MMDB-09/13	22.48	22.97	0.49	116.99	9.53	63.75	20.37	81.25
346	MMDB-09/14	22.97	23.50	0.53	123.20	6.45	57.00	18.07	73.80
347	MMDB-09/15	23.50	24.00	0.50	146.32	4.38	147.65	19.27	74.54
348	MMDB-09/16	24.00	24.49	0.49	15.62	4.76	41.16	18.60	64.57
349	MMDB-09/17	24.49	24.98	0.49	202.85	4.03	85.32	19.44	80.93
350	MMDB-09/18	24.98	25.50	0.52	53.56	6.79	101.48	24.26	69.29
351	MMDB-09/19	25.50	25.96	0.46	221.55	6.81	158.71	25.46	97.49
352	MMDB-09/20	25.96	26.46	0.50	238.34	4.37	228.00	21.90	109.02
353	MMDB-09/21	26.46	26.93	0.47	237.83	6.18	205.78	28.28	92.58
354	MMDB-09/22	26.93	27.42	0.49	160.62	6.22	70.37	17.59	91.23
355	MMDB-09/23	27.42	27.88	0.46	204.96	8.05	48.70	31.31	87.25
356	MMDB-09/24	27.88	28.50	0.62	179.66	9.05	51.82	30.71	89.96
357	MMDB-09/25	28.50	29.56	1.06	218.30	4.27	149.81	35.63	104.18
358	MMDB-09/26	29.56	30.30	0.74	180.71	3.57	226.34	35.76	152.11
359	MMDB-09/27	30.30	30.90	0.60	177.05	3.13	113.19	27.93	95.47
360	MMDB-09/28	30.90	31.50	0.60	202.74	3.99	57.98	29.33	92.72

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To		Primary Analysis PPM (DL = 1 PPM)				
361	MMDB-09/29	31.50	32.15	0.65	90.20	4.20	162.85	26.72	88.03
362	MMDB-09/30	32.15	32.86	0.71	240.16	5.79	194.66	35.16	84.20
363	MMDB-09/31	32.86	33.50	0.64	221.93	6.18	133.58	34.65	94.80
364	MMDB-09/32	33.50	34.50	1.00	79.75	2.44	180.01	25.17	84.68
365	MMDB-09/33	34.50	35.04	0.54	185.35	2.66	286.27	23.51	75.24
366	MMDB-09/34	35.04	35.69	0.65	127.42	3.65	129.75	25.32	81.17
367	MMDB-09/35	35.69	36.67	0.98	23.54	2.52	48.74	14.95	61.63
368	MMDB-09/36	36.67	37.66	0.99	142.06	1.97	157.51	19.56	91.06
369	MMDB-09/37	37.66	38.41	0.75	174.39	4.33	128.89	28.72	84.96
370	MMDB-09/38	38.41	39.00	0.59	161.59	2.31	101.03	18.53	80.75
371	MMDB-09/39	39.00	39.64	0.64	118.98	<1.0	64.84	13.53	62.50
372	MMDB-09/40	39.64	40.33	0.69	158.15	1.05	88.58	20.62	65.18
373	MMDB-09/41	40.33	41.20	0.87	153.30	1.02	69.66	13.46	85.79
374	MMDB-09/42	41.20	41.75	0.55	128.03	<1.0	95.19	14.96	81.95
375	MMDB-09/43	41.75	42.52	0.77	109.54	1.02	65.57	18.36	87.38
376	MMDB-09/44	42.52	43.51	0.99	149.24	2.70	111.92	20.22	88.14
377	MMDB-09/45	43.51	44.53	1.02	135.91	1.92	134.06	13.09	83.30
378	MMDB-09/46	44.53	45.47	0.94	106.38	1.12	73.50	9.12	75.70
379	MMDB-09/47	45.47	46.43	0.96	112.88	1.61	44.58	5.22	64.71
380	MMDB-09/48	46.43	47.38	0.95	133.29	2.71	89.03	7.74	56.20
381	MMDB-09/49	47.38	48.26	0.88	119.12	1.58	101.00	5.14	64.71
382	MMDB-09/50	48.26	49.15	0.89	158.23	1.26	16.26	<1.0	64.47
383	MMDB-09/51	49.15	50.08	0.93	158.31	1.45	10.39	2.08	57.87
384	MMDB-09/52	50.08	51.00	0.92	155.66	1.78	20.05	4.76	58.35
385	MMDB-09/53	51.00	51.90	0.90	392.96	<1.0	19.78	4.20	25.63
386	MMDB-09/54	51.90	52.84	0.94	211.57	<1.0	42.62	5.53	43.07
387	MMDB-09/55	52.84	53.68	0.84	156.95	1.03	16.61	5.50	55.50
388	MMDB-09/56	54.85	55.78	0.93	216.86	1.05	9.88	3.89	38.49
389	MMDB-09/57	55.78	56.68	0.90	311.69	<1.0	6.91	2.85	32.88
390	MMDB-09/58	56.68	57.56	0.88	345.35	<1.0	7.96	2.87	24.72
391	MMDB-09/59	57.56	58.46	0.90	409.63	1.04	13.53	16.13	24.55
392	MMDB-09/60	58.46	59.36	0.90	343.23	1.05	15.28	3.18	40.31
393	MMDB-09/61	59.36	60.24	0.88	339.16	<1.0	24.39	2.40	32.79
394	MMDB-09/62	60.24	61.12	0.88	325.58	<1.0	13.38	2.43	28.67
395	MMDB-09/63	61.12	62.24	1.12	5.47	1.17	25.52	6.17	35.23
396	MMDB-09/64	62.24	63.00	0.76	211.62	<1.0	3.95	1.24	15.20
397	MMDB-09/65	63.00	63.96	0.96	245.48	<1.0	2.39	1.59	9.21
398	MMDB-09/66	63.96	64.99	1.03	369.70	<1.0	4.23	1.60	41.77
399	MMDB-09/67	64.99	66.00	1.01	270.48	<1.0	8.70	1.83	8.04
400	MMDB-09/68	66.00	67.02	1.02	255.40	<1.0	3.55	2.80	25.39
401	MMDB-09/69	67.02	68.02	1.00	8.35	<1.0	3.46	2.41	16.23

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To						
402	MMDB-09/70	68.02	69.00	0.98	368.82	<1.0	2.52	<1.0	102.38
403	MMDB-09/71	69.00	70.00	1.00	6.34	<1.0	3.04	2.24	15.53
404	MMDB-09/72	70.00	71.00	1.00	4.67	<1.0	4.17	1.70	20.84
405	MMDB-09/73	71.00	72.00	1.00	7.74	<1.0	3.33	1.56	19.91
406	MMDB-09/74	72.00	72.99	0.99	3.90	<1.0	5.73	1.94	33.27
407	MMDB-09/75	72.99	74.02	1.03	14.28	<1.0	3.48	<1.0	10.50
408	MMDB-09/76	74.02	75.00	0.98	4.39	<1.0	4.95	1.40	12.33
409	MMDB-09/77	75.00	75.98	0.98	6.40	<1.0	4.92	2.61	12.84
410	MMDB-09/78	75.98	76.92	0.94	8.99	<1.0	6.56	13.88	18.22
411	MMDB-09/79	76.92	77.85	0.93	7.60	<1.0	3.24	1.06	6.93
412	MMDB-09/80	77.85	78.74	0.89	375.93	<1.0	3.85	<1.0	10.03
413	MMDB-09/81	78.74	79.77	1.03	10.07	<1.0	3.13	1.16	5.00
414	MMDB-09/82	79.77	80.81	1.04	392.61	<1.0	5.49	5.91	6.60
415	MMDB-09/83	80.81	81.74	0.93	363.27	<1.0	3.78	<1.0	4.91
416	MMDB-09/84	81.74	82.69	0.95	393.29	<1.0	3.68	<1.0	11.20
417	MMDB-09/85	82.69	83.65	0.96	327.62	<1.0	4.00	<1.0	33.17
418	MMDB-09/86	83.65	84.61	0.96	366.71	<1.0	3.01	<1.0	11.94
419	MMDB-09/87	84.61	85.94	1.33	344.20	<1.0	3.28	<1.0	25.93
420	MMDB-10/01	66.00	66.95	0.95	360.72	<1.0	12.54	16.72	14.15
421	MMDB-10/02	66.95	68.11	1.15	240.05	<1.0	22.21	14.02	23.71
422	MMDB-10/03	68.11	69.13	1.02	64.02	<1.0	39.34	6.83	26.93
423	MMDB-10/04	69.13	70.18	1.05	114.13	1.09	111.21	44.96	31.98
424	MMDB-10/05	70.18	71.38	1.20	130.58	<1.0	101.32	12.41	54.45
425	MMDB-10/06	73.13	74.36	1.23	<1.0	<1.0	26.72	<1.0	11.88
426	MMDB-10/07	75.08	76.05	0.97	2.44	<1.0	3.57	30.84	27.73
427	MMDB-10/08	76.05	77.03	0.98	2.37	<1.0	4.51	5.75	37.68
428	MMDB-10/09	77.03	78.00	0.97	<1.0	<1.0	18.64	22.00	13.30
429	MMDB-10/10	78.00	78.98	0.98	7.95	<1.0	150.82	127.69	31.96
430	MMDB-10/11	78.98	80.00	1.02	361.99	<1.0	108.48	259.68	8.72
431	MMDB-10/12	80.00	80.75	0.75	504.54	<1.0	180.93	282.51	1.09
432	MMDB-10/13	80.75	81.48	0.73	279.81	<1.0	62.66	102.57	21.01
433	MMDB-10/14	81.48	82.28	0.80	100.51	<1.0	18.03	43.27	61.12
434	MMDB-10/15	82.28	82.75	0.47	471.38	<1.0	15.52	43.24	10.66
435	MMDB-10/16	84.00	84.90	0.90	255.22	<1.0	34.66	40.54	64.46
436	MMDB-10/17	84.90	85.91	1.01	196.17	<1.0	17.50	68.25	42.18
437	MMDB-10/18	85.91	86.89	0.98	145.93	<1.0	18.27	9.56	80.50
438	MMDB-10/19	86.89	87.92	1.03	264.35	<1.0	21.27	29.27	35.03
439	MMDB-10/20	87.92	88.93	1.01	287.47	<1.0	10.59	27.47	18.76
440	MMDB-10/21	88.93	89.92	0.99	264.75	<1.0	21.65	34.30	27.28
441	MMDB-10/22	89.92	90.89	0.97	171.49	<1.0	35.01	8.18	59.99
442	MMDB-10/23	90.89	91.88	0.99	132.95	<1.0	48.98	7.77	48.26



ANNEXURE- III-A/12

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To		Primary Analysis PPM (DL = 1 PPM)				
443	MMDB-10/24	91.88	92.87	0.99	2.95	<1.0	28.29	3.70	55.11
444	MMDB-10/25	92.87	93.86	0.99	3.95	<1.0	6.87	12.38	28.81
445	MMDB-10/26	93.86	94.88	1.02	2.20	<1.0	7.52	21.52	3.84
446	MMDB-10/27	94.88	96.00	1.12	6.19	<1.0	8.28	12.19	5.94
447	MMDB-10/28	96.00	96.82	0.82	4.69	<1.0	14.76	5.85	37.80
448	MMDB-10/29	96.82	97.80	0.98	1.77	<1.0	6.66	4.17	25.24
449	MMDB-10/30	97.80	98.78	0.98	182.27	<1.0	12.73	3.48	37.90
450	MMDB-10/31	98.78	99.70	0.92	<1.0	<1.0	18.86	2.73	39.60
451	MMDB-10/32	99.70	100.20	0.50	19.42	<1.0	28.57	<1.0	90.40
452	MMDB-10/33	100.20	101.14	0.94	4.02	<1.0	22.42	7.73	41.12
453	MMDB-10/34	101.14	102.00	0.86	<1.0	<1.0	47.39	14.51	63.52
454	MMDB-10/35	102.00	102.65	0.65	<1.0	<1.0	23.02	5.56	85.96
455	MMDB-10/36	102.65	103.32	0.67	8.42	<1.0	12.14	65.97	36.10
456	MMDB-10/37	103.32	104.07	0.75	4.13	<1.0	7.76	124.69	27.61
457	MMDB-10/38	105.69	106.53	0.84	1.02	<1.0	14.31	33.68	23.90
458	MMDB-10/39	106.53	107.48	0.95	23.78	<1.0	12.72	18.44	30.12
459	MMDB-10/40	107.48	108.42	0.94	215.31	<1.0	10.05	38.55	4.47
460	MMDB-10/41	108.42	109.41	0.99	28.30	<1.0	22.37	14.61	33.79
461	MMDB-10/42	109.41	110.40	0.99	5.93	<1.0	10.48	141.20	25.77
462	MMDB-10/43	110.40	111.36	0.96	3.17	<1.0	11.28	11.90	24.56
463	MMDB-10/44	111.36	112.36	1.00	145.42	<1.0	28.04	12.79	343.36
464	MMDB-10/45	112.36	113.33	0.97	271.73	<1.0	8.69	11.50	23.46
465	MMDB-10/46	113.33	114.34	1.01	228.94	<1.0	26.60	12.25	46.38
466	MMDB-10/47	114.34	115.37	1.03	308.09	<1.0	32.92	10.32	25.40
467	MMDB-10/48	115.37	116.39	1.02	297.49	<1.0	24.95	19.54	22.79
468	MMDB-10/49	116.39	117.32	0.93	338.51	<1.0	11.04	9.00	8.12
469	MMDB-10/50	117.32	118.33	1.01	586.63	<1.0	10.42	53.85	21.93
470	MMDB-10/51	118.33	119.33	1.00	431.46	<1.0	41.39	47.01	1.46
471	MMDB-10/52	119.33	120.32	0.99	10.33	<1.0	75.81	24.00	<1.0
472	MMDB-10/53	120.32	121.31	0.99	123.91	<1.0	20.42	46.21	17.50
473	MMDB-10/54	121.31	122.24	0.93	61.38	<1.0	10.16	13.91	47.30
474	MMDB-11/01	10.74	11.51	0.77	358.72	<1.0	7.74	4.16	3.01
475	MMDB-11/02	11.51	12.00	0.49	311.63	<1.0	14.84	15.47	5.40
476	MMDB-11/03	32.90	34.10	1.20	246.87	<1.0	5.64	5.63	<1.0
477	MMDB-11/04	34.10	35.00	0.90	283.44	<1.0	39.51	22.25	<1.0

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To		Primary Analysis PPM (DL = 1 PPM)				
478	MMDB-11/05	35.00	35.93	0.93	230.96	<1.0	87.13	25.79	<1.0
479	MMDB-11/06	35.93	37.00	1.07	337.69	<1.0	20.60	11.91	<1.0
480	MMDB-11/07	37.00	37.84	0.84	302.58	<1.0	31.87	9.61	<1.0
481	MMDB-11/08	37.84	38.80	0.96	350.57	<1.0	18.94	13.95	2.25
482	MMDB-11/09	38.80	39.75	0.95	337.34	<1.0	28.52	17.57	<1.0
483	MMDB-11/10	39.75	40.72	0.97	438.39	<1.0	18.98	3.37	<1.0
484	MMDB-11/11	40.72	41.71	0.99	337.41	<1.0	20.07	38.26	29.27
485	MMDB-11/12	41.71	42.67	0.96	313.52	<1.0	16.55	4.99	38.75
486	MMDB-11/13	42.67	43.60	0.93	164.73	<1.0	27.96	5.84	54.38
487	MMDB-11/14	43.60	44.55	0.95	228.84	<1.0	21.40	4.35	29.27
488	MMDB-11/15	44.55	45.44	0.89	194.66	<1.0	11.64	4.30	10.20
489	MMDB-11/16	45.44	46.38	0.94	14.28	<1.0	6.95	5.53	<1.0
490	MMDB-11/17	46.38	47.36	0.98	6.93	<1.0	7.97	6.99	28.51
491	MMDB-11/18	47.36	48.22	0.86	1.41	<1.0	14.38	7.11	81.92
492	MMDB-11/19	48.22	49.12	0.90	20.78	<1.0	18.34	4.44	78.54
493	MMDB-11/20	49.12	50.09	0.97	26.37	<1.00	10.71	2.27	20.12
494	MMDB-11/21	50.09	51.00	0.91	5.01	<1.00	17.71	4.48	19.28
495	MMDB-11/22	51.00	52.04	1.04	21.98	<1.00	8.52	2.75	37.95
496	MMDB-11/23	52.04	53.00	0.96	13.54	<1.00	10.15	4.08	10.32
497	MMDB-11/24	53.00	54.00	1.00	16.22	<1.00	4.67	11.93	<1.00
498	MMDB-11/25	54.00	55.00	1.00	12.17	<1.00	5.06	8.33	3.17
499	MMDB-11/26	55.00	56.00	1.00	153.79	<1.00	5.71	4.80	<1.00
500	MMDB-11/27	56.00	57.00	1.00	281.75	<1.00	16.11	6.36	<1.00
501	MMDB-11/28	57.00	58.00	1.00	212.62	<1.00	12.16	5.15	<1.00
502	MMDB-11/29	58.00	59.00	1.00	167.25	<1.00	5.04	4.55	1.09
503	MMDB-11/30	59.00	60.00	1.00	91.05	<1.00	9.39	5.39	5.69
504	MMDB-11/31	60.00	61.00	1.00	77.23	<1.00	19.84	3.46	1.22
505	MMDB-11/32	61.00	62.00	1.00	84.79	<1.00	20.55	9.04	1.09
506	MMDB-11/33	62.00	63.00	1.00	165.26	<1.00	17.98	4.48	<1.00
507	MMDB-11/34	63.00	64.00	1.00	288.22	<1.00	15.16	3.15	<1.00
508	MMDB-11/35	64.00	65.00	1.00	362.64	<1.00	20.17	3.38	<1.00
509	MMDB-11/36	65.00	66.00	1.00	271.66	<1.00	31.32	2.27	1.10
510	MMDB-11/37	66.00	67.00	1.00	309.75	<1.00	26.25	4.56	15.60
511	MMDB-11/38	67.00	68.00	1.00	230.40	<1.00	9.91	7.47	<1.00
512	MMDB-11/39	68.00	69.00	1.00	242.59	<1.00	12.24	2.98	11.90
513	MMDB-11/40	69.00	70.00	1.00	390.81	<1.00	8.69	3.46	<1.00
514	MMDB-11/41	70.00	71.00	1.00	314.24	<1.00	20.42	1.63	<1.00
515	MMDB-11/42	71.00	72.00	1.00	416.40	<1.00	8.61	<1.00	<1.00
516	MMDB-11/43	72.00	73.00	1.00	390.14	<1.00	21.74	5.64	<1.00
517	MMDB-11/44	73.00	74.00	1.00	31.49	<1.00	19.36	3.46	<1.00
518	MMDB-11/45	74.00	75.00	1.00	11.19	<1.00	25.91	3.81	<1.00

Sr.No.	Borehole with Sample No.	Intersection Depth (m)		Thick-ness (m)	W	Sn	Cu	Pb	Zn
		From	To		Primary Analysis PPM (DL = 1 PPM)				
519	MMDB-11/46	75.00	76.00	1.00	12.05	<1.00	25.21	3.85	<1.00
520	MMDB-11/47	76.00	77.00	1.00	17.00	<1.00	12.22	4.11	<1.00
521	MMDB-11/48	77.00	78.00	1.00	9.10	<1.00	5.29	2.80	<1.00
522	MMDB-11/49	78.00	79.00	1.00	425.73	<1.00	2.93	1.37	<1.00
523	MMDB-11/50	79.00	80.00	1.00	355.99	<1.00	3.07	1.62	<1.00
524	MMDB-11/51	80.00	81.00	1.00	368.01	<1.00	11.18	3.28	<1.00
525	MMDB-11/52	81.00	82.05	1.05	389.13	<1.00	21.67	4.52	<1.00
526	MMDB-11/53	82.05	83.03	0.98	422.14	<1.00	10.03	3.99	<1.00
527	MMDB-11/54	83.03	84.00	0.97	316.05	<1.00	7.30	4.30	<1.00
528	MMDB-11/55	84.00	85.00	1.00	174.82	<1.00	5.17	4.98	10.39
529	MMDB-11/56	85.00	86.00	1.00	213.30	<1.00	7.72	7.68	5.58
530	MMDB-11/57	86.00	87.00	1.00	214.35	<1.00	42.46	2.52	2.98
531	MMDB-11/58	87.00	88.00	1.00	312.81	<1.00	67.45	3.78	<1.00
532	MMDB-11/59	88.00	89.00	1.00	320.15	<1.00	17.09	1.30	<1.00
533	MMDB-11/60	89.00	90.00	1.00	130.03	<1.00	39.44	2.05	23.44
534	MMDB-11/61	90.00	91.50	1.50	122.08	<1.00	150.38	18.02	18.89
535	MMDB-11/62	91.50	93.00	1.50	179.44	<1.00	64.34	3.31	14.16