

**SWELLING INDEX TEST & LOW TEMPERATURE GRAY KING ASSAY (LTGK) TEST RESULTS OF
BOREHOLES COAL CORES OF WEST OF URDHAN JAMUNIA BLOCK, , PENCH KANHAN TAWA VALLEY
COALFIELD, DISTRICT-CHHINDWARA, MADHYA PRADESH.**

Borehole No.	SEAM	From	To	Thickness	Sample Type	Coking Test	
						SI	LTGK
CMPWU03	IA	622.49	622.89	0.40	BCSH/I30	0	A
CMPWU03	IB	626.36	627.62	1.26	BCSH/I30	0	A
CMPWU03	IC	628.06	630.37	2.31	BCSH/I30	0	A
CMPWU03	IIA	632.88	635.00	2.12	BCSH/I30	0	A
CMPWU03	IIB	637.81	639.20	1.39	BCSH/I30	0	A
CMPWU03	III	648.30	651.42	3.12	BCSH/I30	0	A
CMPWU03	IV	654.46	657.38	2.92	BCSH/I30	½	A
CMPWU03	VA	659.79	660.72	0.93	BCSH/I30	0	A
CMPWU03	VB	665.97	666.47	0.50	BCSH/I30	0	A
CMPWU-05	IV	676.70	679.76	3.06	BCSH/I30	0	A