



TEST REPORT

TEST REPORT NO. BSS/120/0811-0817 ULR – TC152622600000120F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 02.02.2026	Date of Test End: 05.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 07 No. & 100 gm Each
			Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
Packing of Sample	Paper Pouch		Sample collected and prepared by By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-1/S-1(4.00-5.00M)		15.46	38.98	5.12	1.39	2.41	0.17	0.38	0.39	0.07	0.07	0.06	35.50
2.	BH-1/S-2(5.00-6.00M)		16.53	37.36	5.73	1.20	2.28	0.14	0.36	0.31	0.04	0.05	0.06	35.93
3.	BH-1/S-3(6.00-7.00M)		18.84	34.86	6.94	1.30	2.16	0.14	0.34	0.30	0.03	0.04	0.05	34.94
4.	BH-1/S-4(7.00-8.00M)		17.35	39.16	4.52	0.90	2.03	0.11	0.32	0.24	0.03	0.05	0.05	35.16
5.	BH-1/S-5(8.00-9.00M)		17.43	38.78	4.63	1.10	1.90	0.13	0.33	0.27	0.03	0.04	0.06	35.11
6.	BH-1/S-6 (10.00-11.00M)		20.07	35.40	5.93	1.39	2.41	0.18	0.40	0.43	0.03	0.05	0.06	33.63
7.	BH-1/S-7 (11.00-12.00M)		18.09	36.92	5.83	1.19	2.15	0.14	0.34	0.29	0.03	0.05	0.06	34.89

Remarks:

1. Please see and refer original test for the authenticity of this report.
2. Location of samples as per given information by the Customer.
3. Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



END OF REPORT

Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only



Quality Leads...

TC-15262

CHEMICAL ANALYSIS OF MINERALS & ORES

POLLUTION & ENVIRONMENT PARAMETERS

TEST REPORT

TEST REPORT NO. BSS/121/0818-0824 ULR - TC152622600000121F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 03.02.2026	Date of Test End: 06.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 77 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
			Sample collected and prepared by By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-1/S-8 (12.00-13.00M)		23.20	30.09	9.05	2.09	3.04	0.24	0.45	0.57	0.03	0.04	0.05	31.11
2.	BH-1/S-9 (13.00-14.00M)		24.72	29.64	8.94	2.19	3.17	0.27	0.47	0.65	0.04	0.07	0.05	29.70
3.	BH-1/S-10 (14.00-15.00M)		23.40	30.46	8.64	1.89	2.91	0.22	0.46	0.50	0.04	0.05	0.05	31.37
4.	BH-1/S-11 (15.00-16.00M)		23.40	29.67	9.46	1.99	3.04	0.23	0.49	0.56	0.03	0.04	0.06	31.01
5.	BH-1/S-14 (18.00-19.00M)		22.54	29.95	9.05	1.99	3.04	0.25	0.50	0.62	0.03	0.05	0.06	31.83
6.	BH-1/S-16 (20.00-21.00M)		24.99	28.79	9.14	2.39	3.29	0.29	0.58	0.72	0.04	0.07	0.06	29.61
7.	BH-1/S-24 (28.00-29.00M)		24.98	28.65	8.34	2.09	3.29	0.28	0.52	0.76	0.04	0.05	0.05	30.77

Remarks:

1. Please see and refer original test for the authenticity of this report.
2. Location of samples as per given information by the Customer.
3. Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



END OF REPORT

Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only

Office: **BSS Lab Private Limited**, First Floor, 1338, Vijay Nagar, Kachnar City Road, Jabalpur - 482002 (M.P.), India
Telephone / Fax No. 0761-3581305, Mobile: 09425387402, 09424973438, Email: bsslab.jbp@gmail.com



TEST REPORT

TEST REPORT NO. BSS/122/0825-0832 ULR – TC152622600000122F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 04.02.2026	Date of Test End: 07.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002	Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402	
Name of Sample	LIMESTONE	Received Form and Quantity of Sample	Powder Form 08 No. & 100 gm Each
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Test Required
Packing of Sample	Paper Pouch	Sample collected and prepared by	By Customer

DETAILS OF TEST


S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-2/S-1(4.00-5.00M)		18.56	41.13	1.71	0.60	2.79	0.20	0.33	0.28	0.03	0.07	0.07	34.04
2.	BH-2/S-2(5.00-6.00M)		6.42	50.68	0.91	0.49	1.01	0.13	0.25	0.14	0.02	0.05	0.08	39.63
3.	BH-2/S-3(7.00-8.00M)		7.77	48.24	1.61	0.50	1.27	0.14	0.28	0.17	0.02	0.05	0.08	39.79
4.	BH-2/S-4(8.00-9.00M)		9.59	46.34	3.22	0.50	1.78	0.16	0.28	0.46	0.03	0.06	0.09	37.39
5.	BH-2/S-5 (10.00-11.00M)		10.64	46.76	1.81	0.50	1.65	0.15	0.27	0.25	0.02	0.07	0.07	37.69
6.	BH-2/S-6 (11.00-12.00M)		6.19	50.03	1.61	0.50	1.27	0.14	0.27	0.26	0.02	0.05	0.08	39.58
7.	BH-2/S-7 (12.00-13.00M)		2.97	52.76	0.91	0.40	0.89	0.12	0.27	0.18	0.03	0.04	0.10	41.21
8.	BH-2/S-8 (13.00-14.00M)		5.79	49.09	1.81	0.50	1.14	0.13	0.27	0.25	0.03	0.05	0.08	40.82

Remarks:

1. Please see and refer original test for the authenticity of this report.
2. Location of samples as per given information by the Customer.
3. Sample identification explanations given by the customer.

INDRANEEL DAWANDE
AUTHORIZED SIGNATORY

END OF REPORT



Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any Incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only



Quality Leads...

TC-15262

CHEMICAL ANALYSIS OF MINERALS & ORES

POLLUTION & ENVIRONMENT PARAMETERS

TEST REPORT

TEST REPORT NO. BSS/123/0833-0840 ULR - TC152622600000123F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 05.02.2026	Date of Test End: 09.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 08 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
			Sample collected and prepared by By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID ↓	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₃ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-2/S-9 (14.00-15.00M)		6.67	52.74	1.81	0.59	1.27	0.15	0.30	0.28	0.03	0.07	0.09	36.01
2.	BH-2/S-10 (15.00-16.00M)		8.45	48.10	1.71	0.50	1.14	0.14	0.27	0.20	0.03	0.05	0.07	39.22
3.	BH-2/S-11 (16.00-17.00M)		11.99	42.93	3.92	0.50	2.15	0.18	0.35	0.48	0.02	0.05	0.08	37.32
4.	BH-2/S-12 (17.00-18.00M)		14.74	38.61	5.63	0.50	2.54	0.18	0.37	0.55	0.03	0.07	0.08	36.70
5.	BH-2/S-15 (19.10-19.50M)		19.55	32.19	8.95	1.59	2.54	0.20	0.40	0.46	0.03	0.04	0.10	33.77
6.	BH-2/S-16 (20.00-20.70M)		22.42	31.02	8.54	1.69	2.41	0.19	0.39	0.46	0.03	0.05	0.14	32.45
7.	BH-2/S-17 (20.70-21.00M)		13.19	41.42	4.53	1.10	2.03	0.15	0.35	0.35	0.03	0.07	0.10	36.74
8.	BH-2/S-18 (21.00-21.75M)		24.35	28.11	9.25	2.09	3.29	0.25	0.62	0.66	0.04	0.04	0.39	30.87

Remarks:

- Please see and refer original test for the authenticity of this report.
- Location of samples as per given information by the Customer.
- Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY

END OF REPORT



Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any Incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only

Office: **BSS Lab Private Limited**, First Floor, 1338, Vijay Nagar, Kachnar City Road, Jabalpur - 482002 (M.P.), India
Telephone / Fax No. 0761-3581305, Mobile: 09425387402, 09424973438, Email: bsslab.jbp@gmail.com



Quality Leads...

TC-15262

CHEMICAL ANALYSIS OF MINERALS & ORES

POLLUTION & ENVIRONMENT PARAMETERS

TEST REPORT

TEST REPORT NO. BSS/124/0841-0848 ULR – TC152622600000124F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 06.02.2026	Date of Test End: 10.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 08 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
			Sample collected and prepared by By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID ↓	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-2/S-20 (22.00-23.00M)		22.42	31.30	9.04	0.60	3.55	0.25	0.57	0.75	0.03	0.08	0.12	31.29
2.	BH-2/S-21 (23.00-24.00M)		21.18	30.51	9.56	0.60	3.68	0.26	0.41	0.85	0.03	0.07	0.07	32.80
3.	BH-2/S-22 (24.00-25.00M)		19.03	34.11	8.24	0.50	3.17	0.22	0.39	0.71	0.02	0.07	0.08	33.32
4.	BH-2/S-23 (25.00-26.00M)		19.09	35.95	7.44	0.60	2.41	0.19	0.36	0.45	0.03	0.04	0.08	33.36
5.	BH-2/S-24 (26.00-27.00M)		19.83	32.48	7.95	0.50	2.79	0.20	0.39	0.53	0.03	0.07	0.08	35.10
6.	BH-2/S-25 (27.00-28.00M)		21.48	31.74	9.04	0.60	3.42	0.23	0.39	0.64	0.02	0.08	0.08	32.28
7.	BH-2/S-27 (29.00-29.70M)		23.89	28.10	10.05	2.49	3.42	0.32	0.56	0.79	0.05	0.04	0.10	30.09
8.	BH-2/S-28 (29.70-30.00M)		31.76	18.34	14.39	3.49	4.19	0.44	0.58	0.96	0.07	0.05	0.10	25.71

Remarks:

1. Please see and refer original test for the authenticity of this report.
2. Location of samples as per given information by the Customer.
3. Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



END OF REPORT

Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only

Office: **BSS Lab Private Limited**, First Floor, 1338, Vijay Nagar, Kachnar City Road, Jabalpur - 482002 (M.P.), India
Telephone / Fax No. 0761-3581305, Mobile: 09425387402, 09424973438, Email: bsslab.jbp@gmail.com



TEST REPORT

TEST REPORT NO. BSS/125/0849-0856 ULR - TC152622600000125F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 07.02.2026	Date of Test End: 11.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 08 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
			Sample collected and prepared by
			By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₃ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-4/S-1 (1.00-2.00M)		8.61	47.79	1.21	0.70	1.65	0.14	0.25	0.30	0.01	0.04	0.06	39.19
2.	BH-4/S-2 (2.00-3.00M)		7.56	49.84	1.11	0.60	1.40	0.13	0.25	0.23	0.02	0.05	0.07	38.52
3.	BH-4/S-3 (4.00-5.00M)		12.08	46.30	1.21	0.60	1.65	0.15	0.27	0.32	0.03	0.07	0.07	37.05
4.	BH-4/S-4 (5.00-6.00M)		16.40	38.03	2.61	0.75	3.93	0.20	0.56	0.65	0.03	0.07	0.10	36.56
5.	BH-4/S-5(6.00-7.00M)		8.39	47.51	1.51	0.70	1.39	0.14	0.26	0.29	0.02	0.05	0.07	39.58
6.	BH-4/S-6(7.00-8.00M)		9.21	46.06	2.01	0.70	1.40	0.14	0.27	0.23	0.01	0.05	0.08	39.78
7.	BH-4/S-7(8.00-9.00M)		7.33	49.08	1.00	0.80	1.14	0.13	0.26	0.20	0.03	0.05	0.07	39.83
8.	BH-4/S-8(10.00-11.00M)		12.39	43.16	2.91	0.70	1.77	0.16	0.28	0.40	0.03	0.07	0.06	37.86

Remarks:

1. Please see and refer original test for the authenticity of this report.
2. Location of samples as per given information by the Customer.
3. Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



END OF REPORT

Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only



Quality Leads...

TC-15262

CHEMICAL ANALYSIS OF MINERALS & ORES

POLLUTION & ENVIRONMENT PARAMETERS

TEST REPORT

TEST REPORT NO. BSS/126/0857-0864 ULR - TC152622600000126F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 09.02.2026	Date of Test End: 12.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 1 kg No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required
			SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
			Sample collected and prepared by
			By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₃ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-4/S-9(11.00-12.00M)		8.31	47.60	1.71	0.80	1.40	0.14	0.26	0.27	0.03	0.05	0.07	39.28
2.	BH-4/S-10(13.00-14.00M)		9.45	46.71	2.11	0.70	1.65	0.15	0.29	0.33	0.02	0.05	0.08	38.32
3.	BH-4/S-11(14.00-15.00M)		9.53	45.08	2.72	0.70	1.78	0.14	0.29	0.34	0.03	0.04	0.07	39.13
4.	BH-4/S-12(16.00-17.00M)		9.54	47.87	2.01	0.80	1.39	0.15	0.28	0.27	0.01	0.05	0.08	37.39
5.	BH-4/S-13(17.00-18.00M)		9.56	46.67	2.23	0.70	1.14	0.13	0.26	0.18	0.02	0.05	0.07	38.79
6.	BH-4/S-14(19.00-20.00M)		18.54	37.39	5.13	0.70	1.90	0.16	0.30	0.30	0.02	0.05	0.06	35.26
7.	BH-4/S-15(20.00-21.00M)		20.88	34.10	6.93	0.80	3.42	0.23	0.38	0.71	0.03	0.07	0.07	32.20
8.	BH-4/S-16(21.00-22.00M)		23.20	31.02	8.54	0.80	3.16	0.23	0.37	0.66	0.03	0.08	0.06	31.68

Remarks:

1. Please see and refer original test for the authenticity of this report.
2. Location of samples as per given information by the Customer.
3. Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



END OF REPORT

Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any Incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only

Office: BSS Lab Private Limited, First Floor, 1338, Vijay Nagar, Kachnar City Road, Jabalpur - 482002 (M.P.), India
Telephone / Fax No. 0761-3581305, Mobile: 09425387402, 09424973438, Email: bsslab.jbp@gmail.com



TEST REPORT

TEST REPORT NO. BSS/127/0865-0871 ULR – TC152622600000127F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 10.02.2026	Date of Test End: 13.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 7 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
			Sample collected and prepared by
			By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-4/S-18(23.00-24.00M)		15.96	40.04	4.83	0.70	2.41	0.19	0.33	0.48	0.02	0.05	0.07	34.73
2.	BH-4/S-19(24.00-25.00M)		15.59	37.20	5.43	0.70	2.28	0.18	0.32	0.44	0.03	0.05	0.07	37.52
3.	BH-4/S-20(25.00-26.00M)		13.19	42.80	4.52	0.80	2.15	0.17	0.32	0.40	0.02	0.07	0.07	35.39
4.	BH-4/S-21(26.00-27.00M)		20.20	33.42	7.44	0.80	2.79	0.21	0.36	0.53	0.03	0.07	0.06	34.01
5.	BH-4/S-22(27.00-28.00M)		17.16	37.53	5.84	0.70	2.28	0.18	0.33	0.42	0.03	0.05	0.07	35.35
6.	BH-4/S-23(28.00-29.00M)		16.53	36.90	5.42	0.80	2.28	0.18	0.31	0.43	0.02	0.07	0.06	36.99
7.	BH-4/S-24(29.00-30.00M)		22.68	30.76	8.54	0.80	3.67	0.25	0.40	0.74	0.03	0.08	0.06	31.85

Remarks:

1. Please see and refer original test for the authenticity of this report.
2. Location of samples as per given information by the Customer.
3. Sample identification explanations given by the customer.

INDRANEEL DAWANDE
AUTHORIZED SIGNATORY

END OF REPORT



Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any Incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only



TEST REPORT

TEST REPORT NO. BSS/128/0872-0881 ULR – TC152622600000128F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 11.02.2026	Date of Test End: 14.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No. - 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 10 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
	Sample collected and prepared by		By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₃ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-5/S-1(1.00-2.00M)		6.21	48.97	1.61	0.70	1.65	0.10	0.28	0.15	0.04	0.05	0.07	40.10
2.	BH-5/S-3(4.00-5.00M)		8.51	46.35	2.41	0.70	1.65	0.10	0.30	0.21	0.02	0.07	0.07	39.54
3.	BH-5/S-4(6.00-7.00M)		9.54	44.38	2.31	1.69	2.16	0.22	0.33	0.20	0.03	0.05	0.07	38.98
4.	BH-5/S-5(7.00-8.00M)		9.25	45.99	2.72	0.70	1.78	0.10	0.31	0.26	0.02	0.05	0.07	38.71
5.	BH-5/S-6(8.00-9.00M)		6.79	47.79	2.62	0.80	1.78	0.12	0.27	0.29	0.03	0.07	0.07	39.37
6.	BH-5/S-7(9.00-10.00M)		15.55	41.05	3.62	0.90	1.90	0.12	0.31	0.27	0.03	0.05	0.06	36.02
7.	BH-5/S-8(10.00-11.00M)		11.10	44.70	3.12	0.80	1.65	0.11	0.27	0.21	0.03	0.05	0.06	37.87
8.	BH-5/S-9(11.00-12.00M)		13.02	42.20	3.61	0.90	1.77	0.11	0.29	0.23	0.02	0.07	0.06	37.59
9.	BH-5/S-10(13.00-14.00M)		11.57	41.82	4.52	1.29	2.03	0.19	0.30	0.28	0.03	0.05	0.06	37.74
10.	BH-5/S-11(14.00-15.00M)		6.64	46.63	2.52	0.70	1.52	0.09	0.27	0.19	0.02	0.07	0.06	41.27

Remarks:

- Please see and refer original test for the authenticity of this report.
- Location of samples as per given information by the Customer.
- Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



END OF REPORT

Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any Incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only



TEST REPORT

TEST REPORT NO. BSS/129/0882-0891 ULR - TC152622600000129F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 12.02.2026	Date of Test End: 16.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 10 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
	Sample collected and prepared by		By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-5/S-12(16.00-17.00M)		11.33	41.96	4.32	1.00	2.03	0.14	0.38	0.39	0.03	0.07	0.08	38.25
2.	BH-5/S-13(17.00-18.00M)		14.69	38.39	5.84	1.20	2.28	0.15	0.36	0.50	0.03	0.05	0.06	36.38
3.	BH-5/S-14(18.00-19.00M)		17.47	36.84	5.94	1.50	2.66	0.20	0.37	0.62	0.03	0.05	0.06	34.25
4.	BH-5/S-15(19.00-20.00M)		15.79	39.64	4.83	1.30	2.41	0.18	0.39	0.55	0.03	0.07	0.07	34.71
5.	BH-5/S-16(20.00-21.00M)		17.39	37.91	5.73	1.59	2.79	0.24	0.38	0.69	0.03	0.07	0.07	32.95
6.	BH-5/S-17(21.00-22.00M)		12.57	43.13	3.52	1.10	2.03	0.15	0.32	0.39	0.03	0.05	0.07	36.64
7.	BH-5/S-18(22.00-23.00M)		12.30	42.13	3.82	1.00	2.16	0.15	0.34	0.47	0.02	0.07	0.06	37.43
8.	BH-5/S-19(23.00-24.00M)		9.89	49.81	3.82	1.10	2.28	0.17	0.37	0.50	0.03	0.07	0.09	31.80
9.	BH-5/S-20(24.00-25.00M)		14.55	38.55	5.92	1.19	2.15	0.15	0.36	0.41	0.03	0.05	0.06	36.47
10.	BH-5/S-21(25.00-26.00M)		21.31	32.73	7.84	1.89	2.91	0.232	0.510	0.591	0.035	0.054	0.068	31.80

Remarks:

1. Please see and refer original test for the authenticity of this report.
2. Location of samples as per given information by the Customer.
3. Sample identification explanations given by the customer.



INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



END OF REPORT

Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any Incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only



Quality Leads...

TC-15262

CHEMICAL ANALYSIS OF MINERALS & ORES

POLLUTION & ENVIRONMENT PARAMETERS

TEST REPORT

TEST REPORT NO. BSS/130/0892-0901 ULR - TC152622600000130F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 13.02.2026	Date of Test End: 17.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 10 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required
			SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
			Sample collected and prepared by
			By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-5/S-22(26.00-27.00M)		21.51	30.34	7.03	1.69	3.16	0.205	0.406	0.571	0.026	0.041	0.074	34.94
2.	BH-5/S-23(27.00-28.00M)		16.59	37.48	5.73	1.39	2.66	0.185	0.404	0.555	0.035	0.054	0.142	34.59
3.	BH-5/S-24(28.00-29.00M)		12.49	42.49	4.62	1.49	2.53	0.21	0.37	0.46	0.03	0.07	0.06	35.18
4.	BH-5/S-25(29.00-30.00M)		16.25	38.78	5.23	1.20	2.28	0.16	0.35	0.40	0.03	0.05	0.06	35.19
5.	BH-5/S-27(31.00-32.00M)		16.05	36.84	6.23	1.39	2.53	0.19	0.42	0.46	0.03	0.05	0.06	35.64
6.	BH-5/S-28(32.00-33.00M)		16.86	36.97	6.84	1.79	2.79	0.24	0.43	0.63	0.03	0.07	0.06	33.26
7.	BH-5/S-29(33.00-34.00M)		20.71	32.84	7.84	1.89	2.91	0.25	0.48	0.65	0.03	0.05	0.06	32.18
8.	BH-5/S-30(34.00-35.00M)		18.40	33.98	6.94	1.49	2.66	0.19	0.41	0.56	0.03	0.04	0.05	35.25
9.	BH-5/S-31(35.00-36.00M)		16.13	36.98	6.74	1.30	2.16	0.15	0.37	0.33	0.03	0.05	0.06	35.69
10.	BH-5/S-32(36.00-37.00M)		18.10	34.90	7.54	1.40	2.28	0.20	0.42	0.32	0.04	0.04	0.06	34.69

Remarks:

- Please see and refer original test for the authenticity of this report.
- Location of samples as per given information by the Customer.
- Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any Incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only

END OF REPORT



TEST REPORT

TEST REPORT NO. BSS/131/0902-0910 ULR – TC152622600000131F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 14.02.2026	Date of Test End: 18.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No. - 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form Q1 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
			Sample collected and prepared by By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID ↓	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₃ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-5/S-33(37.00-38.00M)		17.24	37.33	6.04	1.40	2.41	0.19	0.41	0.37	0.03	0.05	0.06	34.38
2.	BH-5/S-34(38.00-38.50M)		18.93	33.32	7.95	1.50	2.54	0.18	0.40	0.45	0.03	0.07	0.21	34.25
3.	BH-5/S-35(38.50-39.00M)		14.96	38.23	5.74	1.40	2.16	0.14	0.34	0.31	0.03	0.06	0.38	36.27
4.	BH-5/S-36(39.00-40.00M)		16.54	36.39	7.64	1.69	2.53	0.22	0.43	0.45	0.03	0.07	0.07	33.93
5.	BH-5/S-37(40.00-41.00M)		20.30	32.81	7.94	1.79	2.92	0.25	0.52	0.56	0.03	0.05	0.06	32.74
6.	BH-5/S-38(41.00-42.00M)		23.27	31.20	8.75	1.99	3.04	0.26	0.51	0.59	0.03	0.05	0.06	30.24
7.	BH-5/S-41(43.65-44.00M)		19.71	34.94	6.13	1.29	2.28	0.16	0.40	0.37	0.04	0.06	0.09	34.29
8.	BH-5/S-43(45.00-46.00M)		23.02	30.11	9.24	1.99	2.79	0.24	0.47	0.46	0.04	0.05	0.05	31.53
9.	BH-5/S-44(46.00-47.00M)		23.30	30.63	8.86	1.79	2.66	0.21	0.48	0.45	0.03	0.05	0.06	31.47

Remarks:

1. Please see and refer original test for the authenticity of this report.
2. Location of samples as per given information by the Customer.
3. Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



END OF REPORT

Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only



TEST REPORT

TEST REPORT NO. BSS/132/0911-0919 ULR – TC152622600000132F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 19.02.2026	Date of Test End: 23.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 100 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
			Sample collected and prepared by
			By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-7/S-1(7.00-8.00M)		30.60	28.41	5.53	1.99	2.95	0.21	0.38	0.47	0.11	0.05	0.04	29.23
2.	BH-7/S-2(8.00-9.00M)		34.55	23.51	7.74	2.09	2.98	0.23	0.37	0.46	0.09	0.04	0.04	27.85
3.	BH-7/S-3(9.00-10.00M)		28.47	27.29	7.34	1.99	2.78	0.21	0.37	0.44	0.07	0.03	0.04	30.51
4.	BH-7/S-4(10.00-11.00M)		27.09	28.42	5.74	2.69	2.99	0.23	0.33	0.45	0.08	0.05	0.04	31.82
5.	BH-7/S-5(11.00-12.00M)		35.18	22.10	7.84	3.09	3.84	0.34	0.44	0.66	0.09	0.03	0.05	26.29
6.	BH-7/S-6(12.00-13.00M)		33.26	21.52	10.25	3.18	3.76	0.33	0.42	0.64	0.07	0.05	0.05	26.45
7.	BH-7/S-7(13.00-14.00M)		32.76	21.70	9.66	2.59	3.48	0.29	0.41	0.58	0.06	0.04	0.04	28.38
8.	BH-7/S-8(14.00-15.00M)		29.63	27.13	6.63	2.79	3.38	0.29	0.43	0.60	0.08	0.07	0.06	28.88
9.	BH-7/S-9(15.00-16.00M)		27.60	26.31	9.26	2.19	2.98	0.24	0.43	0.49	0.08	0.05	0.05	30.27

Remarks:

- Please see and refer original test for the authenticity of this report.
- Location of samples as per given information by the Customer.
- Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



END OF REPORT

Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only



Quality Leads...

TC-15262

CHEMICAL ANALYSIS OF MINERALS & ORES

POLLUTION & ENVIRONMENT PARAMETERS

TEST REPORT

TEST REPORT NO. BSS/133/0920-0928 ULR – TC152622600000133F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 19.02.2026	Date of Test End: 23.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 50 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
			Sample collected and prepared by By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₃ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-7/S-13(19.00-20.00M)		25.60	24.76	12.47	2.69	3.44	0.31	0.48	0.65	0.07	0.04	0.05	29.42
2.	BH-7/S-14(20.00-21.00M)		25.68	26.40	11.14	2.19	2.84	0.22	0.39	0.45	0.08	0.05	0.05	30.50
3.	BH-7/S-15(21.00-22.00M)		27.28	24.73	10.85	2.69	2.68	0.22	0.39	0.36	0.09	0.05	0.06	30.61
4.	BH-7/S-16(22.00-23.00M)		27.10	21.13	14.69	3.09	3.42	0.33	0.43	0.64	0.10	0.05	0.05	28.94
5.	BH-7/S-17(23.00-24.00M)		25.16	24.08	12.98	2.69	3.25	0.30	0.47	0.60	0.07	0.03	0.06	30.23
6.	BH-7/S-18(24.00-25.00M)		25.09	25.43	12.25	2.39	3.02	0.26	0.44	0.52	0.08	0.05	0.05	30.41
7.	BH-7/S-20(26.00-27.00M)		27.63	23.21	12.26	2.59	3.30	0.29	0.47	0.59	0.07	0.05	0.05	29.42
8.	BH-7/S-21(27.00-28.00M)		25.11	25.29	12.25	2.39	3.15	0.28	0.46	0.59	0.06	0.04	0.05	30.28
9.	BH-7/S-22(28.00-29.00M)		25.85	24.08	12.88	2.59	3.24	0.30	0.51	0.61	0.07	0.05	0.06	29.72

Remarks:

1. Please see and refer original test for the authenticity of this report.
2. Location of samples as per given information by the Customer.
3. Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



END OF REPORT

Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any Incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only

Office: BSS Lab Private Limited, First Floor, 1338, Vijay Nagar, Kachnar City Road, Jabalpur - 482002 (M.P.), India
Telephone / Fax No. 0761-3581305, Mobile: 09425387402, 09424973438, Email: bsslab.jbp@gmail.com



Quality Leads...

TC-15262

CHEMICAL ANALYSIS OF MINERALS & ORES

POLLUTION & ENVIRONMENT PARAMETERS

TEST REPORT

TEST REPORT NO. BSS/134/0929-0932 ULR – TC152622600000134F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 20.02.2026	Date of Test End: 27.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No. - 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 04 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
			Sample collected and prepared by By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-8/S-1(6.00-7.00M)		17.63	38.34	1.51	2.89	3.42	0.23	0.38	1.00	0.03	0.07	0.08	34.24
2.	BH-8/S-2(7.00-8.00M)		12.50	42.97	1.00	1.89	2.53	0.18	0.38	0.71	0.03	0.05	0.10	37.51
3.	BH-8/S-3(8.50-9.00M)		18.06	38.91	2.21	1.69	3.04	0.22	0.38	0.84	0.06	0.05	0.12	34.37
4.	BH-8/S-4(9.00-9.50M)		18.41	39.40	1.61	1.89	3.54	0.29	0.42	0.94	0.05	0.07	0.10	33.11

Remarks:

1. Please see and refer original test for the authenticity of this report.
2. Location of samples as per given information by the Customer.
3. Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



END OF REPORT

Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only



TEST REPORT

TEST REPORT NO. BSS/135/0933-0941 ULR – TC152622600000135F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 25.02.2026	Date of Test End: 03.03.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form Ø9 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
			Sample collected and prepared by By Customer


DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₃ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-9/S-1(3.00-4.00m)		17.54	39.40	2.61	1.09	1.90	0.15	0.29	0.23	0.03	0.05	0.07	36.49
2.	BH-9/S-2(4.00-5.00m)		18.34	40.28	2.71	1.10	2.03	0.15	0.30	0.24	0.03	0.05	0.07	34.54
3.	BH-9/S-3(5.00-6.00m)		21.11	36.68	3.22	1.30	2.66	0.18	0.34	0.35	0.03	0.07	0.07	33.76
4.	BH-9/S-4(6.00-7.00m)		18.42	37.41	2.87	1.59	2.54	0.14	0.31	0.26	0.03	0.05	0.09	35.52
5.	BH-9/S-5(7.00-8.00m)		22.65	34.11	4.72	1.29	3.04	0.19	0.37	0.41	0.02	0.07	0.07	32.89
6.	BH-9/S-6(8.00-9.00m)		23.37	35.21	4.02	1.39	2.79	0.20	0.33	0.37	0.03	0.07	0.06	32.02
7.	BH-9/S-7(9.00-10.00m)		20.39	38.12	3.61	0.90	1.90	0.12	0.32	0.17	0.03	0.04	0.11	34.30
8.	BH-9/S-8(10.00-11.00m)		23.86	27.96	9.95	1.79	3.55	0.25	0.40	0.54	0.03	0.07	0.08	31.43
9.	BH-9/S-9(11.00-12.00m)		22.69	29.76	8.74	1.69	3.16	0.24	0.39	0.50	0.02	0.08	0.07	32.46

Remarks:

1. Please see and refer original test for the authenticity of this report.
2. Location of samples as per given information by the Customer.
3. Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



END OF REPORT

Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only



TEST REPORT

TEST REPORT NO. BSS/136/0942-0949 ULR – TC152622600000136F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 23.01.2026		Date of Test Start: 25.02.2026	Date of Test End: 03.03.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form d No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
			Sample collected and prepared by By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	BH-9/S-10(12.00-13.00m)		23.02	30.30	8.23	1.39	2.78	0.20	0.37	0.41	0.03	0.07	0.08	33.00
2.	BH-9/S-11(13.00-14.00m)		23.27	28.31	9.37	1.80	3.56	0.24	0.48	0.52	0.03	0.07	0.09	32.20
3.	BH-9/S-12(14.00-15.00m)		23.53	28.84	9.46	1.89	3.68	0.25	0.44	0.53	0.03	0.08	0.08	31.19
4.	BH-9/S-13(15.00-16.00m)		22.37	32.59	6.54	1.39	2.91	0.20	0.37	0.43	0.03	0.07	0.07	32.85
5.	BH-9/S-15(17.00-18.00m)		23.49	30.47	9.24	1.69	3.29	0.25	0.39	0.51	0.03	0.08	0.07	30.41
6.	BH-9/S-16(18.00-19.00m)		23.27	30.50	10.16	1.79	3.42	0.25	0.50	0.60	0.03	0.07	0.09	29.27
7.	BH-9/S-18(20.00-21.00m)		24.42	28.10	10.45	1.99	4.31	0.27	0.52	0.59	0.03	0.08	0.08	29.14
8.	BH-9/S-27(29.00-30.00m)		21.61	23.74	8.93	1.59	3.16	0.22	0.39	0.54	0.03	0.07	0.07	39.48

Remarks:

1. Please see and refer original test for the authenticity of this report.
2. Location of samples as per given information by the Customer.
3. Sample identification explanations given by the customer.


INDRANEEL DAWANDE
AUTHORIZED SIGNATORY



END OF REPORT

Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any Incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only



Quality Leads...

TC-15262

CHEMICAL ANALYSIS OF MINERALS & ORES

POLLUTION & ENVIRONMENT PARAMETERS

TEST REPORT

TEST REPORT NO. BSS/137/0950-0961 ULR - TC152622600000137F		Date of Issue Test Report: 29.05.2026	
Date of Sample Received: 31.01.2026		Date of Test Start: 28.02.2026	Date of Test End: 05.03.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002		Attention: Mr. INDRANEEL DAWANDE Contact No.- 9425387402
Name of Sample	LIMESTONE		Received Form and Quantity of Sample
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.		Powder Form 12 No. & 100 gm Each
Packing of Sample	Paper Pouch		Test Required SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
	Sample collected and prepared by		By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %												
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₂ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760
1.	CHANNEL SAMPLE/01		14.54	42.09	1.71	1.29	2.41	0.16	0.38	0.54	0.04	0.05	0.06	36.50
2.	PIT-01/01		19.76	39.00	1.81	1.79	3.17	0.26	0.34	0.82	0.08	0.04	0.04	32.62
3.	PIT-01/02		9.68	46.71	1.11	1.29	2.15	0.13	0.32	0.36	0.07	0.07	0.05	37.91
4.	PIT-01/03		12.86	45.08	1.21	1.40	2.41	0.17	0.30	0.43	0.08	0.05	0.05	35.90
5.	PIT-01/04		14.13	43.33	1.41	1.69	2.79	0.21	0.32	0.61	0.09	0.07	0.04	35.30
6.	PIT-01/05		13.74	43.92	1.41	1.10	2.41	0.15	0.36	0.46	0.04	0.07	0.06	36.17
7.	PIT-01/06		13.14	41.72	1.51	1.20	2.28	0.15	0.39	0.49	0.05	0.04	0.06	38.77
8.	PIT-01/07		12.53	44.89	1.51	1.39	2.53	0.19	0.32	0.53	0.05	0.07	0.04	35.87
9.	PIT-01/08		10.29	45.02	1.21	1.39	2.41	0.16	0.30	0.47	0.07	0.04	0.05	38.50
10.	PIT-01/09		15.07	42.76	1.41	1.69	2.53	0.17	0.31	0.51	0.09	0.07	0.05	35.27
11.	PIT-01/10		17.64	37.06	1.51	1.49	3.04	0.20	0.37	0.75	0.04	0.04	0.05	37.73
12.	PIT-01/11		12.14	44.45	1.21	1.20	2.15	0.14	0.28	0.39	0.06	0.07	0.05	37.76

Remarks:

- Please see and refer original test for the authenticity of this report.
- Location of samples as per given information by the Customer.
- Sample identification explanations given by the customer.


INDRANEEL DAWANDE

AUTHORIZED SIGNATORY



Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the sample submitted. 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab shall not be responsible for any variation in characteristics of the submitted samples taken up for analysis. 6. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 7. Sample will be disposed after fifteen days from the date of issue of the test report. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only.

Office: BSS Lab Private Limited, First Floor, 1338, Vijay Nagar, Kachnar City Road, Jabalpur - 482002 (M.P.), India
Telephone / Fax No. 0761-3581305, Mobile: 09425387402, 09424973438, Email: bsslab.jbp@gmail.com



Quality Leads...

TC-15262

CHEMICAL ANALYSIS OF MINERALS & ORES

POLLUTION & ENVIRONMENT PARAMETERS

TEST REPORT

TEST REPORT NO. BSS/138/0962-0972		Date of Issue Test Report: 29.05.2026	
ULR - TC152622600000138F			
Date of Sample Received: 31.01.2026		Date of Test Start: 23.02.2026	Date of Test End: 26.02.2026
Name of Customer And Address	ENGEOTECH CONSULTANT 1338, KACHNAR CITY ROAD, VIJAY NAGAR, JABALPUR (M.P.) 482002	Attention: Mr. INDRANEEL DAWANDE Contact No. - 9425387402	
Name of Sample	LIMESTONE	Received Form and Quantity of Sample	Powder Form 11 No. & 100 gm Each
Sample is Representative of	NANHWARA KYMORE LIMESTONE BLOCK VILLAGE-NANHWARA, KYMORE TEHSIL-VIJAYRAGHAVGARH DIST- KATNI (M.P.) AERA: 22.52 Sq. K.M.	Test Required	SiO ₂ , CaO, MgO, Fe ₂ O ₃ , Al ₂ O ₃ , MnO ₂ , Cl ⁻ , LOI, P ₂ O ₅ , Na ₂ O, K ₂ O & TiO ₂
Packing of Sample	Paper Pouch	Sample collected and prepared by	By Customer

DETAILS OF TEST

S. No.	RE- PRESENTATIVE SAMPLE ID	RESULT IN %													
		PARAMETERS	SiO ₂	CaO	MgO	Fe ₃ O ₃	Al ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	MnO ₂	P ₂ O ₅	Cl ⁻	LOI	
		TEST METHOD	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IS: 1760	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IBM: 2012	IS: 1760	IS: 1760	
1.	PIT-03/01		19.15	40.84	1.11	0.90	1.77	0.10	0.28	0.17	0.03	0.04	0.05	35.52	
2.	PIT-03/02		16.06	40.16	2.72	1.49	2.41	0.17	0.38	0.28	0.07	0.07	0.06	36.02	
3.	PIT-03/03		15.24	40.86	2.21	1.39	2.28	0.15	0.37	0.35	0.08	0.05	0.05	36.72	
4.	PIT-03/04		20.34	32.86	1.91	1.89	3.29	0.24	0.39	0.83	0.09	0.05	0.04	37.94	
5.	PIT-03/05		17.37	40.41	1.51	1.49	2.03	0.14	0.32	0.24	0.07	0.04	0.05	36.22	
6.	PIT-03/06		12.66	42.80	1.31	1.10	2.28	0.17	0.38	0.48	0.04	0.05	0.07	38.44	
7.	PIT-03/07		16.30	44.24	1.21	0.70	1.65	0.09	0.35	0.15	0.03	0.07	0.07	35.01	
8.	PIT-03/08		13.41	42.51	3.52	1.19	2.03	0.12	0.31	0.21	0.06	0.05	0.05	36.44	
9.	PIT-03/09		16.69	41.90	1.81	0.80	1.77	0.10	0.32	0.16	0.04	0.04	0.06	36.22	
10.	PIT-03/10		16.33	42.00	1.91	1.40	1.90	0.12	0.37	0.20	0.05	0.05	0.06	35.51	
11.	PIT-03/11		18.66	39.71	1.81	1.29	2.15	0.14	0.32	0.31	0.04	0.05	0.05	35.40	

Remarks:

- Please see and refer original test for the authenticity of this report.
- Location of samples as per given information by the Customer.
- Sample identification explanations given by the customer.



INDRANEEL DAWANDE

AUTHORIZED SIGNATORY



Terms & Conditions:

1. Sample not drawn by us. 2. The Analysis results provided are applicable only to the submitted sample(s). 3. The Analysis report in full or part shall not be reproduced in any media, unless written consent is given by B.S.S. Lab. 4. The Analysis result will be kept confidential. 5. B.S.S. Lab and its staff shall not be liable to the customer or any third party for any actions taken on the basis of such reports or findings, nor for any incorrect results arising from erroneous, unclear, incomplete, misleading or false information provided to our lab. 6. Sample will be disposed after fifteen days from the date of issue of the test report. 7. Unused samples or samples not accepted for any reason shall be returned to the customer on a written request. 8. The charges agreed at the time of finalizing the order shall be binding on the customer for the duration of the order only. 9. All the terms and conditions mentioned here above are assumed to be agreed by the customer. 10. Authenticity of this report must be cross checked with the original report. 11. Subject to Jabalpur Jurisdiction only.