



**Blendable Grade Limestone demarcated based on grade classification, NMI-IBM for exploratory boreholes
drilled in Revuru Block, District: Suryapet, Telangana**

BH. No.	From (m)	To (m)	Thickness (m)	CaO%	MgO %	Al₂O₃ %	SiO₂ %	Fe₂O₃ %	Na₂O %	SO₃%	P₂O₅ %	K₂O %	LOI %	GRADE
MRB-03	9.00	15.00	6.00	42.94	0.50	3.24	12.08	6.95	0.09	0.06	0.08	0.24	33.39	BLENDABLE GRADE LIMESTONE