



Bulk Density: 2.68 gm/cc

Polygon No.	BH No.	Polygonal Area (m ²)	From (m)	To (m)	Thick. (m)	Volume (m ³)	Geological Gross in-situ Resources (tonnes)	Average Quality									
								CaO %	MgO %	Al ₂ O ₃ %	SiO ₂ %	Fe ₂ O ₃ %	Na ₂ O %	SO ₃ %	P ₂ O ₅ %	K ₂ O %	LOI %
P1	MRB-03	1232810.59	9.00	15.00	6.00	7396863.54	19823594.29	42.94	0.50	3.24	12.08	6.95	0.09	0.06	0.08	0.24	33.39
Total Geological Gross in-situ Resources of Blendable Grade Limestone in Tonnes							19823594.29	42.94	0.50	3.24	12.08	6.95	0.09	0.06	0.08	0.24	33.39
Total Geological Gross in-situ Resources of Blendable Grade Limestone in Million Tonnes							19.82										