



Bulk Density: 2.68 gm/cc

BH.No.	Section Line	Sectional Area (m ²)	Strike Influence (m)	Volume (m ³)	Geological Gross In-situ Resources (tonnes)	Average Quality									
						CaO %	MgO %	Al ₂ O ₃ %	SiO ₂ %	Fe ₂ O ₃ %	Na ₂ O %	SO ₃ %	P ₂ O ₅ %	K ₂ O %	LOI %
MRB-01	S2-S2'	59421.86	755.79	44910447.57	120359999.49	52.54	0.61	0.84	6.68	0.41	0.09	0.16	0.16	0.15	37.96
MRB-02	S2-S2'	60732.88	696.49	42299843.59	113363580.82	52.52	0.55	1.38	4.69	0.56	0.06	0.02	0.04	0.27	39.71
MRB-03	S1-S1'	39373.56	636.10	25045521.52	67121997.66	49.37	0.51	1.85	7.78	3.00	0.05	0.03	0.08	0.24	36.84
MRB-04	S1-S1'	48207.30	716.05	34518837.17	92510483.60	51.42	0.61	1.05	7.32	0.47	0.09	0.11	0.14	0.20	38.30
MRB-05	S3-S3'	46626.83	776.92	36225316.76	97083848.93	51.98	0.66	0.92	6.74	0.39	0.02	0.03	0.15	0.17	38.77
Total Geological Gross In-situ Resources of Cement Grade Limestone in Tonnes					490439910.50	51.78	0.59	1.16	6.50	0.81	0.07	0.07	0.12	0.20	38.43
Total Geological Gross In-situ Resources of Cement Grade Limestone in Million Tonnes (MT)					490.44										