



**Statement showing Bulk density determination of glauconitic mineralisation
for Jhari block (G-3), Dist.- Satna, Madhya Pradesh**

Sl. No.	Sample No.	Borehole No.	From (m)	To (m)	Bulk Density (gm/cm³)
1	MJHR/BD01	MJHR-01	9.89	10.00	2.62
2	MJHR/BD02	MJHR-03	17.87	18.00	2.58
3	MJHR/BD03	MJHR-04	32.50	32.60	2.67
4	MJHR/BD04	MJHR-05	29.87	30.00	2.62
Average Bulk Density					2.62