

Statement showing section wise, borehole wise Reconnaissance category of resource (334) of Cement (Portland) Grade Limestone Estimated by Cross Sectional method, Pedaveedu West (G-3) block, Suryapet Dist., Telangana									
							Bulk Density: 2.685		
BH No.	Section Line	Area (m ²)	Section Influence (m)	Volume (m ³)	Gross Geological Resources ('000 tonnes)	Net Geological Resources ('000 tonnes)	Average Quality		
							CaO %	MgO %	SiO ₂ %
PBH-07	S7-S7'	7166.19	202.95	1454378.261	3905	3124	45.90	1.19	0.90
PBH-02(P)	S7-S7'	9522.23	202.95	1932536.579	5189	4151	47.46	1.01	1.06
PBH-08(P)	S6-S6'	12953.11	547.16	7087423.668	19030	15224	46.03	1.33	2.40
PBH-03(P)	S6-S6'	24820.2	547.16	13580620.63	36464	29171	46.73	1.15	1.33
MPWB-01(P)	S5-S5'	6850.58	920.62	6306746.707	16934	13547	49.15	0.62	2.02
MPWB-07(P)	S5-S5'	41441.26	120.615	4998437.575	13421	10737	49.67	0.68	2.20
MPWB-06	S5-S5'	41133.66	120.615	4961336.401	13321	10657	48.11	0.90	3.10
MPWB-01(P)	S5-S5'	34109.79	120.615	4114152.321	11046	8837	49.15	0.62	2.02
MPWB-03(P)	S4-S4'	11941.48	762.87	9109796.848	24460	19568	51.36	0.90	1.39
PBH-09	S3-S3'	37352.12	395.92	14788451.35	39707	31766	45.23	0.96	1.16
MPWB-05(P)	S2-S2'	40134.48	435.28	17469736.45	46906	37525	51.08	0.94	1.80
Resources in thousand tonnes					230383.00	184307.00	48.34	0.95	1.71
Resources in Million Tonnes					230.38	184.31			