



**BULK DENSITY STUDY FOR SAMPLES COLLECTED FROM CORE SAMPLES
IN AKAPUR BLOCK, YAVATMAL DISTRICT, MAHARASHTRA**

Sl.No.	BH.No	From (m)	To (m)	Sample No.	Bulk Density (gm/cc)
1	MAK-04	16.15	16.35	MK-BD-01	2.84
2	MAK-01	31.57	31.77	MK-BD-02	2.84
Average Bulk Density					2.84