



**Bulk Density: 2.84 gm/cc**

BH.No.	Section Line	Sectional Area (m <sup>2</sup> )	Strike Influence (m)	Volume (m <sup>3</sup> )	Geological Gross In-situ Resources (tonnes)	Average Quality									
						CaO %	MgO %	Al <sub>2</sub> O <sub>3</sub> %	SiO <sub>2</sub> %	Fe <sub>2</sub> O <sub>3</sub> %	SO <sub>3</sub> %	P <sub>2</sub> O <sub>5</sub> %	K <sub>2</sub> O %	Na <sub>2</sub> O %	LOI %
MAK-07	S2-S2'	11192.31	959.21	10735771.26	30489590.39	44.34	6.65	1.25	5.70	0.55	0.05	0.02	0.24	0.02	40.94
Total Geological Gross In-situ Resources of Cement Grade Limestone in Tonnes					30489590.39	44.34	6.65	1.25	5.70	0.55	0.05	0.02	0.24	0.02	40.94
Total Geological Gross In-situ Resources of Cement Grade Limestone in Million Tonnes (MT)					30.49										