



Bulk Density: 2.84 gm/cc

BH.No.	Section Line	Sectional Area (m ²)	Strike Influence (m)	Volume (m ³)	Geological Gross In-situ Resources (tonnes)	Average Quality									
						CaO %	MgO %	Al ₂ O ₃ %	SiO ₂ %	Fe ₂ O ₃ %	SO ₃ %	P ₂ O ₅ %	K ₂ O %	Na ₂ O %	LOI %
MAK-07	S2-S2'	1591.15	959.21	1526246.99	4334541.46	38.00	11.13	1.36	5.36	0.42	0.09	0.02	0.28	0.02	43.10
Total Geological Gross In-situ Resources of Beneficial Grade Limestone in Tonnes					4334541.46	38.00	11.13	1.36	5.36	0.42	0.09	0.02	0.28	0.02	43.10
Total Geological Gross In-situ Resources of Beneficial Grade Limestone in Million Tonnes (MT)					4.33										