

Details of the Chemical Analysis for Graphite of Primary Samples of the boreholes drilled by MECL in Jamtola-Khandapar Block, District- Balaghat, Madhya Pradesh

BH No. - MJGR-03									
Sl. No.	Sample No.	Depth (m)		Extrapolated Length	Sample Length	Moist% (AD)	Ash% (AD)	VM% (AD)	FC% (AD)
		From	To						
1	MJGR/03/01	40.66	41.66	1.00	0.99	0.1	78.4	21.5	0.0
2	MJGR/03/02	41.66	42.66	1.00	0.99	0.3	76.4	23.1	0.2
3	MJGR/03/03	42.66	43.66	1.00	0.96	0.4	81.8	17.8	0.1
4	MJGR/03/04	43.66	44.16	0.50	0.48	0.2	76.0	23.7	0.1
5	MJGR/03/05	44.16	44.66	0.50	0.49	0.2	72.4	27.3	0.1
6	MJGR/03/06	44.66	45.16	0.50	0.49	0.8	71.4	27.8	0.0
7	MJGR/03/07	45.16	45.66	0.50	0.49	0.3	70.8	28.6	0.3
8	MJGR/03/08	45.66	46.16	0.50	0.49	0.2	68.4	31.2	0.2
9	MJGR/03/09	46.16	47.16	1.00	0.98	0.2	77.8	22.0	0.0
10	MJGR/03/10	47.16	48.16	1.00	0.95	0.2	77.1	22.2	0.5
11	MJGR/03/11	48.16	49.16	1.00	0.95	0.4	76.6	22.2	0.8

BH No. - MJGR-04									
Sl. No.	Sample No.	Depth (m)		Extrapolated Length	Sample Length	Moist% (AD)	Ash% (AD)	VM% (AD)	FC% (AD)
		From	To						
12	MJGR/04/13	32.22	32.72	0.50	0.50	0.3	91.8	7.6	0.3
13	MJGR/04/14	32.72	33.22	0.50	0.49	0.3	91.6	6.7	1.5
14	MJGR/04/15	33.22	33.72	0.50	0.49	0.3	91.9	6.9	0.9
15	MJGR/04/16	33.72	34.22	0.50	0.49	0.1	92.0	6.0	2.0
16	MJGR/04/17	34.22	34.72	0.50	0.49	0.3	91.4	8.3	0.0
17	MJGR/04/18	34.72	35.22	0.50	0.49	0.4	91.4	6.6	1.6
18	MJGR/04/19	35.22	35.72	0.50	0.49	0.4	91.6	6.2	1.9
19	MJGR/04/20	35.72	36.22	0.50	0.49	0.4	91.5	5.5	2.6
20	MJGR/04/21	36.22	36.72	0.50	0.48	0.4	92.2	5.9	1.5
21	MJGR/04/22	36.72	37.22	0.50	0.48	0.3	91.7	5.3	2.8