

Details of Bedrock Sample Analysis for Graphite in Jamtola-Khandapar Block, District: Balaghat, Madhya Pradesh

Sl. No.	Sample Code	Northing	Easting	Details	Moist.%	Ash %	V.M. %	F.C.*%
1	MJK/G/01	454855.00	2430133.00	Graphite	0.11	93.63	3.49	2.76
2	MJK/G/02	455020.00	2429475.00	Carbonaceous Phyllite	0.14	96.77	2.81	0.28
3	MJK/G/03	455189.00	2429504.00	Carbonaceous Phyllite	0.10	99.10	0.54	0.27
4	MJK/G/04	455220.00	2429528.00	Carbonaceous Phyllite	0.32	95.31	4.08	0.29
5	MJK/G/05	455152.00	2429608.00	Carbonaceous Phyllite	0.40	95.76	3.67	0.17
6	MJK/G/06	455052.00	2429606.00	Carbonaceous Phyllite	0.32	95.47	4.16	0.06
7	MJK/G/07	454835.00	2430108.00	Graphite	0.06	92.89	3.78	3.27
8	MJK/G/08	454856.00	2430185.00	Graphite	0.14	93.51	4.55	1.79
9	MJK/G/09	454944.00	2430246.00	Graphite	0.18	93.58	3.45	2.78
10	MJK/G/10	454979.00	2430276.00	Graphite	0.30	92.20	4.30	3.20
11	MJK/G/11	455308.00	2430901.00	Carbonaceous Phyllite	0.13	95.49	3.20	1.18
12	MJK/G/12	455308.00	2430865.00	Graphite	0.10	93.10	5.05	1.75
13	MJK/G/13	454845.51	2430107.15	Graphite	0.06	92.83	3.73	3.38
14	MJK/G/14	455338.00	2430900.00	Carbonaceous Phyllite	0.28	97.53	1.87	0.31
15	MJK/G/15	455261.00	2431014.00	Graphite Band	0.24	94.15	3.53	2.09
16	MJK/G/16	455308.00	2431286.00	Graphite	0.22	94.75	3.30	1.73
17	MJK/G/17	455317.00	2431298.00	Graphite	0.25	92.15	4.36	3.24
18	MJK/G/18	455378.00	2431458.00	Carbonaceous Phyllite	0.34	96.72	2.82	0.12
19	MJK/G/19	455472.00	2431497.00	Graphite	0.22	96.58	2.95	0.24