



Bulk Density: 2.81 gm/cc

BH.No.	Section Line	Sectional Area (m ²)	Strike Influence (m)	Volume (m ³)	Geological Gross In-situ Resources (tonnes)	Average Quality									
						CaO %	MgO %	Al ₂ O ₃ %	SiO ₂ %	Fe ₂ O ₃ %	SO ₃ %	P ₂ O ₅ %	K ₂ O %	Na ₂ O %	LOI %
MMC-01	S3-S3'	108489.68	475.96	51636748.09	143550159.70	32.35	18.92	0.41	1.03	0.18	0.02	0.15	0.04	0.05	46.62
MMC-02	S3-S3'	61652.24	360.38	22218236.02	61766696.13	33.36	18.23	0.48	2.52	0.21	0.03	0.09	0.07	0.04	44.78
MMC-03	S2-S2'	76479.21	377.89	28900728.48	80344025.17	32.73	18.85	0.72	1.95	0.27	0.02	0.06	0.11	0.04	45.04
MMC-05	S2-S2'	46042.73	507.66	23374050.64	64979860.77	33.45	18.30	0.36	0.72	0.18	0.02	0.05	0.06	0.04	46.62
Total Geological Gross In-situ Resources of SMS (LD) Grade Dolomite in Tonnes					350640741.76	32.82	18.67	0.49	1.44	0.20	0.03	0.10	0.07	0.05	45.94
Total Geological Gross In-situ Resources of SMS (LD) Grade Dolomite in Million Tonnes					350.64										