

**Statement Showing Bulk Density data measured at Majhauri (G-3) Block for Iron and Bauxite,
District - Jabalpur, Madhya Pradesh**

Sl. No.	Pit No.	Easting	Northing	Weight of excavated material (Kg)	Weight of excavated material (tonnes)	Volume of pit filled by fine sand (m ³)	Bulk Density (t/m ³)
1	BD PIT-1	418024.46	2605476.38	263.12	0.26	0.17	1.548
2	BD PIT-2	417731.56	2605438.66	319.08	0.32	0.23	1.387
3	BD PIT-3	416207.13	2603262.65	370.12	0.37	0.25	1.480
4	BD PIT-4	416478.62	2603465.54	239.40	0.24	0.18	1.230
5	BD PIT-5	417209.89	2604739.01	270.62	0.27	0.22	1.330