

Statement showing mineralised Zone details with respect to $\text{Al}_2\text{O}_3 \geq 20\%$, $\text{Ti} \geq 2\%$ and $\text{V} \geq 500$ ppm, Majhauri (G-3) Block for Iron and Bauxite, Distt.- Jabalpur, Madhya Pradesh

Sl. No.	BH No.	From (m)	To (m)	Thickness (m)	Al_2O_3 %	Ti %	V (ppm)
1	MBM-1	0.00	20.00	20.00	31.08	3.33	744.66
2	MBM-2	0.00	12.00	12.00	27.93	3.33	984.26
3	MBM-3	0.00	2.00	2.00	22.06	-	-
4	MBM-4	0.00	20.00	20.00	25.64	2.42	735.50