

**Details of the Chemical Analysis for Copper, Lead, Zinc, Nickel, Cobalt, Molybdenum,
and Tungsten of Primary Samples of the boreholes drilled by MECL (Present G3 Exploration)
in Thakurdih Area-1 Block, District-East Singhbhum, Jharkhand**

Borehole No: MTB-01												
Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
1	MTB-01/01	41.50	42.00	0.49	0.50	0.01	<0.01	0.01	0.07	0.01	<0.01	<0.01
2	MTB-01/02	42.00	42.50	0.49	0.50	<0.01	<0.01	0.01	0.07	0.01	<0.01	<0.01
3	MTB-01/03	42.50	43.00	0.50	0.50	0.11	<0.01	0.01	0.12	0.01	<0.01	<0.01
4	MTB-01/04	43.00	43.50	0.50	0.50	0.05	<0.01	0.01	0.06	0.01	<0.01	<0.01
5	MTB-01/05	43.50	44.00	0.50	0.50	0.01	<0.01	0.01	0.04	0.01	<0.01	<0.01
6	MTB-01/06	44.00	44.50	0.50	0.50	0.01	<0.01	0.01	0.03	0.01	<0.01	<0.01
7	MTB-01/07	51.00	51.50	0.47	0.50	0.02	<0.01	0.01	0.04	0.01	<0.01	<0.01
8	MTB-01/08	51.50	52.00	0.47	0.50	0.11	<0.01	0.01	0.05	0.01	<0.01	<0.01
9	MTB-01/09	52.00	52.50	0.48	0.50	0.02	<0.01	0.01	0.03	0.01	<0.01	<0.01
10	MTB-01/10	52.50	53.00	0.48	0.50	0.02	<0.01	0.01	0.04	0.01	<0.01	0.01
11	MTB-01/11	53.00	53.50	0.48	0.50	0.05	<0.01	0.01	0.05	<0.01	<0.01	<0.01
12	MTB-01/12	53.50	54.00	0.48	0.50	0.01	<0.01	0.01	0.02	<0.01	<0.01	<0.01
13	MTB-01/13	54.00	54.50	0.48	0.50	0.10	<0.01	0.01	0.05	0.01	<0.01	<0.01
14	MTB-01/14	54.50	55.00	0.48	0.50	0.20	<0.01	0.01	0.03	0.01	<0.01	<0.01
15	MTB-01/15	55.00	55.50	0.49	0.50	0.01	<0.01	0.01	0.04	0.01	<0.01	<0.01
16	MTB-01/16	55.50	56.50	0.98	1.00	0.01	<0.01	0.01	0.03	0.01	<0.01	<0.01
17	MTB-01/17	56.50	57.50	0.98	1.00	0.08	<0.01	0.01	0.03	0.01	<0.01	<0.01
18	MTB-01/18	57.50	58.00	0.49	0.50	0.43	<0.01	0.01	0.04	0.01	<0.01	<0.01
19	MTB-01/19	58.00	58.50	0.50	0.50	0.17	<0.01	0.01	0.04	0.01	<0.01	<0.01
20	MTB-01/20	58.50	59.50	1.00	1.00	0.05	<0.01	0.01	0.03	0.01	<0.01	<0.01
21	MTB-01/21	65.50	66.50	1.00	1.00	0.01	<0.01	0.01	0.02	<0.01	<0.01	<0.01
22	MTB-01/22	66.50	67.00	0.50	0.50	0.01	<0.01	<0.01	0.02	0.01	<0.01	<0.01
23	MTB-01/23	67.00	67.50	0.44	0.50	0.06	<0.01	0.01	0.05	0.01	<0.01	<0.01
24	MTB-01/24	67.50	68.50	0.88	1.00	0.01	<0.01	0.01	0.02	<0.01	<0.01	<0.01
25	MTB-01/25	71.50	72.50	0.96	1.00	0.01	<0.01	0.01	0.02	0.01	<0.01	<0.01
26	MTB-01/26	72.50	73.00	0.48	0.50	0.02	<0.01	0.01	0.03	0.01	<0.01	<0.01
27	MTB-01/27	73.00	73.50	0.49	0.50	0.02	<0.01	0.01	0.03	0.01	<0.01	<0.01
28	MTB-01/28	73.50	74.00	0.49	0.50	0.04	<0.01	0.01	0.04	0.01	<0.01	<0.01
29	MTB-01/29	74.00	74.50	0.49	0.50	0.03	<0.01	0.01	0.03	0.01	<0.01	<0.01
30	MTB-01/30	97.00	98.00	0.99	1.00	0.02	<0.01	0.01	0.03	<0.01	<0.01	<0.01
31	MTB-01/31	98.00	99.00	0.99	1.00	0.04	<0.01	0.01	0.05	0.01	<0.01	<0.01
32	MTB-01/32	99.00	100.00	1.00	1.00	<0.01	<0.01	0.01	0.03	0.01	<0.01	<0.01
33	MTB-01/33	100.00	101.00	1.00	1.00	0.02	<0.01	0.01	0.03	<0.01	<0.01	0.01
34	MTB-01/34	101.00	102.00	1.00	1.00	0.12	<0.01	0.01	0.03	0.01	<0.01	<0.01
35	MTB-01/35	102.00	103.00	1.00	1.00	0.01	<0.01	<0.01	0.03	<0.01	<0.01	<0.01
Borehole No: MTB-02												
36	MTB-02/01	22.00	23.00	0.96	1.00	0.02	<0.01	0.01	0.11	0.01	<0.01	<0.01
37	MTB-02/02	23.00	23.50	0.48	0.50	0.06	<0.01	0.01	0.10	0.01	<0.01	<0.01
38	MTB-02/03	23.50	24.00	0.47	0.50	0.11	<0.01	<0.01	0.14	0.01	<0.01	<0.01
39	MTB-02/04	24.00	25.00	0.96	1.00	0.02	<0.01	0.01	0.07	0.01	<0.01	<0.01
40	MTB-02/05	63.00	64.00	0.97	1.00	0.04	<0.01	<0.01	0.03	0.01	<0.01	<0.01
41	MTB-02/06	64.00	64.50	0.48	0.50	0.04	<0.01	<0.01	0.04	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
43	MTB-02/08	65.00	65.50	0.48	0.50	0.07	<0.01	0.01	0.06	0.01	<0.01	0.01
44	MTB-02/09	65.50	66.00	0.47	0.50	0.27	<0.01	0.01	0.06	0.01	<0.01	<0.01
45	MTB-02/10	66.00	66.50	0.48	0.50	0.03	<0.01	<0.01	0.05	0.01	<0.01	<0.01
46	MTB-02/11	66.50	67.00	0.47	0.50	0.04	<0.01	0.01	0.05	0.01	<0.01	<0.01
47	MTB-02/12	67.00	67.50	0.48	0.50	0.03	<0.01	<0.01	0.04	0.01	<0.01	0.01
48	MTB-02/13	67.50	68.50	0.96	1.00	0.09	<0.01	0.01	0.06	0.01	<0.01	<0.01
49	MTB-02/14	79.00	80.00	0.86	1.00	0.15	<0.01	<0.01	0.03	0.01	<0.01	<0.01
50	MTB-02/15	80.00	80.50	0.43	0.50	0.19	<0.01	0.01	0.03	0.01	<0.01	0.01
51	MTB-02/16	80.50	81.00	0.43	0.50	0.40	<0.01	0.01	0.04	0.01	<0.01	<0.01
52	MTB-02/17	81.00	81.50	0.44	0.50	0.31	<0.01	<0.01	0.04	0.01	<0.01	<0.01
53	MTB-02/18	81.50	82.00	0.43	0.50	0.32	<0.01	0.01	0.04	0.01	<0.01	<0.01
54	MTB-02/19	82.00	82.50	0.50	0.50	0.81	<0.01	0.01	0.11	0.03	0.01	<0.01
55	MTB-02/20	82.50	83.00	0.50	0.50	0.26	<0.01	0.01	0.04	0.02	<0.01	0.01
56	MTB-02/21	83.00	83.50	0.50	0.50	0.11	<0.01	0.01	0.03	0.01	<0.01	<0.01
57	MTB-02/22	83.50	84.00	0.50	0.50	0.23	<0.01	0.01	0.04	0.01	<0.01	<0.01
58	MTB-02/23	84.00	84.50	0.50	0.50	0.46	<0.01	0.01	0.05	0.02	<0.01	0.01
59	MTB-02/24	84.50	85.00	0.50	0.50	0.42	<0.01	0.01	0.10	0.02	<0.01	<0.01
60	MTB-02/25	85.00	85.50	0.50	0.50	0.41	<0.01	0.01	0.08	0.03	0.01	<0.01
61	MTB-02/26	85.50	86.00	0.50	0.50	0.42	<0.01	0.01	0.06	0.02	<0.01	<0.01
62	MTB-02/27	86.00	86.50	0.50	0.50	0.25	<0.01	<0.01	0.03	0.02	<0.01	<0.01
63	MTB-02/28	86.50	87.00	0.50	0.50	0.27	<0.01	<0.01	0.03	0.01	<0.01	<0.01
64	MTB-02/29	87.00	88.00	0.88	1.00	0.04	<0.01	0.01	0.02	0.01	<0.01	<0.01
65	MTB-02/30	91.50	92.50	0.98	1.00	0.10	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
66	MTB-02/31	92.50	93.00	0.49	0.50	0.15	<0.01	0.01	0.02	0.01	<0.01	<0.01
67	MTB-02/32	93.00	93.50	0.49	0.50	0.28	<0.01	0.01	0.02	0.01	<0.01	<0.01
68	MTB-02/33	93.50	94.00	0.49	0.50	0.11	<0.01	0.01	0.02	0.01	<0.01	<0.01
69	MTB-02/34	94.00	94.50	0.50	0.50	0.32	<0.01	0.01	0.03	0.01	<0.01	<0.01
70	MTB-02/35	94.50	95.33	0.82	0.83	0.06	<0.01	0.01	0.02	0.01	<0.01	<0.01
71	MTB-02/36	95.33	96.16	0.81	0.83	0.12	<0.01	0.01	0.03	0.01	<0.01	<0.01
72	MTB-02/37	96.16	96.66	0.49	0.50	0.19	<0.01	0.01	0.03	0.01	<0.01	<0.01
73	MTB-02/38	96.66	97.66	0.99	1.00	0.02	<0.01	<0.01	0.02	0.01	<0.01	<0.01
Borehole No: MTB-03												
74	MTB-03/01	34.36	35.36	1.00	1.00	0.05	<0.01	<0.01	0.04	0.01	<0.01	<0.01
75	MTB-03/02	35.36	35.86	0.50	0.50	0.04	<0.01	<0.01	0.05	0.01	<0.01	<0.01
76	MTB-03/03	35.86	36.36	0.50	0.50	0.06	<0.01	<0.01	0.04	0.01	<0.01	<0.01
77	MTB-03/04	36.36	36.86	0.50	0.50	0.14	<0.01	<0.01	0.07	0.01	<0.01	0.01
78	MTB-03/05	36.86	37.86	1.00	1.00	0.12	<0.01	<0.01	0.08	0.01	<0.01	<0.01
79	MTB-03/06	39.00	40.00	1.00	1.00	0.06	<0.01	<0.01	0.01	0.01	<0.01	<0.01
80	MTB-03/07	40.00	40.50	0.49	0.50	0.13	<0.01	<0.01	0.01	0.01	<0.01	<0.01
81	MTB-03/08	40.50	41.00	0.48	0.50	0.15	<0.01	<0.01	0.02	0.01	<0.01	<0.01
82	MTB-03/09	41.00	41.50	0.49	0.50	0.13	<0.01	<0.01	0.02	0.01	<0.01	<0.01
83	MTB-03/10	41.50	42.00	0.48	0.50	0.04	<0.01	<0.01	0.01	0.01	<0.01	<0.01
84	MTB-03/11	42.00	42.50	0.49	0.50	0.19	<0.01	<0.01	0.02	0.01	<0.01	<0.01
85	MTB-03/12	42.50	43.00	0.48	0.50	0.01	<0.01	<0.01	0.01	0.01	<0.01	<0.01
86	MTB-03/13	43.00	44.00	1.00	1.00	0.22	<0.01	0.01	0.02	0.01	0.01	<0.01
87	MTB-03/14	44.00	45.00	1.00	1.00	0.04	<0.01	0.01	0.01	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
89	MTB-03/16	49.50	50.50	0.96	1.00	0.01	<0.01	<0.01	0.01	0.01	<0.01	<0.01
90	MTB-03/17	50.50	51.00	0.48	0.50	0.02	<0.01	<0.01	0.01	0.01	<0.01	<0.01
91	MTB-03/18	51.00	51.50	0.48	0.50	0.33	<0.01	<0.01	0.03	0.01	<0.01	<0.01
92	MTB-03/19	51.50	52.00	0.48	0.50	0.86	<0.01	<0.01	0.03	0.02	<0.01	<0.01
93	MTB-03/20	52.00	52.50	0.49	0.50	0.56	<0.01	<0.01	0.04	0.02	<0.01	<0.01
94	MTB-03/21	52.50	53.00	0.48	0.50	0.94	<0.01	<0.01	0.03	0.01	<0.01	<0.01
95	MTB-03/22	53.00	53.50	0.49	0.50	0.07	<0.01	0.01	0.02	0.01	<0.01	<0.01
96	MTB-03/23	53.50	54.00	0.48	0.50	0.14	<0.01	0.01	0.01	0.01	<0.01	<0.01
97	MTB-03/24	54.00	55.00	0.97	1.00	0.02	<0.01	<0.01	0.01	0.01	<0.01	<0.01
98	MTB-03/25	55.00	55.50	0.51	0.50	0.06	<0.01	0.01	0.01	0.01	<0.01	<0.01
99	MTB-03/26	55.50	56.00	0.51	0.50	0.08	<0.01	0.01	0.02	0.01	<0.01	<0.01
100	MTB-03/27	56.00	56.50	0.51	0.50	0.03	<0.01	0.01	0.03	0.02	<0.01	<0.01
101	MTB-03/28	56.50	57.50	1.02	1.00	<0.01	<0.01	0.01	0.03	0.01	<0.01	<0.01
102	MTB-03/29	57.50	58.00	0.51	0.50	0.13	<0.01	0.01	0.03	0.01	<0.01	<0.01
103	MTB-03/30	58.00	59.00	0.94	1.00	0.12	<0.01	<0.01	0.02	0.01	<0.01	<0.01
104	MTB-03/31	59.00	59.50	0.47	0.50	0.28	<0.01	<0.01	0.02	0.01	<0.01	<0.01
105	MTB-03/32	59.50	60.00	0.47	0.50	0.07	<0.01	0.01	0.02	0.01	<0.01	<0.01
106	MTB-03/33	60.00	60.50	0.47	0.50	0.11	<0.01	<0.01	0.02	0.01	<0.01	<0.01
107	MTB-03/34	60.50	61.50	0.99	1.00	0.07	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
108	MTB-03/35	61.50	62.50	1.04	1.00	0.15	<0.01	<0.01	0.02	0.01	<0.01	<0.01
109	MTB-03/36	62.50	63.00	0.52	0.50	0.24	<0.01	<0.01	0.05	0.02	<0.01	<0.01
110	MTB-03/37	63.00	64.00	1.04	1.00	0.04	<0.01	<0.01	0.02	0.01	<0.01	<0.01
111	MTB-03/38	64.00	65.00	1.00	1.00	0.19	<0.01	<0.01	0.03	0.01	<0.01	<0.01
112	MTB-03/39	65.00	66.00	1.00	1.00	0.20	<0.01	<0.01	0.02	0.01	<0.01	<0.01
113	MTB-03/40	66.00	67.00	1.00	1.00	0.06	<0.01	0.01	0.02	0.01	<0.01	<0.01
114	MTB-03/41	67.00	68.00	1.01	1.00	0.03	<0.01	<0.01	0.02	0.01	<0.01	<0.01
115	MTB-03/42	68.00	69.00	1.01	1.00	0.10	<0.01	<0.01	0.03	0.01	<0.01	<0.01
116	MTB-03/43	69.00	70.00	1.01	1.00	0.13	<0.01	<0.01	0.03	0.01	<0.01	<0.01
117	MTB-03/44	70.00	71.00	0.98	1.00	0.21	<0.01	0.01	0.03	0.01	<0.01	<0.01
118	MTB-03/45	71.00	72.00	0.98	1.00	0.02	<0.01	0.03	0.02	0.01	<0.01	<0.01
119	MTB-03/46	72.00	73.00	0.98	1.00	0.05	<0.01	0.01	0.02	0.01	<0.01	<0.01
120	MTB-03/47	73.00	74.00	0.88	1.00	0.07	<0.01	<0.01	0.02	<0.01	<0.01	0.01
121	MTB-03/48	74.00	75.00	0.88	1.00	0.04	<0.01	<0.01	0.02	0.02	<0.01	<0.01
122	MTB-03/49	75.00	75.50	0.44	0.50	0.04	<0.01	<0.01	0.03	0.02	<0.01	<0.01
123	MTB-03/50	75.50	76.00	0.44	0.50	0.15	<0.01	<0.01	0.03	0.02	<0.01	<0.01
124	MTB-03/51	76.00	76.50	0.50	0.50	0.25	<0.01	<0.01	0.04	0.02	<0.01	<0.01
125	MTB-03/52	76.50	77.00	0.50	0.50	0.08	<0.01	<0.01	0.03	0.01	<0.01	<0.01
126	MTB-03/53	77.00	77.50	0.50	0.50	0.09	<0.01	<0.01	0.03	0.01	<0.01	<0.01
127	MTB-03/54	77.50	78.00	0.50	0.50	0.03	<0.01	<0.01	0.01	0.01	<0.01	<0.01
128	MTB-03/55	78.00	78.50	0.50	0.50	0.45	<0.01	<0.01	0.03	0.02	<0.01	<0.01
129	MTB-03/56	78.50	79.00	0.50	0.50	0.16	<0.01	<0.01	0.02	0.01	<0.01	0.01
130	MTB-03/57	79.00	79.40	0.40	0.40	0.02	<0.01	<0.01	0.01	0.01	<0.01	<0.01
131	MTB-03/58	79.40	79.80	0.40	0.40	1.34	<0.01	<0.01	0.03	0.02	<0.01	<0.01
132	MTB-03/59	79.80	80.80	1.00	1.00	0.09	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01
133	MTB-03/60	80.80	81.20	0.40	0.40	0.03	<0.01	<0.01	0.01	0.01	<0.01	<0.01
134	MTB-03/61	81.20	81.60	0.40	0.40	0.52	<0.01	0.01	0.02	0.02	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
136	MTB-03/63	103.70	104.70	0.97	1.00	0.09	<0.01	<0.01	0.01	0.01	<0.01	<0.01
137	MTB-03/64	104.70	105.20	0.49	0.50	0.74	<0.01	<0.01	0.03	0.01	<0.01	<0.01
138	MTB-03/65	105.20	105.70	0.48	0.50	0.14	<0.01	<0.01	0.02	0.02	<0.01	<0.01
139	MTB-03/66	105.70	106.70	1.00	1.00	0.12	<0.01	0.01	0.02	0.01	<0.01	<0.01
Borehole No: MTB-04												
140	MTB-04/01	42.00	43.00	0.99	1.00	0.05	<0.01	<0.01	0.03	0.01	0.01	<0.01
141	MTB-04/02	43.00	43.50	0.49	0.50	0.33	<0.01	<0.01	0.03	0.01	<0.01	<0.01
142	MTB-04/03	43.50	44.00	0.48	0.50	0.10	<0.01	<0.01	0.02	0.01	<0.01	<0.01
143	MTB-04/04	44.00	44.50	0.49	0.50	0.08	<0.01	<0.01	0.03	0.01	<0.01	<0.01
144	MTB-04/05	44.50	45.50	0.97	1.00	0.04	<0.01	<0.01	0.03	0.01	<0.01	<0.01
145	MTB-04/06	45.50	46.00	0.49	0.50	0.27	<0.01	<0.01	0.03	0.01	<0.01	<0.01
146	MTB-04/07	46.00	47.00	0.95	1.00	0.03	<0.01	<0.01	0.01	0.01	<0.01	<0.01
147	MTB-04/08	49.00	50.00	1.00	1.00	0.14	<0.01	<0.01	0.02	0.01	<0.01	<0.01
148	MTB-04/09	50.00	50.50	0.50	0.50	0.21	<0.01	<0.01	0.03	0.01	<0.01	<0.01
149	MTB-04/10	50.50	51.00	0.50	0.50	0.46	<0.01	0.01	0.04	0.02	<0.01	<0.01
150	MTB-04/11	51.00	52.00	1.00	1.00	0.18	<0.01	<0.01	0.04	0.01	<0.01	<0.01
151	MTB-04/12	52.00	52.50	0.50	0.50	0.29	<0.01	0.01	0.06	0.02	<0.01	<0.01
152	MTB-04/13	52.50	53.00	0.50	0.50	0.41	<0.01	0.01	0.08	0.03	<0.01	<0.01
153	MTB-04/14	53.00	53.50	0.50	0.50	0.24	<0.01	<0.01	0.03	0.01	<0.01	<0.01
154	MTB-04/15	53.50	54.00	0.50	0.50	0.26	<0.01	<0.01	0.01	0.01	<0.01	<0.01
155	MTB-04/16	54.00	54.50	0.50	0.50	0.29	<0.01	<0.01	0.13	0.04	0.01	<0.01
156	MTB-04/17	54.50	55.00	0.50	0.50	0.89	<0.01	<0.01	0.14	0.04	0.01	<0.01
157	MTB-04/18	55.00	55.50	0.50	0.50	0.77	<0.01	0.01	0.12	0.03	0.01	<0.01
158	MTB-04/19	55.50	56.00	0.50	0.50	0.11	<0.01	<0.01	0.05	0.02	<0.01	<0.01
159	MTB-04/20	56.00	56.50	0.50	0.50	0.38	<0.01	<0.01	0.06	0.02	<0.01	<0.01
160	MTB-04/21	56.50	57.00	0.50	0.50	0.09	<0.01	<0.01	0.02	0.01	<0.01	<0.01
161	MTB-04/22	57.00	57.50	0.50	0.50	0.66	<0.01	<0.01	0.06	0.02	<0.01	<0.01
162	MTB-04/23	57.50	58.00	0.50	0.50	0.09	<0.01	<0.01	0.03	0.01	<0.01	<0.01
163	MTB-04/24	58.00	58.50	0.50	0.50	0.20	<0.01	0.01	0.03	0.01	<0.01	<0.01
164	MTB-04/25	58.50	59.00	0.50	0.50	0.02	<0.01	0.01	0.02	0.01	<0.01	<0.01
165	MTB-04/26	59.00	59.50	0.50	0.50	0.06	<0.01	0.01	0.02	0.01	<0.01	<0.01
166	MTB-04/27	59.50	60.00	0.50	0.50	0.19	<0.01	0.01	0.03	0.01	<0.01	<0.01
167	MTB-04/28	60.00	60.50	0.50	0.50	0.37	<0.01	<0.01	0.04	0.02	<0.01	<0.01
168	MTB-04/29	60.50	61.00	0.50	0.50	0.24	<0.01	0.01	0.04	0.01	<0.01	<0.01
169	MTB-04/30	61.00	61.50	0.50	0.50	0.43	<0.01	0.01	0.04	0.02	<0.01	<0.01
170	MTB-04/31	61.50	62.00	0.50	0.50	0.15	<0.01	<0.01	0.02	0.01	<0.01	<0.01
171	MTB-04/32	62.00	62.50	0.50	0.50	1.11	<0.01	0.01	0.05	0.02	<0.01	<0.01
172	MTB-04/33	62.50	63.00	0.50	0.50	0.08	<0.01	<0.01	0.03	0.02	0.01	<0.01
173	MTB-04/34	63.00	63.50	0.50	0.50	0.22	<0.01	<0.01	0.03	0.02	<0.01	<0.01
174	MTB-04/35	63.50	64.00	0.50	0.50	0.09	<0.01	<0.01	0.05	0.02	<0.01	<0.01
175	MTB-04/36	64.00	64.50	0.50	0.50	0.40	<0.01	0.01	0.06	0.02	<0.01	<0.01
176	MTB-04/37	64.50	65.00	0.50	0.50	0.69	<0.01	0.01	0.06	0.03	<0.01	<0.01
177	MTB-04/38	65.00	65.50	0.50	0.50	0.18	<0.01	0.01	0.05	0.02	<0.01	<0.01
178	MTB-04/39	65.50	66.00	0.50	0.50	0.40	<0.01	<0.01	0.07	0.03	<0.01	<0.01
179	MTB-04/40	66.00	66.50	0.50	0.50	0.37	<0.01	<0.01	0.05	0.02	<0.01	<0.01
180	MTB-04/41	66.50	67.00	0.50	0.50	0.42	<0.01	0.01	0.07	0.03	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
182	MTB-04/43	67.50	68.00	0.49	0.50	0.21	<0.01	0.01	0.04	0.02	<0.01	<0.01
183	MTB-04/44	68.00	68.50	0.49	0.50	0.39	<0.01	0.01	0.04	0.02	<0.01	<0.01
184	MTB-04/45	68.50	69.50	0.98	1.00	0.21	<0.01	0.01	0.03	0.02	<0.01	<0.01
185	MTB-04/46	69.50	70.00	0.49	0.50	0.21	<0.01	0.01	0.04	0.02	<0.01	<0.01
186	MTB-04/47	70.00	71.00	0.97	1.00	0.08	<0.01	0.01	0.03	0.01	<0.01	<0.01
187	MTB-04/48	71.00	72.00	0.97	1.00	0.11	<0.01	0.01	0.03	0.01	<0.01	<0.01
188	MTB-04/49	72.00	73.00	0.97	1.00	0.05	<0.01	0.01	0.03	0.01	<0.01	<0.01
189	MTB-04/50	73.00	73.50	0.50	0.50	0.45	<0.01	0.01	0.03	0.01	<0.01	<0.01
190	MTB-04/51	73.50	74.00	0.50	0.50	0.23	<0.01	0.01	0.03	0.01	<0.01	<0.01
191	MTB-04/52	74.00	74.50	0.50	0.50	0.17	<0.01	0.01	0.02	0.01	<0.01	<0.01
192	MTB-04/53	74.50	75.00	0.50	0.50	0.01	<0.01	0.01	0.02	0.01	<0.01	<0.01
193	MTB-04/54	75.00	75.50	0.50	0.50	0.18	<0.01	0.01	0.02	0.01	<0.01	<0.01
194	MTB-04/55	75.50	76.00	0.50	0.50	0.22	<0.01	0.01	0.02	0.01	<0.01	<0.01
195	MTB-04/56	76.00	76.50	0.50	0.50	0.19	<0.01	0.01	0.02	0.02	<0.01	<0.01
196	MTB-04/57	76.50	77.00	0.50	0.50	0.25	<0.01	0.01	0.02	0.02	<0.01	<0.01
197	MTB-04/58	77.00	77.50	0.50	0.50	0.17	<0.01	0.01	0.03	0.01	<0.01	<0.01
198	MTB-04/59	77.50	78.25	0.75	0.75	0.34	<0.01	0.01	0.02	0.01	<0.01	<0.01
199	MTB-04/60	78.25	79.00	0.75	0.75	0.06	<0.01	0.01	0.02	0.01	<0.01	<0.01
200	MTB-04/61	79.00	79.50	0.49	0.50	0.14	<0.01	0.01	0.02	0.01	<0.01	<0.01
201	MTB-04/62	79.50	80.00	0.49	0.50	0.01	<0.01	0.01	0.02	<0.01	<0.01	<0.01
202	MTB-04/63	80.00	80.50	0.49	0.50	0.28	<0.01	0.01	0.02	0.01	<0.01	<0.01
203	MTB-04/64	80.50	81.00	0.49	0.50	0.34	<0.01	0.01	0.03	0.01	<0.01	<0.01
204	MTB-04/65	81.00	82.00	0.98	1.00	0.01	<0.01	0.01	0.02	0.01	<0.01	<0.01
Borehole No: MTB-05												
205	MTB-05/01	69.00	70.00	1.00	1.00	0.05	<0.01	0.01	0.01	0.01	<0.01	<0.01
206	MTB-05/02	70.00	70.50	0.49	0.50	0.19	<0.01	0.01	0.03	0.01	<0.01	0.01
207	MTB-05/03	70.50	71.00	0.49	0.50	0.14	<0.01	0.01	0.05	<0.01	0.01	<0.01
208	MTB-05/04	71.00	71.50	0.49	0.50	0.07	<0.01	0.01	0.02	<0.01	<0.01	<0.01
209	MTB-05/05	71.50	72.00	0.49	0.50	0.09	<0.01	0.01	0.01	0.01	0.01	<0.01
210	MTB-05/06	72.00	72.50	0.49	0.50	0.12	<0.01	0.01	0.02	0.01	<0.01	<0.01
211	MTB-05/07	72.50	73.00	0.49	0.50	0.21	<0.01	0.01	0.02	0.01	0.01	<0.01
212	MTB-05/08	73.00	73.50	0.50	0.50	0.14	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
213	MTB-05/09	73.50	74.00	0.50	0.50	0.06	<0.01	0.01	0.03	0.01	<0.01	<0.01
214	MTB-05/10	74.00	74.50	0.50	0.50	0.06	<0.01	0.01	0.03	0.01	<0.01	<0.01
215	MTB-05/11	74.50	75.50	1.00	1.00	0.02	<0.01	<0.01	0.03	0.01	<0.01	<0.01
216	MTB-05/12	75.50	76.50	0.98	1.00	0.02	<0.01	0.01	0.01	<0.01	<0.01	<0.01
217	MTB-05/13	76.50	77.50	0.98	1.00	0.08	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
218	MTB-05/14	77.50	78.00	0.49	0.50	0.03	<0.01	0.01	0.01	<0.01	<0.01	<0.01
219	MTB-05/15	78.00	78.50	0.49	0.50	0.33	<0.01	0.01	0.02	0.01	<0.01	<0.01
220	MTB-05/16	78.50	79.00	0.49	0.50	0.07	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
221	MTB-05/17	79.00	80.00	0.97	1.00	0.07	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
222	MTB-05/18	80.00	80.50	0.49	0.50	0.03	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01
223	MTB-05/19	80.50	81.00	0.48	0.50	0.87	<0.01	0.01	0.02	0.01	0.01	<0.01
224	MTB-05/20	81.00	81.50	0.49	0.50	1.30	<0.01	<0.01	0.02	0.01	<0.01	<0.01
225	MTB-05/21	81.50	82.00	0.40	0.50	0.08	<0.01	0.01	0.01	0.01	<0.01	<0.01
226	MTB-05/22	82.00	83.00	0.99	1.00	0.06	<0.01	0.01	0.01	<0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
228	MTB-05/24	84.00	84.50	0.49	0.50	0.08	<0.01	0.01	0.02	0.01	<0.01	<0.01
229	MTB-05/25	84.50	85.00	0.50	0.50	0.06	<0.01	0.01	0.01	0.01	<0.01	<0.01
230	MTB-05/26	85.00	85.50	0.49	0.50	0.31	<0.01	0.01	0.01	<0.01	<0.01	<0.01
231	MTB-05/27	85.50	86.00	0.49	0.50	0.39	<0.01	0.01	0.03	0.01	<0.01	<0.01
232	MTB-05/28	86.00	86.50	0.49	0.50	0.14	<0.01	0.01	0.03	0.01	<0.01	<0.01
233	MTB-05/29	86.50	86.90	0.40	0.40	0.21	<0.01	0.01	0.03	0.01	<0.01	<0.01
234	MTB-05/30	86.90	87.30	0.40	0.40	5.29	<0.01	0.01	0.08	0.02	0.01	<0.01
235	MTB-05/31	87.30	87.70	0.40	0.40	5.27	<0.01	0.01	0.10	0.03	0.02	<0.01
236	MTB-05/32	87.70	88.20	0.47	0.50	0.95	<0.01	0.01	0.07	0.02	<0.01	<0.01
237	MTB-05/33	88.20	88.70	0.49	0.50	0.33	<0.01	0.01	0.05	0.02	<0.01	<0.01
238	MTB-05/34	88.70	89.20	0.48	0.50	2.96	<0.01	0.01	0.07	0.01	0.01	<0.01
239	MTB-05/35	89.20	89.70	0.48	0.50	1.35	<0.01	0.01	0.07	0.01	0.01	<0.01
240	MTB-05/36	89.70	90.20	0.49	0.50	1.40	<0.01	0.01	0.04	0.01	<0.01	<0.01
241	MTB-05/37	90.20	90.70	0.48	0.50	0.27	<0.01	0.01	0.03	<0.01	<0.01	<0.01
242	MTB-05/38	90.70	91.20	0.48	0.50	0.08	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
243	MTB-05/39	91.20	91.70	0.48	0.50	0.05	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
244	MTB-05/40	91.70	92.20	0.49	0.50	0.12	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
245	MTB-05/41	92.20	92.70	0.48	0.50	0.03	<0.01	0.01	0.01	<0.01	<0.01	<0.01
246	MTB-05/42	92.70	93.20	0.49	0.50	0.02	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
247	MTB-05/43	93.20	93.70	0.48	0.50	0.02	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
248	MTB-05/44	93.70	94.20	0.49	0.50	0.46	0.01	0.01	0.02	<0.01	<0.01	<0.01
249	MTB-05/45	94.20	95.20	1.98	1.00	0.17	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
250	MTB-05/46	95.20	96.20	0.99	1.00	0.02	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
251	MTB-05/47	96.20	96.50	0.30	0.30	0.04	<0.01	<0.01	0.03	<0.01	<0.01	<0.01
252	MTB-05/48	96.50	97.00	0.49	0.50	3.91	0.01	0.01	0.09	0.02	0.01	<0.01
253	MTB-05/49	97.00	98.00	1.00	1.00	0.11	<0.01	0.01	0.02	<0.01	<0.01	0.01
254	MTB-05/50	98.00	98.50	0.50	0.50	0.11	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
255	MTB-05/51	98.50	99.00	0.50	0.50	0.56	<0.01	<0.01	0.03	<0.01	<0.01	<0.01
256	MTB-05/52	99.00	99.50	0.50	0.50	1.26	<0.01	<0.01	0.03	0.01	<0.01	<0.01
257	MTB-05/53	99.50	100.00	0.50	0.50	0.07	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
258	MTB-05/54	100.00	101.00	1.00	1.00	0.24	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
259	MTB-05/55	104.50	105.50	0.95	1.00	0.06	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
260	MTB-05/56	105.50	106.00	0.48	0.50	0.07	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
261	MTB-05/57	106.00	106.50	0.48	0.50	2.48	<0.01	<0.01	0.09	<0.01	<0.01	<0.01
262	MTB-05/58	106.50	107.00	0.48	0.50	0.10	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
263	MTB-05/59	107.00	107.50	0.48	0.50	1.32	<0.01	<0.01	0.03	<0.01	<0.01	<0.01
264	MTB-05/60	107.50	108.00	0.48	0.50	2.88	0.01	0.01	0.07	0.02	<0.01	<0.01
265	MTB-05/61	108.00	109.00	0.96	1.00	0.05	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
Borehole No: MTB-06												
266	MTB-06/01	41.00	42.00	1.00	1.00	0.01	<0.01	0.01	0.23	0.01	<0.01	<0.01
267	MTB-06/02	42.00	42.50	0.50	0.50	0.11	<0.01	<0.01	0.06	0.01	0.01	<0.01
268	MTB-06/03	42.50	43.00	0.50	0.50	0.18	<0.01	<0.01	0.12	0.02	0.01	<0.01
269	MTB-06/04	43.00	43.50	0.50	0.50	0.30	<0.01	<0.01	0.10	0.03	<0.01	<0.01
270	MTB-06/05	43.50	44.00	0.50	0.50	0.20	<0.01	<0.01	0.17	0.05	<0.01	<0.01
271	MTB-06/06	44.00	44.50	0.50	0.50	0.32	<0.01	<0.01	0.26	0.06	<0.01	<0.01
272	MTB-06/07	44.50	45.00	0.50	0.50	0.14	<0.01	<0.01	0.19	0.04	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
274	MTB-06/09	45.50	46.00	0.50	0.50	0.29	<0.01	<0.01	0.06	0.02	<0.01	<0.01
275	MTB-06/10	46.00	46.50	0.50	0.50	0.02	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
276	MTB-06/11	46.50	47.50	1.00	1.00	0.02	<0.01	0.01	0.02	0.01	<0.01	<0.01
277	MTB-06/12	78.50	79.50	0.98	1.00	0.02	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
278	MTB-06/13	79.50	80.00	0.50	0.50	0.28	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
279	MTB-06/14	80.00	80.30	0.30	0.30	<0.01	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
280	MTB-06/15	80.30	80.80	0.50	0.50	0.07	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
281	MTB-06/16	80.80	81.80	1.00	1.00	0.03	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
282	MTB-06/17	81.80	82.40	0.58	0.60	0.01	<0.01	<0.01	0.03	0.01	<0.01	<0.01
283	MTB-06/18	82.40	83.00	0.56	0.60	0.01	<0.01	0.01	0.03	0.01	<0.01	<0.01
284	MTB-06/19	83.00	83.50	0.47	0.50	0.06	<0.01	0.01	0.03	0.01	<0.01	<0.01
285	MTB-06/20	83.50	84.00	0.47	0.50	0.08	<0.01	<0.01	0.03	<0.01	<0.01	<0.01
286	MTB-06/21	84.00	84.50	0.47	0.50	1.64	<0.01	<0.01	0.03	0.01	0.01	<0.01
287	MTB-06/22	84.50	85.00	0.47	0.50	0.24	<0.01	<0.01	0.02	0.01	<0.01	<0.01
288	MTB-06/23	85.00	85.50	0.50	0.50	0.27	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
289	MTB-06/24	85.50	86.00	0.50	0.50	0.05	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
290	MTB-06/25	86.00	86.50	0.50	0.50	0.11	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
291	MTB-06/26	86.50	87.00	0.50	0.50	0.12	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
292	MTB-06/27	87.00	87.50	0.50	0.50	0.39	<0.01	<0.01	0.03	<0.01	<0.01	<0.01
293	MTB-06/28	87.50	88.00	0.50	0.50	0.21	<0.01	<0.01	0.04	<0.01	<0.01	<0.01
294	MTB-06/29	88.00	88.50	0.50	0.50	0.32	<0.01	<0.01	0.03	0.01	<0.01	<0.01
295	MTB-06/30	88.50	89.00	0.50	0.50	0.59	<0.01	<0.01	0.03	0.01	<0.01	<0.01
296	MTB-06/31	89.00	89.50	0.50	0.50	4.22	<0.01	<0.01	0.06	0.02	<0.01	<0.01
297	MTB-06/32	89.50	90.00	0.50	0.50	0.78	<0.01	<0.01	0.05	0.01	<0.01	<0.01
298	MTB-06/33	90.00	90.50	0.50	0.50	0.05	<0.01	<0.01	0.03	0.01	<0.01	<0.01
299	MTB-06/34	90.50	91.00	0.50	0.50	0.47	<0.01	<0.01	0.03	0.01	<0.01	<0.01
300	MTB-06/35	91.00	91.50	0.50	0.50	0.03	<0.01	<0.01	0.03	0.01	<0.01	<0.01
301	MTB-06/36	91.50	92.50	1.00	1.00	0.02	<0.01	<0.01	0.03	0.01	<0.01	<0.01
302	MTB-06/37	103.00	104.00	1.00	1.00	0.02	<0.01	<0.01	0.03	0.01	<0.01	<0.01
303	MTB-06/38	104.00	104.50	0.50	0.50	0.24	<0.01	<0.01	0.06	0.01	<0.01	<0.01
304	MTB-06/39	104.50	105.00	0.50	0.50	0.19	<0.01	<0.01	0.03	0.01	<0.01	<0.01
305	MTB-06/40	105.00	105.50	0.50	0.50	0.14	<0.01	<0.01	0.03	0.01	<0.01	<0.01
306	MTB-06/41	105.50	106.00	0.50	0.50	0.09	<0.01	<0.01	0.03	0.01	<0.01	<0.01
307	MTB-06/42	106.00	106.50	0.50	0.50	0.04	<0.01	<0.01	0.03	0.01	<0.01	<0.01
308	MTB-06/43	106.50	107.00	0.50	0.50	0.18	<0.01	<0.01	0.03	0.01	<0.01	<0.01
309	MTB-06/44	107.00	107.50	0.50	0.50	0.23	<0.01	<0.01	0.03	0.01	<0.01	<0.01
310	MTB-06/45	107.50	108.00	0.50	0.50	0.08	<0.01	<0.01	0.03	0.01	<0.01	<0.01
311	MTB-06/46	108.00	108.50	0.50	0.50	0.16	<0.01	<0.01	0.02	0.01	0.01	<0.01
312	MTB-06/47	108.50	109.00	0.49	0.50	0.11	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
313	MTB-06/48	109.00	109.50	0.50	0.50	0.10	<0.01	<0.01	0.03	0.01	<0.01	<0.01
314	MTB-06/49	109.50	110.00	0.50	0.50	0.10	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
315	MTB-06/50	110.00	111.00	1.00	1.00	0.13	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
316	MTB-06/51	114.00	115.00	1.00	1.00	0.07	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
317	MTB-06/52	115.00	115.50	0.50	0.50	0.03	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
318	MTB-06/53	115.50	116.00	0.50	0.50	0.41	<0.01	<0.01	0.03	0.01	<0.01	<0.01
319	MTB-06/54	116.00	116.50	0.50	0.50	0.15	<0.01	<0.01	0.03	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
321	MTB-06/56	117.00	117.50	0.50	0.50	1.01	<0.01	<0.01	0.03	0.01	<0.01	<0.01
322	MTB-06/57	117.50	118.00	0.49	0.50	0.50	<0.01	<0.01	0.03	0.01	<0.01	<0.01
323	MTB-06/58	118.00	118.50	0.50	0.50	0.44	<0.01	<0.01	0.02	0.01	<0.01	<0.01
324	MTB-06/59	118.50	119.50	1.00	1.00	0.02	<0.01	<0.01	0.02	0.01	<0.01	<0.01
325	MTB-06/60	119.50	120.00	0.50	0.50	0.05	<0.01	<0.01	0.02	0.01	<0.01	0.01
326	MTB-06/61	120.00	120.50	0.50	0.50	0.15	<0.01	<0.01	0.03	0.01	<0.01	<0.01
327	MTB-06/62	120.50	121.00	0.50	0.50	0.58	<0.01	<0.01	0.02	0.01	<0.01	<0.01
328	MTB-06/63	121.00	121.50	0.50	0.50	0.83	<0.01	<0.01	0.02	0.01	<0.01	<0.01
329	MTB-06/64	121.50	122.00	0.50	0.50	1.12	<0.01	<0.01	0.02	0.01	<0.01	<0.01
330	MTB-06/65	122.00	122.60	0.60	0.60	0.13	<0.01	<0.01	0.02	0.01	<0.01	<0.01
331	MTB-06/66	122.60	123.20	0.60	0.60	0.13	<0.01	<0.01	0.04	0.01	<0.01	<0.01
332	MTB-06/67	123.20	123.80	0.60	0.60	0.09	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
333	MTB-06/68	123.80	124.30	0.50	0.50	0.27	<0.01	<0.01	0.02	0.01	0.01	<0.01
334	MTB-06/69	124.30	124.80	0.50	0.50	0.10	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
335	MTB-06/70	124.80	125.80	1.00	1.00	0.06	<0.01	<0.01	0.01	0.01	<0.01	<0.01
336	MTB-06/71	125.80	126.80	1.00	1.00	0.12	<0.01	<0.01	0.01	0.01	<0.01	<0.01
337	MTB-06/72	126.80	127.80	1.00	1.00	0.04	<0.01	<0.01	0.01	0.01	<0.01	<0.01
338	MTB-06/73	127.80	128.30	0.50	0.50	0.13	<0.01	<0.01	0.02	0.01	<0.01	<0.01
339	MTB-06/74	128.30	128.80	0.50	0.50	0.03	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
340	MTB-06/75	128.80	129.30	0.50	0.50	0.28	<0.01	<0.01	0.01	0.01	<0.01	<0.01
341	MTB-06/76	129.30	129.80	0.50	0.50	0.04	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
342	MTB-06/77	129.80	130.55	0.75	0.75	0.04	<0.01	<0.01	0.01	0.01	<0.01	<0.01
343	MTB-06/78	130.55	131.30	0.75	0.75	0.04	<0.01	<0.01	0.01	<0.01	<0.01	0.01
344	MTB-06/79	131.30	131.80	0.50	0.50	0.14	<0.01	<0.01	0.01	0.01	<0.01	<0.01
345	MTB-06/80	131.80	132.30	0.50	0.50	0.51	<0.01	<0.01	0.03	0.02	<0.01	<0.01
346	MTB-06/81	132.30	132.80	0.50	0.50	0.45	<0.01	<0.01	0.03	0.02	<0.01	<0.01
347	MTB-06/82	132.80	133.30	0.50	0.50	0.29	<0.01	<0.01	0.01	0.01	<0.01	<0.01
348	MTB-06/83	133.30	133.80	0.50	0.50	0.08	<0.01	<0.01	0.02	0.01	<0.01	<0.01
349	MTB-06/84	133.80	134.30	0.50	0.50	0.10	<0.01	<0.01	0.03	0.02	<0.01	<0.01
350	MTB-06/85	134.30	134.80	0.50	0.50	0.13	<0.01	<0.01	0.02	0.01	<0.01	<0.01
351	MTB-06/86	134.80	135.30	0.50	0.50	0.07	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
352	MTB-06/87	135.30	136.30	1.00	1.00	0.02	<0.01	<0.01	0.01	0.01	<0.01	<0.01
Borehole No: MTB-07												
353	MTB-07/01	46.50	47.50	0.69	1.00	0.04	<0.01	<0.01	0.03	0.01	<0.01	<0.01
354	MTB-07/02	47.50	48.25	0.51	0.75	0.29	<0.01	<0.01	0.05	0.02	0.01	<0.01
355	MTB-07/03	48.25	49.00	0.51	0.75	0.17	<0.01	<0.01	0.04	0.02	<0.01	<0.01
356	MTB-07/04	49.00	50.00	0.98	1.00	0.04	<0.01	<0.01	0.01	0.01	<0.01	<0.01
357	MTB-07/05	50.00	50.60	0.59	0.60	0.15	<0.01	<0.01	0.04	0.01	<0.01	0.04
358	MTB-07/06	50.60	51.20	0.59	0.60	0.10	<0.01	<0.01	0.06	0.02	<0.01	<0.01
359	MTB-07/07	51.20	51.70	0.50	0.50	0.55	<0.01	0.01	0.07	0.03	0.01	<0.01
360	MTB-07/08	51.70	52.10	0.40	0.40	0.01	<0.01	0.01	0.06	0.02	<0.01	<0.01
361	MTB-07/09	52.10	52.60	0.49	0.50	0.22	<0.01	<0.01	0.03	0.01	0.01	<0.01
362	MTB-07/10	52.60	53.10	0.49	0.50	0.28	<0.01	<0.01	0.02	0.01	<0.01	<0.01
363	MTB-07/11	53.10	53.60	0.49	0.50	0.48	<0.01	<0.01	0.03	0.01	<0.01	0.01
364	MTB-07/12	53.60	54.10	0.49	0.50	0.84	<0.01	<0.01	0.05	0.02	<0.01	<0.01
365	MTB-07/13	54.10	54.60	0.49	0.50	0.09	<0.01	0.01	0.03	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
367	MTB-07/15	55.10	55.80	0.69	0.70	0.07	<0.01	<0.01	0.02	0.01	<0.01	<0.01
368	MTB-07/16	55.80	56.50	0.69	0.70	0.11	<0.01	<0.01	0.02	0.01	<0.01	<0.01
369	MTB-07/17	56.50	57.00	0.49	0.50	0.31	<0.01	<0.01	0.03	0.01	<0.01	<0.01
370	MTB-07/18	57.00	57.50	0.50	0.50	1.41	<0.01	<0.01	0.06	0.02	0.01	<0.01
371	MTB-07/19	57.50	58.00	0.50	0.50	0.27	<0.01	<0.01	0.03	0.01	<0.01	<0.01
372	MTB-07/20	58.00	58.50	0.49	0.50	0.16	<0.01	<0.01	0.03	0.01	0.01	<0.01
373	MTB-07/21	58.50	59.00	0.49	0.50	0.22	<0.01	0.01	0.04	0.02	<0.01	<0.01
374	MTB-07/22	59.00	59.50	0.49	0.50	0.38	<0.01	<0.01	0.03	0.01	<0.01	<0.01
375	MTB-07/23	59.50	60.00	0.49	0.50	0.18	<0.01	<0.01	0.02	0.01	<0.01	<0.01
376	MTB-07/24	60.00	60.50	0.49	0.50	0.04	<0.01	<0.01	0.02	0.01	<0.01	<0.01
377	MTB-07/25	60.50	61.00	0.49	0.50	0.18	<0.01	<0.01	0.05	0.02	0.01	<0.01
378	MTB-07/26	61.00	61.50	0.50	0.50	0.18	<0.01	<0.01	0.05	0.01	<0.01	<0.01
379	MTB-07/27	61.50	62.00	0.50	0.50	0.36	<0.01	<0.01	0.04	0.02	<0.01	<0.01
380	MTB-07/28	62.00	62.50	0.50	0.50	0.12	<0.01	<0.01	0.03	0.01	<0.01	<0.01
381	MTB-07/29	62.50	63.00	0.50	0.50	0.03	<0.01	<0.01	0.05	0.02	<0.01	<0.01
382	MTB-07/30	63.00	63.50	0.50	0.50	0.02	<0.01	<0.01	0.02	0.01	<0.01	<0.01
383	MTB-07/31	63.50	64.00	0.50	0.50	0.29	<0.01	<0.01	0.04	0.02	<0.01	<0.01
384	MTB-07/32	64.00	64.50	0.50	0.50	1.33	<0.01	<0.01	0.06	0.03	0.02	<0.01
385	MTB-07/33	64.50	65.00	0.50	0.50	0.13	<0.01	0.01	0.04	0.02	<0.01	<0.01
386	MTB-07/34	65.00	65.50	0.50	0.50	0.75	<0.01	<0.01	0.05	0.03	<0.01	<0.01
387	MTB-07/35	65.50	66.00	0.50	0.50	0.44	<0.01	<0.01	0.05	0.02	0.01	<0.01
388	MTB-07/36	66.00	66.50	0.50	0.50	0.27	<0.01	<0.01	0.03	0.02	<0.01	<0.01
389	MTB-07/37	66.50	67.00	0.50	0.50	0.34	<0.01	<0.01	0.02	0.01	<0.01	<0.01
390	MTB-07/38	67.00	67.50	0.50	0.50	0.04	<0.01	<0.01	0.02	0.02	<0.01	<0.01
391	MTB-07/39	67.50	68.00	0.50	0.50	4.94	<0.01	<0.01	0.06	0.04	0.01	<0.01
392	MTB-07/40	68.00	68.50	0.50	0.50	1.42	<0.01	<0.01	0.03	0.03	0.01	<0.01
393	MTB-07/41	68.50	69.50	0.99	1.00	0.16	<0.01	<0.01	0.01	0.01	<0.01	<0.01
394	MTB-07/42	69.50	70.50	0.99	1.00	0.07	<0.01	<0.01	0.02	0.01	<0.01	<0.01
395	MTB-07/43	70.50	71.50	1.00	1.00	0.08	<0.01	<0.01	0.02	0.01	<0.01	<0.01
396	MTB-07/44	71.50	72.00	0.50	0.50	0.17	<0.01	0.01	0.05	0.02	<0.01	<0.01
397	MTB-07/45	72.00	72.50	0.50	0.50	0.05	<0.01	<0.01	0.03	0.02	<0.01	<0.01
398	MTB-07/46	72.50	73.50	1.00	1.00	0.12	<0.01	<0.01	0.03	0.01	<0.01	<0.01
399	MTB-07/47	73.50	74.00	0.50	0.50	0.35	<0.01	0.01	0.04	0.02	<0.01	<0.01
400	MTB-07/48	74.00	74.50	0.50	0.50	0.36	<0.01	<0.01	0.03	0.01	<0.01	<0.01
401	MTB-07/49	74.50	75.00	0.50	0.50	0.24	<0.01	<0.01	0.02	0.01	<0.01	<0.01
402	MTB-07/50	75.00	75.50	0.50	0.50	0.13	<0.01	<0.01	0.02	0.01	<0.01	<0.01
403	MTB-07/51	75.50	76.00	0.50	0.50	0.12	<0.01	<0.01	0.03	0.01	<0.01	<0.01
404	MTB-07/52	76.00	76.50	0.49	0.50	0.43	<0.01	<0.01	0.06	0.02	<0.01	0.01
405	MTB-07/53	76.50	77.00	0.50	0.50	0.30	<0.01	<0.01	0.06	0.02	<0.01	<0.01
406	MTB-07/54	77.00	77.50	0.50	0.50	0.13	<0.01	0.01	0.03	0.01	0.01	<0.01
407	MTB-07/55	77.50	78.00	0.50	0.50	0.23	<0.01	0.01	0.03	0.01	<0.01	<0.01
408	MTB-07/56	78.00	79.00	0.98	1.00	0.01	<0.01	<0.01	0.03	0.01	<0.01	<0.01
409	MTB-07/57	79.00	80.00	0.93	1.00	0.34	<0.01	<0.01	0.03	0.01	<0.01	<0.01
410	MTB-07/58	80.00	81.00	0.93	1.00	0.06	<0.01	<0.01	0.03	0.01	<0.01	<0.01
411	MTB-07/59	85.50	86.50	1.00	1.00	0.08	<0.01	0.01	0.03	0.01	<0.01	<0.01
412	MTB-07/60	86.50	87.00	0.50	0.50	0.22	<0.01	0.01	0.03	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
414	MTB-07/62	87.50	88.00	0.50	0.50	0.17	<0.01	0.01	0.03	0.01	0.01	<0.01
415	MTB-07/63	88.00	89.00	1.00	1.00	0.07	<0.01	<0.01	0.02	0.01	<0.01	<0.01
416	MTB-07/64	93.00	94.00	1.00	1.00	0.07	<0.01	0.01	0.02	0.01	<0.01	<0.01
417	MTB-07/65	94.00	94.50	0.42	0.50	0.09	<0.01	0.01	0.03	0.01	<0.01	<0.01
418	MTB-07/66	94.50	95.00	0.42	0.50	0.49	<0.01	0.01	0.03	0.02	<0.01	<0.01
419	MTB-07/67	95.00	95.50	0.42	0.50	0.57	<0.01	0.01	0.02	0.01	<0.01	0.01
420	MTB-07/68	95.50	96.00	0.42	0.50	0.06	<0.01	0.01	0.02	0.02	<0.01	<0.01
421	MTB-07/69	96.00	97.00	1.00	1.00	0.10	<0.01	<0.01	0.02	0.01	<0.01	<0.01
422	MTB-07/70	97.00	97.50	0.49	0.50	0.24	<0.01	0.01	0.02	0.01	<0.01	<0.01
423	MTB-07/71	97.50	98.00	0.49	0.50	0.15	<0.01	0.01	0.03	0.01	<0.01	<0.01
424	MTB-07/72	98.00	99.00	1.00	1.00	0.07	<0.01	<0.01	0.01	0.01	<0.01	<0.01
425	MTB-07/73	99.00	100.00	1.00	1.00	0.07	<0.01	0.01	0.03	0.01	<0.01	<0.01
426	MTB-07/74	100.00	100.50	0.50	0.50	0.52	<0.01	0.01	0.03	0.01	<0.01	<0.01
427	MTB-07/75	100.50	101.00	0.50	0.50	0.05	<0.01	0.01	0.05	0.02	<0.01	<0.01
428	MTB-07/76	101.00	101.50	0.50	0.50	0.08	<0.01	0.01	0.05	0.02	<0.01	<0.01
429	MTB-07/77	101.50	102.00	0.50	0.50	0.68	<0.01	0.01	0.05	0.01	<0.01	<0.01
430	MTB-07/78	102.00	102.50	0.50	0.50	0.41	<0.01	0.01	0.04	0.01	<0.01	<0.01
431	MTB-07/79	102.50	103.00	0.50	0.50	0.34	<0.01	0.01	0.03	0.02	<0.01	<0.01
432	MTB-07/80	103.00	103.50	0.50	0.50	0.34	<0.01	0.01	0.05	0.02	<0.01	<0.01
433	MTB-07/81	103.50	104.00	0.50	0.50	0.97	<0.01	0.01	0.05	0.01	<0.01	<0.01
434	MTB-07/82	104.00	104.50	0.50	0.50	0.82	<0.01	0.01	0.05	0.01	<0.01	<0.01
435	MTB-07/83	104.50	105.00	0.50	0.50	0.74	<0.01	<0.01	0.03	0.01	<0.01	<0.01
436	MTB-07/84	105.00	106.00	1.00	1.00	0.27	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
437	MTB-07/85	106.00	106.50	0.49	0.50	0.57	<0.01	<0.01	0.03	0.01	<0.01	<0.01
438	MTB-07/86	106.50	107.00	0.49	0.50	0.47	<0.01	<0.01	0.04	0.02	<0.01	<0.01
439	MTB-07/87	107.00	107.50	0.49	0.50	0.58	<0.01	<0.01	0.04	0.02	<0.01	<0.01
440	MTB-07/88	107.50	108.00	0.49	0.50	0.26	<0.01	0.01	0.03	0.01	<0.01	<0.01
441	MTB-07/89	108.00	108.50	0.49	0.50	0.41	<0.01	0.01	0.03	0.01	<0.01	<0.01
442	MTB-07/90	108.50	109.00	0.49	0.50	0.70	<0.01	0.01	0.04	0.02	<0.01	<0.01
443	MTB-07/91	109.00	110.00	1.00	1.00	0.17	<0.01	0.01	0.03	0.02	<0.01	<0.01
Borehole No: MTB-08												
444	MTB-08/01	46.50	47.50	1.00	1.00	0.01	<0.01	<0.01	0.05	<0.01	<0.01	<0.01
445	MTB-08/02	47.50	48.00	0.50	0.50	0.25	<0.01	0.01	0.01	0.03	<0.01	<0.01
446	MTB-08/03	48.00	48.50	0.50	0.50	1.11	<0.01	0.01	0.04	0.10	<0.01	<0.01
447	MTB-08/04	48.50	49.00	0.50	0.50	0.93	<0.01	0.01	0.04	0.11	<0.01	<0.01
448	MTB-08/05	49.00	49.50	0.49	0.50	1.08	<0.01	0.01	0.04	0.13	<0.01	<0.01
449	MTB-08/06	49.50	50.00	0.49	0.50	0.55	<0.01	0.01	0.03	0.06	<0.01	<0.01
450	MTB-08/07	50.00	50.50	0.49	0.50	0.90	<0.01	0.01	0.04	0.08	<0.01	<0.01
451	MTB-08/08	50.50	51.00	0.49	0.50	1.59	<0.01	0.01	0.04	0.07	<0.01	<0.01
452	MTB-08/09	51.00	52.00	0.98	1.00	0.06	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
453	MTB-08/10	177.00	178.00	1.00	1.00	0.03	<0.01	<0.01	0.01	0.01	0.01	<0.01
454	MTB-08/11	178.00	178.50	0.50	0.50	0.04	<0.01	<0.01	0.01	0.01	<0.01	<0.01
455	MTB-08/12	178.50	179.00	0.50	0.50	0.11	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
456	MTB-08/13	179.00	179.50	0.50	0.50	0.16	<0.01	<0.01	0.02	0.01	<0.01	<0.01
457	MTB-08/14	179.50	180.00	0.50	0.50	0.06	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
458	MTB-08/15	180.00	181.00	1.00	1.00	0.03	<0.01	<0.01	0.01	<0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
460	MTB-08/17	182.00	183.00	1.00	1.00	0.15	<0.01	0.01	0.02	0.01	0.01	<0.01
461	MTB-08/18	183.00	183.50	0.50	0.50	0.23	<0.01	0.01	0.02	<0.01	0.01	<0.01
462	MTB-08/19	183.50	184.00	0.50	0.50	0.07	<0.01	0.01	0.01	<0.01	<0.01	<0.01
463	MTB-08/20	184.00	184.50	0.50	0.50	0.14	<0.01	0.01	0.02	0.01	0.02	<0.01
464	MTB-08/21	184.50	185.00	0.50	0.50	0.07	<0.01	0.01	0.02	0.01	<0.01	<0.01
465	MTB-08/22	185.00	185.50	0.50	0.50	0.09	<0.01	<0.01	0.02	0.01	<0.01	<0.01
466	MTB-08/23	185.50	186.00	0.50	0.50	0.10	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
467	MTB-08/24	186.00	186.50	0.50	0.50	0.08	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
468	MTB-08/25	186.50	187.00	0.50	0.50	0.09	<0.01	<0.01	0.01	0.01	<0.01	<0.01
469	MTB-08/26	187.00	187.50	0.50	0.50	0.06	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
470	MTB-08/27	187.50	188.00	0.50	0.50	0.11	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
471	MTB-08/28	188.00	188.50	0.50	0.50	0.42	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
472	MTB-08/29	188.50	189.00	0.50	0.50	0.11	<0.01	0.01	0.01	<0.01	<0.01	<0.01
473	MTB-08/30	189.00	189.50	0.50	0.50	0.08	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01
474	MTB-08/31	189.50	190.50	1.00	1.00	0.02	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01
475	MTB-08/32	197.00	198.00	1.00	1.00	0.08	<0.01	0.01	0.01	0.01	<0.01	<0.01
476	MTB-08/33	198.00	198.50	0.50	0.50	0.11	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
477	MTB-08/34	198.50	199.00	0.50	0.50	0.09	<0.01	<0.01	0.01	<0.01	<0.01	0.01
478	MTB-08/35	199.00	199.50	0.50	0.50	0.78	<0.01	0.01	0.03	0.01	<0.01	<0.01
479	MTB-08/36	199.50	200.00	0.50	0.50	0.19	<0.01	0.01	0.01	<0.01	<0.01	<0.01
480	MTB-08/37	200.00	200.50	0.50	0.50	3.28	<0.01	0.01	0.12	0.01	0.01	<0.01
481	MTB-08/38	200.50	201.00	0.50	0.50	2.41	<0.01	<0.01	0.18	0.02	0.01	<0.01
482	MTB-08/39	201.00	201.50	0.50	0.50	1.37	<0.01	<0.01	0.06	0.02	<0.01	<0.01
483	MTB-08/40	201.50	202.00	0.50	0.50	0.03	<0.01	<0.01	0.06	0.02	<0.01	0.01
484	MTB-08/41	202.00	202.50	0.49	0.50	0.65	<0.01	<0.01	0.01	0.01	<0.01	0.02
485	MTB-08/42	202.50	203.00	0.49	0.50	0.27	<0.01	<0.01	0.02	0.02	<0.01	<0.01
486	MTB-08/43	203.00	203.50	0.49	0.50	1.89	0.01	<0.01	0.03	<0.01	<0.01	0.02
487	MTB-08/44	203.50	204.00	0.49	0.50	1.50	<0.01	<0.01	0.01	0.01	<0.01	<0.01
488	MTB-08/45	204.00	204.50	0.49	0.50	2.86	<0.01	0.01	0.07	0.01	<0.01	<0.01
489	MTB-08/46	204.50	205.00	0.49	0.50	0.44	<0.01	<0.01	0.06	0.02	0.02	<0.01
490	MTB-08/47	205.00	205.50	0.50	0.50	2.77	<0.01	<0.01	0.08	0.01	0.16	<0.01
491	MTB-08/48	205.50	206.00	0.50	0.50	0.36	0.01	0.01	0.03	0.01	<0.01	<0.01
492	MTB-08/49	206.00	206.50	0.50	0.50	1.18	0.01	0.01	0.06	0.01	0.12	<0.01
493	MTB-08/50	206.50	207.00	0.50	0.50	0.20	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
494	MTB-08/51	207.00	208.00	1.00	1.00	0.03	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
Borehole No: MTB-09												
495	MTB-09/01	65.50	66.50	1.00	1.00	0.04	<0.01	<0.01	0.03	0.02	<0.01	<0.01
496	MTB-09/02	66.50	67.00	0.50	0.50	0.19	<0.01	<0.01	0.03	0.01	<0.01	<0.01
497	MTB-09/03	67.00	67.50	0.50	0.50	0.19	<0.01	<0.01	0.03	0.01	0.01	<0.01
498	MTB-09/04	67.50	68.50	1.00	1.00	0.04	<0.01	<0.01	0.03	0.01	<0.01	<0.01
499	MTB-09/05	68.50	69.00	0.50	0.50	0.31	<0.01	<0.01	0.03	0.01	<0.01	<0.01
500	MTB-09/06	69.00	69.50	0.50	0.50	0.04	<0.01	<0.01	0.04	0.01	<0.01	<0.01
501	MTB-09/07	69.50	70.00	0.50	0.50	0.35	<0.01	<0.01	0.04	0.01	0.02	<0.01
502	MTB-09/08	70.00	70.50	0.50	0.50	0.21	<0.01	<0.01	0.04	0.01	<0.01	<0.01
503	MTB-09/09	70.50	71.00	0.50	0.50	0.06	<0.01	<0.01	0.03	0.01	<0.01	<0.01
504	MTB-09/10	71.00	71.50	0.50	0.50	0.15	<0.01	<0.01	0.04	0.01	0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
506	MTB-09/12	72.25	73.00	0.75	0.75	0.01	<0.01	<0.01	0.03	0.01	0.01	<0.01
507	MTB-09/13	73.00	74.00	1.00	1.00	<0.01	<0.01	<0.01	0.02	0.01	0.01	<0.01
508	MTB-09/14	74.00	75.00	1.00	1.00	0.01	<0.01	<0.01	0.02	0.01	<0.01	<0.01
509	MTB-09/15	75.00	75.50	0.50	0.50	0.45	<0.01	<0.01	0.03	0.01	0.04	<0.01
510	MTB-09/16	75.50	76.00	0.50	0.50	0.11	<0.01	<0.01	0.03	0.01	<0.01	<0.01
511	MTB-09/17	76.00	76.50	0.50	0.50	0.19	<0.01	<0.01	0.02	0.01	<0.01	<0.01
512	MTB-09/18	76.50	77.00	0.50	0.50	0.09	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
513	MTB-09/19	77.00	77.50	0.50	0.50	0.11	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
514	MTB-09/20	77.50	78.00	0.50	0.50	0.19	<0.01	<0.01	0.03	0.01	<0.01	<0.01
515	MTB-09/21	78.00	78.50	0.50	0.50	0.55	<0.01	<0.01	0.05	0.01	0.01	<0.01
516	MTB-09/22	78.50	79.25	0.75	0.75	0.06	<0.01	0.01	0.05	0.01	<0.01	<0.01
517	MTB-09/23	79.25	79.75	0.49	0.50	0.17	<0.01	0.01	0.02	0.01	<0.01	<0.01
518	MTB-09/24	79.75	80.75	0.97	1.00	0.02	<0.01	<0.01	0.02	0.01	<0.01	<0.01
519	MTB-09/25	80.75	81.25	0.49	0.50	0.13	<0.01	<0.01	0.01	0.01	<0.01	<0.01
520	MTB-09/26	81.25	82.25	0.97	1.00	0.04	<0.01	<0.01	0.01	0.01	<0.01	<0.01
521	MTB-09/27	85.00	86.00	0.99	1.00	0.06	<0.01	<0.01	0.02	0.01	<0.01	<0.01
522	MTB-09/28	86.00	86.50	0.50	0.50	0.06	<0.01	<0.01	0.03	0.02	<0.01	<0.01
523	MTB-09/29	86.50	87.00	0.50	0.50	0.23	<0.01	<0.01	0.04	0.02	<0.01	<0.01
524	MTB-09/30	87.00	88.00	1.00	1.00	0.07	<0.01	<0.01	0.02	0.01	<0.01	<0.01
525	MTB-09/31	88.00	88.50	0.49	0.50	0.28	<0.01	0.01	0.03	0.01	<0.01	<0.01
526	MTB-09/32	88.50	89.00	0.49	0.50	0.36	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
527	MTB-09/33	89.00	89.50	0.49	0.50	0.18	<0.01	0.01	0.03	0.01	<0.01	<0.01
528	MTB-09/34	89.50	90.00	0.49	0.50	0.01	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
529	MTB-09/35	90.00	90.50	0.49	0.50	0.08	<0.01	<0.01	0.03	0.01	<0.01	<0.01
530	MTB-09/36	90.50	91.00	0.49	0.50	0.30	<0.01	<0.01	0.04	0.02	<0.01	<0.01
531	MTB-09/37	91.00	91.75	0.75	0.75	0.12	<0.01	<0.01	0.02	0.01	<0.01	<0.01
532	MTB-09/38	91.75	92.50	0.75	0.75	0.09	<0.01	<0.01	0.01	0.01	<0.01	<0.01
533	MTB-09/39	92.50	93.00	0.50	0.50	0.08	<0.01	0.01	0.02	0.01	<0.01	<0.01
534	MTB-09/40	93.00	93.50	0.50	0.50	0.23	<0.01	0.01	0.02	0.01	<0.01	<0.01
535	MTB-09/41	93.50	94.00	0.50	0.50	0.03	<0.01	<0.01	0.01	0.01	<0.01	<0.01
536	MTB-09/42	94.00	95.00	1.00	1.00	0.09	<0.01	<0.01	0.01	0.01	<0.01	<0.01
537	MTB-09/43	99.50	100.50	0.49	1.00	0.08	<0.01	<0.01	0.01	0.01	<0.01	<0.01
538	MTB-09/44	100.50	101.00	0.49	0.50	0.54	<0.01	<0.01	0.01	0.01	<0.01	<0.01
539	MTB-09/45	101.00	101.50	0.49	0.50	1.08	<0.01	0.01	0.02	0.01	<0.01	<0.01
540	MTB-09/46	101.50	102.00	0.49	0.50	0.02	<0.01	<0.01	0.01	0.01	<0.01	0.01
541	MTB-09/47	102.00	103.00	1.00	1.00	0.02	<0.01	<0.01	0.01	0.01	<0.01	<0.01
542	MTB-09/48	110.00	111.00	1.00	1.00	0.15	<0.01	<0.01	0.02	0.01	<0.01	<0.01
543	MTB-09/49	111.00	111.50	0.50	0.50	0.27	<0.01	<0.01	0.02	0.01	<0.01	<0.01
544	MTB-09/50	111.50	112.25	0.75	0.75	0.05	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
545	MTB-09/51	112.25	113.00	0.75	0.75	0.01	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
546	MTB-09/52	113.00	113.50	0.50	0.50	0.16	<0.01	0.01	0.02	0.01	<0.01	<0.01
547	MTB-09/53	113.50	114.00	0.50	0.50	0.12	<0.01	<0.01	0.01	0.01	<0.01	<0.01
548	MTB-09/54	114.00	114.50	0.50	0.50	0.07	<0.01	<0.01	0.02	0.01	<0.01	<0.01
549	MTB-09/55	114.50	115.00	0.50	0.50	0.17	<0.01	<0.01	0.02	0.01	<0.01	<0.01
550	MTB-09/56	115.00	115.50	0.50	0.50	0.29	<0.01	<0.01	0.02	0.01	<0.01	<0.01
551	MTB-09/57	115.50	116.50	1.00	1.00	0.05	<0.01	0.01	0.02	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
553	MTB-09/59	122.50	123.00	0.50	0.50	0.13	<0.01	<0.01	0.01	0.01	<0.01	<0.01
554	MTB-09/60	123.00	123.50	0.50	0.50	0.50	<0.01	0.01	0.02	0.01	<0.01	<0.01
555	MTB-09/61	123.50	124.00	0.50	0.50	0.13	<0.01	<0.01	0.02	0.01	<0.01	<0.01
556	MTB-09/62	124.00	124.50	0.50	0.50	0.10	<0.01	<0.01	0.02	0.01	<0.01	<0.01
557	MTB-09/63	124.50	125.50	1.00	1.00	0.04	<0.01	<0.01	0.01	0.01	<0.01	<0.01
Borehole No: MTB-10												
558	MTB-10/001	90.00	91.00	1.00	1.00	<0.01	<0.01	<0.01	0.02	0.01	<0.01	<0.01
559	MTB-10/002	91.00	91.50	0.50	0.50	0.17	<0.01	<0.01	0.04	0.01	<0.01	<0.01
560	MTB-10/003	91.50	92.00	0.50	0.50	0.27	<0.01	<0.01	0.06	0.01	<0.01	<0.01
561	MTB-10/004	92.00	93.00	1.00	1.00	0.06	<0.01	<0.01	0.05	0.01	<0.01	<0.01
562	MTB-10/005	93.00	93.50	0.50	0.50	0.01	<0.01	<0.01	0.03	0.01	<0.01	<0.01
563	MTB-10/006	93.50	94.00	0.50	0.50	0.10	<0.01	<0.01	0.07	0.02	<0.01	<0.01
564	MTB-10/007	94.00	94.50	0.50	0.50	0.05	<0.01	<0.01	0.40	0.08	<0.01	<0.01
565	MTB-10/008	94.50	95.50	1.00	1.00	0.06	<0.01	<0.01	0.09	0.02	0.01	<0.01
566	MTB-10/009	103.50	104.50	1.00	1.00	0.02	<0.01	<0.01	0.04	0.02	<0.01	<0.01
567	MTB-10/010	104.50	105.00	0.50	0.50	0.38	<0.01	<0.01	0.04	0.01	<0.01	<0.01
568	MTB-10/011	105.00	105.50	0.50	0.50	0.01	<0.01	0.01	0.03	0.01	<0.01	<0.01
569	MTB-10/012	105.50	106.50	1.00	1.00	0.01	<0.01	<0.01	0.02	0.01	<0.01	<0.01
570	MTB-10/013	106.50	107.50	1.00	1.00	<0.01	<0.01	<0.01	0.02	0.01	<0.01	0.01
571	MTB-10/014	107.50	108.00	0.50	0.50	0.03	<0.01	<0.01	0.03	0.01	<0.01	<0.01
572	MTB-10/015	108.00	108.50	0.50	0.50	0.09	<0.01	<0.01	0.03	0.01	<0.01	<0.01
573	MTB-10/016	108.50	109.00	0.50	0.50	0.12	<0.01	<0.01	0.03	0.01	<0.01	<0.01
574	MTB-10/017	109.00	109.50	0.50	0.50	0.06	<0.01	<0.01	0.04	0.01	<0.01	<0.01
575	MTB-10/018	109.50	110.00	0.50	0.50	0.37	<0.01	<0.01	0.03	0.01	<0.01	<0.01
576	MTB-10/019	110.00	111.00	1.00	1.00	0.07	<0.01	<0.01	0.02	0.01	<0.01	<0.01
577	MTB-10/020	111.00	112.00	1.00	1.00	0.10	<0.01	<0.01	0.02	0.01	<0.01	<0.01
578	MTB-10/021	112.00	112.75	0.71	0.75	0.03	<0.01	<0.01	0.03	0.01	0.02	<0.01
579	MTB-10/022	112.75	113.25	0.48	0.50	0.13	<0.01	<0.01	0.03	0.01	0.01	<0.01
580	MTB-10/023	113.25	113.75	0.48	0.50	0.01	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
581	MTB-10/024	113.75	114.25	0.48	0.50	0.24	<0.01	<0.01	0.02	0.01	<0.01	<0.01
582	MTB-10/025	114.25	114.75	0.48	0.50	0.06	<0.01	<0.01	0.02	0.01	<0.01	<0.01
583	MTB-10/026	114.75	115.50	0.72	0.75	0.12	<0.01	<0.01	0.03	0.01	<0.01	<0.01
584	MTB-10/027	115.50	116.50	0.96	1.00	0.02	<0.01	<0.01	0.02	0.01	<0.01	<0.01
585	MTB-10/028	116.50	117.00	0.48	0.50	0.12	<0.01	<0.01	0.02	0.01	<0.01	<0.01
586	MTB-10/029	117.00	117.50	0.48	0.50	0.04	<0.01	<0.01	0.02	0.01	<0.01	<0.01
587	MTB-10/030	117.50	118.00	0.48	0.50	0.03	<0.01	<0.01	0.02	0.01	<0.01	<0.01
588	MTB-10/031	118.00	119.00	0.97	1.00	0.12	<0.01	<0.01	0.02	0.01	<0.01	<0.01
589	MTB-10/032	122.50	123.50	1.00	1.00	0.03	<0.01	<0.01	0.02	0.01	<0.01	<0.01
590	MTB-10/033	123.50	124.00	0.50	0.50	0.06	<0.01	0.01	0.02	0.01	<0.01	<0.01
591	MTB-10/034	124.00	124.50	0.50	0.50	0.09	<0.01	0.01	0.02	0.01	<0.01	<0.01
592	MTB-10/035	124.50	125.00	0.50	0.50	0.03	<0.01	0.01	0.02	0.01	<0.01	<0.01
593	MTB-10/036	125.00	125.50	0.50	0.50	0.11	<0.01	0.01	0.03	0.01	<0.01	<0.01
594	MTB-10/037	125.50	126.00	0.50	0.50	0.06	<0.01	0.01	0.02	0.01	<0.01	<0.01
595	MTB-10/038	126.00	126.50	0.50	0.50	0.20	<0.01	<0.01	0.03	0.01	<0.01	<0.01
596	MTB-10/039	126.50	127.00	0.50	0.50	0.13	<0.01	0.01	0.03	0.01	<0.01	<0.01
597	MTB-10/040	127.00	127.50	0.50	0.50	0.02	<0.01	0.01	0.03	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
599	MTB-10/042	128.00	128.50	0.50	0.50	0.18	<0.01	0.01	0.04	0.02	<0.01	<0.01
600	MTB-10/043	128.50	129.00	0.50	0.50	0.07	<0.01	0.01	0.03	0.01	<0.01	<0.01
601	MTB-10/044	129.00	130.00	1.00	1.00	0.01	<0.01	0.01	0.02	0.02	<0.01	<0.01
602	MTB-10/045	130.00	130.50	0.49	0.50	0.01	<0.01	0.01	0.02	0.01	<0.01	<0.01
603	MTB-10/046	130.50	131.00	0.49	0.50	0.09	<0.01	0.01	0.03	0.01	<0.01	<0.01
604	MTB-10/047	131.00	131.50	0.49	0.50	0.40	<0.01	<0.01	0.04	0.02	<0.01	<0.01
605	MTB-10/048	131.50	132.00	0.49	0.50	0.11	<0.01	0.01	0.04	0.02	<0.01	<0.01
606	MTB-10/049	132.00	132.50	0.49	0.50	0.19	<0.01	<0.01	0.05	0.01	<0.01	<0.01
607	MTB-10/050	132.50	133.00	0.49	0.50	0.16	<0.01	<0.01	0.03	0.02	<0.01	<0.01
608	MTB-10/051	133.00	133.50	0.50	0.50	0.10	<0.01	<0.01	0.03	0.01	<0.01	<0.01
609	MTB-10/052	133.50	134.00	0.50	0.50	0.22	<0.01	0.01	0.06	0.02	<0.01	<0.01
610	MTB-10/053	134.00	134.50	0.50	0.50	0.07	<0.01	<0.01	0.03	0.02	<0.01	<0.01
611	MTB-10/054	134.50	135.00	0.50	0.50	0.27	<0.01	0.01	0.05	0.02	<0.01	<0.01
612	MTB-10/055	135.00	135.50	0.50	0.50	0.19	<0.01	0.01	0.05	0.02	<0.01	<0.01
613	MTB-10/056	135.50	136.00	0.50	0.50	0.51	<0.01	0.01	0.05	0.03	<0.01	<0.01
614	MTB-10/057	136.00	136.50	0.50	0.50	0.14	<0.01	0.01	0.04	0.02	<0.01	<0.01
615	MTB-10/058	136.50	137.00	0.50	0.50	0.35	<0.01	0.01	0.04	0.02	<0.01	<0.01
616	MTB-10/059	137.00	137.50	0.50	0.50	0.54	<0.01	0.01	0.05	0.02	<0.01	<0.01
617	MTB-10/060	137.50	138.50	1.00	1.00	0.03	<0.01	<0.01	0.02	0.01	<0.01	<0.01
618	MTB-10/061	138.50	139.00	0.50	0.50	0.21	<0.01	0.01	0.04	0.02	<0.01	<0.01
619	MTB-10/062	139.00	139.50	0.48	0.50	0.30	<0.01	0.01	0.04	0.02	<0.01	<0.01
620	MTB-10/063	139.50	140.00	0.48	0.50	0.55	<0.01	0.01	0.04	0.02	<0.01	<0.01
621	MTB-10/064	140.00	140.50	0.48	0.50	0.29	<0.01	0.01	0.04	0.02	<0.01	<0.01
622	MTB-10/065	140.50	141.00	0.48	0.50	0.83	<0.01	0.01	0.12	0.04	<0.01	<0.01
623	MTB-10/066	141.00	141.50	0.49	0.50	0.03	<0.01	0.01	0.03	0.02	<0.01	<0.01
624	MTB-10/067	141.50	142.00	0.49	0.50	1.08	<0.01	0.01	0.06	0.02	<0.01	<0.01
625	MTB-10/068	142.00	142.50	0.48	0.50	0.47	<0.01	0.01	0.04	0.02	<0.01	<0.01
626	MTB-10/069	142.50	143.00	0.48	0.50	0.19	<0.01	0.01	0.04	0.02	<0.01	<0.01
627	MTB-10/070	143.00	143.50	0.48	0.50	0.19	<0.01	<0.01	0.03	0.02	<0.01	<0.01
628	MTB-10/071	143.50	144.00	0.48	0.50	0.34	<0.01	0.01	0.04	0.01	<0.01	<0.01
629	MTB-10/072	144.00	144.50	0.48	0.50	0.39	<0.01	0.01	0.04	0.02	<0.01	<0.01
630	MTB-10/073	144.50	145.00	0.48	0.50	0.20	<0.01	<0.01	0.02	0.01	<0.01	<0.01
631	MTB-10/074	145.00	145.75	0.75	0.75	0.11	<0.01	0.01	0.02	0.01	<0.01	<0.01
632	MTB-10/075	145.75	146.50	0.75	0.75	0.07	<0.01	0.01	0.01	0.01	<0.01	<0.01
633	MTB-10/076	146.50	147.00	0.50	0.50	0.07	<0.01	0.01	0.01	0.01	<0.01	<0.01
634	MTB-10/077	147.00	147.50	0.50	0.50	0.10	<0.01	0.01	0.02	0.01	<0.01	<0.01
635	MTB-10/078	147.50	148.00	0.50	0.50	0.03	<0.01	0.01	0.02	0.01	<0.01	<0.01
636	MTB-10/079	148.00	148.50	0.50	0.50	0.15	<0.01	0.01	0.02	0.01	<0.01	<0.01
637	MTB-10/080	148.50	149.50	1.00	1.00	0.04	<0.01	0.01	0.01	0.01	<0.01	<0.01
638	MTB-10/081	154.00	155.00	1.00	1.00	0.08	<0.01	0.01	0.02	0.01	<0.01	<0.01
639	MTB-10/082	155.00	155.50	0.50	0.50	0.05	<0.01	0.01	0.02	0.01	<0.01	<0.01
640	MTB-10/083	155.50	156.00	0.50	0.50	0.27	<0.01	0.01	0.02	0.01	<0.01	<0.01
641	MTB-10/084	156.00	156.50	0.50	0.50	0.22	<0.01	0.01	0.02	0.01	<0.01	<0.01
642	MTB-10/085	156.50	157.00	0.50	0.50	0.20	<0.01	0.01	0.03	0.01	<0.01	<0.01
643	MTB-10/086	157.00	157.50	0.50	0.50	0.13	<0.01	0.01	0.02	0.01	<0.01	<0.01
644	MTB-10/087	157.50	158.00	0.50	0.50	0.06	<0.01	0.01	0.02	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
646	MTB-10/089	169.50	170.50	1.00	1.00	0.14	<0.01	0.02	0.02	0.01	<0.01	<0.01
647	MTB-10/090	170.50	171.00	0.50	0.50	0.40	<0.01	0.02	0.03	0.01	<0.01	<0.01
648	MTB-10/091	171.00	171.50	0.50	0.50	0.34	<0.01	0.02	0.02	0.01	<0.01	<0.01
649	MTB-10/092	171.50	172.00	0.50	0.50	0.22	<0.01	0.02	0.02	0.01	<0.01	<0.01
650	MTB-10/093	172.00	172.50	0.50	0.50	0.05	<0.01	0.02	0.02	0.01	<0.01	<0.01
651	MTB-10/094	172.50	173.00	0.50	0.50	0.02	<0.01	0.02	0.02	0.01	<0.01	<0.01
652	MTB-10/095	173.00	174.00	1.00	1.00	0.08	<0.01	0.02	0.01	0.01	<0.01	<0.01
Borehole No: MTB-11												
653	MTB-11/01	75.00	76.00	0.94	1.00	0.02	<0.01	<0.01	0.02	0.01	<0.01	<0.01
654	MTB-11/02	76.00	76.50	0.49	0.50	0.15	<0.01	<0.01	0.03	0.01	<0.01	<0.01
655	MTB-11/03	76.50	77.37	0.85	0.87	0.03	<0.01	<0.01	0.02	0.01	<0.01	<0.01
656	MTB-11/04	77.37	78.25	0.85	0.88	0.04	<0.01	<0.01	0.02	0.01	<0.01	<0.01
657	MTB-11/05	78.25	78.75	0.49	0.50	0.28	<0.01	0.01	0.02	0.02	<0.01	<0.01
658	MTB-11/06	78.75	79.25	0.49	0.50	0.28	<0.01	<0.01	0.02	0.01	<0.01	<0.01
659	MTB-11/07	79.25	79.75	0.50	0.50	0.10	<0.01	<0.01	0.02	0.01	<0.01	<0.01
660	MTB-11/08	79.75	80.25	0.50	0.50	0.14	0.02	<0.01	0.01	0.01	<0.01	<0.01
661	MTB-11/09	80.25	80.75	0.50	0.50	0.13	<0.01	<0.01	0.01	0.01	<0.01	<0.01
662	MTB-11/10	80.75	81.25	0.50	0.50	0.07	<0.01	<0.01	0.01	0.01	<0.01	<0.01
663	MTB-11/11	81.25	81.75	0.50	0.50	0.05	<0.01	<0.01	0.02	0.01	<0.01	<0.01
664	MTB-11/12	81.75	82.25	0.50	0.50	0.19	<0.01	0.01	0.02	0.01	<0.01	<0.01
665	MTB-11/13	82.25	83.25	1.00	1.00	0.03	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
666	MTB-11/14	101.00	102.00	1.00	1.00	0.09	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
667	MTB-11/15	102.00	102.50	0.50	0.50	0.17	<0.01	0.01	0.02	0.01	<0.01	<0.01
668	MTB-11/16	102.50	103.00	0.50	0.50	0.16	<0.01	<0.01	0.01	0.01	<0.01	<0.01
669	MTB-11/17	103.00	103.50	0.50	0.50	0.19	<0.01	<0.01	0.01	0.01	<0.01	<0.01
670	MTB-11/18	103.50	104.00	0.50	0.50	0.26	<0.01	0.01	0.02	0.01	<0.01	<0.01
671	MTB-11/19	104.00	104.50	0.50	0.50	0.15	<0.01	0.01	0.02	0.01	<0.01	<0.01
672	MTB-11/20	104.50	105.00	0.50	0.50	0.18	<0.01	0.01	0.02	0.01	<0.01	<0.01
673	MTB-11/21	105.00	105.50	0.50	0.50	0.06	<0.01	0.01	0.02	0.01	<0.01	<0.01
674	MTB-11/22	105.50	106.00	0.50	0.50	0.06	<0.01	0.01	0.01	0.01	<0.01	<0.01
675	MTB-11/23	106.00	106.50	0.50	0.50	0.24	<0.01	0.01	0.02	0.01	<0.01	<0.01
676	MTB-11/24	106.50	107.50	1.00	1.00	0.03	<0.01	<0.01	0.01	0.01	<0.01	<0.01
677	MTB-11/25	124.50	125.50	0.96	1.00	0.03	<0.01	0.01	0.01	<0.01	<0.01	<0.01
678	MTB-11/26	125.50	126.00	0.48	0.50	0.02	<0.01	0.02	0.01	0.01	<0.01	<0.01
679	MTB-11/27	126.00	126.50	0.48	0.50	0.22	<0.01	0.03	0.01	0.01	<0.01	0.01
680	MTB-11/28	126.50	127.00	0.48	0.50	0.06	<0.01	0.04	<0.01	0.01	<0.01	<0.01
681	MTB-11/29	127.00	128.00	1.00	1.00	0.03	<0.01	0.03	0.01	<0.01	<0.01	<0.01
682	MTB-11/30	131.50	132.50	1.00	1.00	0.02	<0.01	0.01	<0.01	<0.01	<0.01	<0.01
683	MTB-11/31	132.50	133.00	0.50	0.50	0.02	<0.01	0.02	0.01	0.01	<0.01	<0.01
684	MTB-11/32	133.00	133.50	0.46	0.50	0.11	<0.01	0.03	0.02	0.02	<0.01	<0.01
685	MTB-11/33	133.50	134.00	0.47	0.50	0.64	<0.01	0.02	0.01	0.01	<0.01	<0.01
686	MTB-11/34	134.00	135.00	0.93	1.00	0.05	<0.01	0.01	0.01	<0.01	<0.01	<0.01
687	MTB-11/35	141.50	142.50	1.00	1.00	0.22	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01
688	MTB-11/36	142.50	143.00	0.50	0.50	0.38	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
689	MTB-11/37	143.00	143.50	0.50	0.50	0.62	<0.01	0.01	0.01	<0.01	<0.01	<0.01
690	MTB-11/38	143.50	144.50	0.98	1.00	0.10	<0.01	0.02	0.01	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
692	MTB-11/40	145.50	146.00	0.50	0.50	0.19	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
693	MTB-11/41	146.00	146.50	0.50	0.50	0.67	<0.01	0.01	0.01	0.01	<0.01	<0.01
694	MTB-11/42	146.50	147.00	0.50	0.50	0.25	<0.01	0.01	0.01	<0.01	<0.01	<0.01
695	MTB-11/43	147.00	147.50	0.50	0.50	0.14	<0.01	0.01	0.01	<0.01	<0.01	<0.01
696	MTB-11/44	147.50	148.00	0.50	0.50	0.59	<0.01	0.01	0.01	<0.01	<0.01	<0.01
697	MTB-11/45	148.00	148.50	0.50	0.50	0.07	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01
698	MTB-11/46	148.50	149.00	0.50	0.50	0.18	<0.01	<0.01	0.01	0.01	<0.01	<0.01
699	MTB-11/47	149.00	150.00	0.50	1.00	0.04	<0.01	0.03	<0.01	0.01	<0.01	<0.01
700	MTB-11/48	110.00	111.00	1.00	1.00	0.28	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
701	MTB-11/49	111.00	111.50	0.50	0.50	0.30	<0.01	0.02	0.01	0.01	<0.01	<0.01
702	MTB-11/50	111.50	112.25	0.75	0.75	0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01
703	MTB-11/51	112.25	113.00	0.75	0.75	0.02	<0.01	<0.01	0.01	0.01	<0.01	<0.01
Borehole No: MTB-12												
704	MTB-12/001	41.50	42.50	1.00	1.00	0.08	<0.01	0.02	0.02	0.01	<0.01	<0.01
705	MTB-12/002	42.50	43.00	0.50	0.50	0.08	<0.01	0.02	0.02	0.01	<0.01	<0.01
706	MTB-12/003	43.00	43.50	0.50	0.50	0.11	<0.01	0.02	0.02	0.01	<0.01	<0.01
707	MTB-12/004	43.50	44.00	0.50	0.50	0.08	<0.01	0.02	0.02	0.01	<0.01	<0.01
708	MTB-12/005	44.00	44.50	0.49	0.50	0.09	<0.01	0.02	0.02	0.01	<0.01	<0.01
709	MTB-12/006	44.50	45.00	0.49	0.50	0.23	<0.01	0.02	0.02	0.01	<0.01	<0.01
710	MTB-12/007	45.00	45.50	0.45	0.50	0.03	<0.01	0.02	0.02	0.01	<0.01	<0.01
711	MTB-12/008	45.50	46.00	0.45	0.50	0.22	<0.01	0.02	0.02	0.01	<0.01	<0.01
712	MTB-12/009	46.00	46.50	0.45	0.50	0.06	<0.01	0.01	0.02	0.01	<0.01	<0.01
713	MTB-12/010	46.50	47.50	0.87	1.00	0.05	<0.01	0.01	0.02	0.01	<0.01	<0.01
714	MTB-12/011	73.50	74.50	1.00	1.00	0.02	<0.01	0.01	0.02	0.01	<0.01	<0.01
715	MTB-12/012	74.50	75.00	0.50	0.50	0.11	<0.01	0.01	0.01	0.01	<0.01	<0.01
716	MTB-12/013	75.00	75.50	0.50	0.50	<0.01	<0.01	0.01	0.02	0.01	<0.01	<0.01
717	MTB-12/014	75.50	76.25	0.75	0.75	0.02	<0.01	0.01	0.02	0.01	<0.01	<0.01
718	MTB-12/015	76.25	77.00	0.75	0.75	0.03	<0.01	<0.01	0.02	0.01	<0.01	<0.01
719	MTB-12/016	77.00	77.75	0.71	0.75	0.03	<0.01	0.01	0.02	0.01	<0.01	<0.01
720	MTB-12/017	77.75	78.50	0.71	0.75	0.03	<0.01	0.01	0.02	0.01	<0.01	<0.01
721	MTB-12/018	78.50	79.50	0.94	1.00	0.01	<0.01	0.01	0.01	<0.01	<0.01	<0.01
722	MTB-12/019	79.50	80.00	0.48	0.50	0.20	<0.01	0.01	0.02	0.01	<0.01	<0.01
723	MTB-12/020	80.00	80.50	0.44	0.50	0.03	<0.01	0.01	0.01	0.01	<0.01	<0.01
724	MTB-12/021	80.50	81.00	0.48	0.50	0.01	<0.01	0.01	0.02	0.01	<0.01	<0.01
725	MTB-12/022	81.00	81.50	0.49	0.50	0.69	<0.01	0.01	0.02	0.01	<0.01	<0.01
726	MTB-12/023	81.50	82.00	0.48	0.50	<0.01	<0.01	<0.01	0.02	0.01	<0.01	<0.01
727	MTB-12/024	82.00	82.50	0.49	0.50	0.20	<0.01	0.01	0.02	0.01	<0.01	<0.01
728	MTB-12/025	82.50	83.00	0.48	0.50	0.08	<0.01	0.01	0.01	0.01	<0.01	<0.01
729	MTB-12/026	83.00	83.50	0.45	0.50	0.08	<0.01	0.01	0.01	0.01	<0.01	<0.01
730	MTB-12/027	83.50	84.50	0.90	1.00	0.02	<0.01	0.01	0.01	0.01	<0.01	<0.01
Borehole No: MTB-13												
731	MTB-13/001	29.50	30.50	0.96	1.00	0.30	<0.01	<0.01	0.03	0.01	<0.01	<0.01
732	MTB-13/002	30.50	31.00	0.48	0.50	0.25	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
733	MTB-13/003	31.00	31.50	0.48	0.50	0.54	<0.01	<0.01	0.03	0.01	<0.01	<0.01
734	MTB-13/004	31.50	32.00	0.49	0.50	0.40	<0.01	<0.01	0.04	0.01	<0.01	<0.01
735	MTB-13/005	32.00	32.50	0.48	0.50	0.84	<0.01	<0.01	0.05	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
737	MTB-13/007	33.00	33.50	0.50	0.50	0.77	<0.01	<0.01	0.09	0.01	0.01	<0.01
738	MTB-13/008	33.50	34.00	0.50	0.50	3.24	<0.01	<0.01	0.11	0.01	0.01	<0.01
739	MTB-13/009	34.00	34.50	0.49	0.50	0.30	<0.01	<0.01	0.07	0.01	<0.01	<0.01
740	MTB-13/010	34.50	35.00	0.49	0.50	0.14	<0.01	<0.01	0.08	0.01	<0.01	<0.01
741	MTB-13/011	35.00	36.00	0.98	1.00	0.01	<0.01	0.01	0.07	<0.01	<0.01	<0.01
742	MTB-13/012	36.00	37.00	0.98	1.00	0.04	<0.01	<0.01	0.04	<0.01	<0.01	<0.01
743	MTB-13/013	37.00	37.50	0.43	0.50	0.17	<0.01	<0.01	0.02	0.01	<0.01	<0.01
744	MTB-13/014	37.50	38.00	0.43	0.50	0.35	<0.01	<0.01	0.02	0.01	<0.01	<0.01
745	MTB-13/015	38.00	38.50	0.43	0.50	0.36	<0.01	<0.01	0.04	0.01	0.01	<0.01
746	MTB-13/016	38.50	39.00	0.43	0.50	0.04	<0.01	0.01	0.04	0.01	<0.01	<0.01
747	MTB-13/017	39.00	39.50	0.43	0.50	0.05	<0.01	0.01	0.04	0.01	<0.01	<0.01
748	MTB-13/018	39.50	40.00	0.43	0.50	0.14	<0.01	<0.01	0.04	0.01	<0.01	<0.01
749	MTB-13/019	40.00	41.00	0.83	1.00	0.04	<0.01	0.01	0.03	0.01	<0.01	<0.01
750	MTB-13/020	60.00	61.00	1.00	1.00	0.01	<0.01	<0.01	0.01	<0.01	<0.01	0.01
751	MTB-13/021	61.00	61.50	0.50	0.50	0.39	<0.01	<0.01	0.03	0.01	<0.01	<0.01
752	MTB-13/022	61.50	62.00	0.50	0.50	0.42	<0.01	<0.01	0.04	0.01	<0.01	<0.01
753	MTB-13/023	62.00	62.50	0.50	0.50	0.04	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
754	MTB-13/024	62.50	63.50	1.00	1.00	0.09	<0.01	<0.01	0.02	<0.01	0.01	<0.01
755	MTB-13/025	82.50	83.50	0.96	1.00	0.01	<0.01	0.01	0.01	0.01	<0.01	<0.01
756	MTB-13/026	83.50	84.00	0.48	0.50	0.23	<0.01	<0.01	0.02	0.02	<0.01	<0.01
757	MTB-13/027	84.00	84.50	0.48	0.50	0.08	<0.01	<0.01	0.01	0.01	<0.01	<0.01
758	MTB-13/028	84.50	85.00	0.48	0.50	0.05	<0.01	0.01	0.02	0.02	<0.01	<0.01
759	MTB-13/029	85.00	85.50	0.49	0.50	0.30	<0.01	<0.01	0.03	0.01	<0.01	0.39
760	MTB-13/030	85.50	86.00	0.49	0.50	0.68	<0.01	<0.01	0.02	0.01	<0.01	<0.01
761	MTB-13/031	86.00	86.50	0.49	0.50	0.59	<0.01	<0.01	0.04	0.01	<0.01	<0.01
762	MTB-13/032	86.50	87.00	0.49	0.50	0.10	<0.01	<0.01	0.02	0.01	<0.01	<0.01
763	MTB-13/033	87.00	88.00	0.97	1.00	<0.01	<0.01	0.01	0.02	0.01	<0.01	<0.01
764	MTB-13/034	100.00	101.00	0.91	1.00	0.01	<0.01	0.01	0.02	0.01	<0.01	<0.01
765	MTB-13/035	101.00	101.50	0.49	0.50	0.01	<0.01	0.01	0.02	0.01	<0.01	<0.01
766	MTB-13/036	101.50	102.00	0.48	0.50	0.13	<0.01	0.01	0.02	0.01	<0.01	<0.01
767	MTB-13/037	102.00	102.50	0.49	0.50	0.17	<0.01	0.01	0.02	0.01	<0.01	<0.01
768	MTB-13/038	102.50	103.00	0.48	0.50	0.83	<0.01	0.01	0.02	0.01	<0.01	<0.01
769	MTB-13/039	103.00	103.50	0.50	0.50	0.35	<0.01	<0.01	0.02	0.01	<0.01	<0.01
770	MTB-13/040	103.50	104.00	0.50	0.50	0.12	<0.01	0.01	0.01	0.01	<0.01	<0.01
771	MTB-13/041	104.00	105.00	0.99	1.00	0.04	<0.01	0.01	0.01	0.01	<0.01	<0.01
Borehole No: MTB-14												
772	MTB-14/001	101.44	102.44	0.98	1.00	0.01	<0.01	<0.01	0.01	0.01	<0.01	<0.01
773	MTB-14/002	102.44	103.00	0.55	0.56	0.26	<0.01	0.01	0.03	0.01	0.01	<0.01
774	MTB-14/003	103.00	103.50	0.48	0.50	0.18	<0.01	<0.01	0.03	0.01	<0.01	<0.01
775	MTB-14/004	103.50	104.00	0.49	0.50	0.07	<0.01	<0.01	0.02	0.02	<0.01	<0.01
776	MTB-14/005	104.00	104.50	0.48	0.50	0.04	<0.01	<0.01	0.02	0.02	<0.01	<0.01
777	MTB-14/006	104.50	105.00	0.49	0.50	0.06	<0.01	<0.01	0.02	0.01	<0.01	<0.01
778	MTB-14/007	105.00	106.00	0.97	1.00	0.02	<0.01	<0.01	0.02	0.01	<0.01	<0.01
779	MTB-14/008	106.00	106.75	0.73	0.75	0.09	<0.01	<0.01	0.03	0.01	<0.01	<0.01
780	MTB-14/009	106.75	107.50	0.73	0.75	0.05	<0.01	<0.01	0.04	0.01	<0.01	<0.01
781	MTB-14/010	107.50	108.00	0.49	0.50	0.16	<0.01	<0.01	0.03	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
783	MTB-14/012	108.50	109.00	0.49	0.50	0.07	<0.01	<0.01	0.02	0.01	<0.01	<0.01
784	MTB-14/013	109.00	109.50	0.50	0.50	0.29	<0.01	<0.01	0.02	0.01	<0.01	<0.01
785	MTB-14/014	109.50	110.00	0.50	0.50	0.09	<0.01	<0.01	0.03	0.01	<0.01	<0.01
786	MTB-14/015	110.00	110.50	0.50	0.50	1.56	<0.01	<0.01	0.11	0.05	<0.01	<0.01
787	MTB-14/016	110.50	111.00	0.50	0.50	1.12	<0.01	<0.01	0.02	0.01	<0.01	<0.01
788	MTB-14/017	111.00	111.50	0.50	0.50	0.18	<0.01	<0.01	0.02	0.02	<0.01	<0.01
789	MTB-14/018	111.50	112.00	0.50	0.50	0.29	<0.01	<0.01	0.02	0.01	<0.01	<0.01
790	MTB-14/019	112.00	112.50	0.50	0.50	0.01	<0.01	<0.01	0.01	0.01	<0.01	<0.01
791	MTB-14/020	112.50	113.00	0.50	0.50	0.26	<0.01	0.01	0.01	0.01	<0.01	<0.01
792	MTB-14/021	113.00	113.50	0.50	0.50	0.22	<0.01	0.01	0.02	0.01	<0.01	<0.01
793	MTB-14/022	113.50	114.00	0.50	0.50	0.01	<0.01	<0.01	<0.01	<0.01	<0.01	<0.01
794	MTB-14/023	114.00	114.50	0.50	0.50	0.18	<0.01	<0.01	0.01	0.01	<0.01	<0.01
795	MTB-14/024	114.50	115.00	0.50	0.50	0.01	<0.01	<0.01	0.01	0.02	<0.01	<0.01
796	MTB-14/025	115.00	115.50	0.50	0.50	0.03	<0.01	0.01	0.01	<0.01	<0.01	<0.01
797	MTB-14/026	115.50	116.00	0.50	0.50	0.13	<0.01	<0.01	0.02	0.01	<0.01	<0.01
798	MTB-14/027	116.00	116.50	0.50	0.50	0.20	<0.01	<0.01	0.02	0.01	<0.01	<0.01
799	MTB-14/028	116.50	117.50	1.00	1.00	0.01	<0.01	<0.01	0.01	0.01	<0.01	<0.01
800	MTB-14/029	117.50	118.50	1.00	1.00	0.06	<0.01	0.01	0.02	0.02	<0.01	<0.01
801	MTB-14/030	118.50	119.00	0.50	0.50	0.14	<0.01	0.02	0.01	0.01	<0.01	<0.01
802	MTB-14/031	119.00	119.50	0.50	0.50	0.11	<0.01	0.01	0.01	0.01	<0.01	<0.01
803	MTB-14/032	119.50	120.25	0.75	0.75	<0.01	<0.01	<0.01	<0.01	0.01	<0.01	<0.01
804	MTB-14/033	120.25	121.00	0.75	0.75	0.01	<0.01	<0.01	0.01	0.01	<0.01	<0.01
805	MTB-14/034	121.00	121.50	0.50	0.50	1.49	<0.01	<0.01	0.02	0.01	<0.01	<0.01
806	MTB-14/035	121.50	122.00	0.50	0.50	0.20	<0.01	<0.01	0.02	0.01	<0.01	<0.01
807	MTB-14/036	122.00	122.50	0.50	0.50	0.20	<0.01	<0.01	0.02	0.01	<0.01	<0.01
808	MTB-14/037	122.50	123.00	0.50	0.50	0.43	<0.01	<0.01	0.02	0.01	<0.01	<0.01
809	MTB-14/038	123.00	123.75	0.75	0.75	0.01	<0.01	0.01	0.02	0.01	<0.01	<0.01
810	MTB-14/039	123.75	124.25	0.50	0.50	0.80	<0.01	<0.01	0.03	0.02	<0.01	<0.01
811	MTB-14/040	124.25	124.75	0.50	0.50	0.03	<0.01	0.01	0.03	0.01	<0.01	<0.01
812	MTB-14/041	124.75	125.25	0.50	0.50	0.11	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
813	MTB-14/042	125.25	125.75	0.50	0.50	0.16	<0.01	<0.01	0.03	0.01	<0.01	<0.01
814	MTB-14/043	125.75	126.25	0.50	0.50	0.03	<0.01	<0.01	0.02	0.01	<0.01	<0.01
815	MTB-14/044	126.25	126.75	0.50	0.50	0.27	<0.01	<0.01	0.03	0.02	<0.01	<0.01
816	MTB-14/045	126.75	127.75	1.00	1.00	0.21	<0.01	<0.01	0.03	0.01	<0.01	<0.01
817	MTB-14/046	127.75	128.75	1.00	1.00	0.06	<0.01	<0.01	0.02	0.01	<0.01	<0.01
818	MTB-14/047	128.75	129.75	1.00	1.00	0.08	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
819	MTB-14/048	129.75	130.25	0.50	0.50	0.19	<0.01	<0.01	0.05	0.01	0.01	<0.01
820	MTB-14/049	130.25	130.75	0.50	0.50	0.19	<0.01	<0.01	0.03	0.01	<0.01	<0.01
821	MTB-14/050	130.75	131.25	0.50	0.50	0.05	<0.01	<0.01	0.02	0.01	<0.01	<0.01
822	MTB-14/051	131.25	132.00	0.75	0.75	0.10	<0.01	<0.01	0.02	0.01	<0.01	<0.01
823	MTB-14/052	132.00	132.75	0.75	0.75	0.12	<0.01	<0.01	0.03	0.01	<0.01	<0.01
824	MTB-14/053	132.75	133.25	0.50	0.50	0.15	<0.01	<0.01	0.02	0.01	<0.01	<0.01
825	MTB-14/054	133.25	133.75	0.50	0.50	0.09	<0.01	<0.01	0.01	0.01	<0.01	<0.01
826	MTB-14/055	133.75	134.25	0.50	0.50	0.07	<0.01	0.01	0.01	0.02	<0.01	<0.01
827	MTB-14/056	134.25	134.75	0.50	0.50	0.29	<0.01	0.01	0.02	0.02	<0.01	<0.01
828	MTB-14/057	134.75	135.25	0.50	0.50	0.11	<0.01	<0.01	0.02	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
830	MTB-14/059	135.75	136.25	0.50	0.50	0.75	<0.01	<0.01	0.03	0.02	<0.01	<0.01
831	MTB-14/060	136.25	136.75	0.50	0.50	0.24	<0.01	<0.01	0.04	0.02	<0.01	<0.01
832	MTB-14/061	136.75	137.25	0.50	0.50	0.11	<0.01	<0.01	0.03	0.02	<0.01	<0.01
833	MTB-14/062	137.25	137.75	0.50	0.50	0.37	<0.01	<0.01	0.03	0.02	<0.01	<0.01
834	MTB-14/063	137.75	138.25	0.50	0.50	0.78	<0.01	<0.01	0.03	0.02	<0.01	<0.01
835	MTB-14/064	138.25	138.75	0.50	0.50	0.27	<0.01	<0.01	0.03	0.02	<0.01	<0.01
836	MTB-14/065	138.75	139.75	0.98	1.00	0.06	<0.01	<0.01	0.03	0.01	<0.01	<0.01
837	MTB-14/066	139.75	140.75	0.98	1.00	0.12	<0.01	<0.01	0.03	0.01	<0.01	<0.01
838	MTB-14/067	140.75	141.75	0.98	1.00	0.11	<0.01	<0.01	0.03	0.02	<0.01	<0.01
839	MTB-14/068	141.75	142.75	0.99	1.00	0.04	<0.01	<0.01	0.01	0.02	<0.01	<0.01
840	MTB-14/069	142.75	143.75	1.00	1.00	0.12	<0.01	<0.01	0.02	0.02	<0.01	0.01
841	MTB-14/070	143.75	144.25	0.50	0.50	0.20	<0.01	<0.01	0.02	0.01	<0.01	<0.01
842	MTB-14/071	144.25	144.75	0.50	0.50	0.23	<0.01	<0.01	0.02	0.01	<0.01	<0.01
843	MTB-14/072	144.75	145.25	0.50	0.50	0.12	<0.01	<0.01	0.02	0.01	<0.01	<0.01
844	MTB-14/073	145.25	145.75	0.50	0.50	0.23	<0.01	<0.01	0.01	0.01	<0.01	<0.01
845	MTB-14/074	145.75	146.25	0.50	0.50	0.32	<0.01	<0.01	0.02	0.02	<0.01	<0.01
846	MTB-14/075	146.25	146.75	0.50	0.50	0.18	<0.01	<0.01	0.02	0.01	<0.01	<0.01
847	MTB-14/076	146.75	147.25	0.50	0.50	0.05	<0.01	<0.01	0.01	0.01	<0.01	<0.01
848	MTB-14/077	147.25	148.00	0.75	0.75	0.01	<0.01	<0.01	0.02	0.01	<0.01	<0.01
849	MTB-14/078	148.00	148.50	0.50	0.50	0.04	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
850	MTB-14/079	148.50	149.00	0.50	0.50	0.10	<0.01	<0.01	0.02	0.01	<0.01	0.01
851	MTB-14/080	149.00	149.50	0.50	0.50	0.11	<0.01	<0.01	0.02	0.01	<0.01	<0.01
852	MTB-14/081	149.50	150.00	0.50	0.50	0.10	<0.01	0.01	0.02	0.01	<0.01	<0.01
853	MTB-14/082	150.00	150.50	0.50	0.50	0.04	<0.01	<0.01	0.02	0.01	<0.01	<0.01
854	MTB-14/083	150.50	151.50	1.00	1.00	0.04	<0.01	<0.01	0.01	0.01	<0.01	<0.01
855	MTB-14/084	151.50	152.00	0.50	0.50	0.09	<0.01	<0.01	0.01	0.01	<0.01	<0.01
856	MTB-14/085	152.00	152.50	0.50	0.50	0.16	<0.01	<0.01	0.01	0.01	<0.01	<0.01
857	MTB-14/086	152.50	153.00	0.50	0.50	0.13	<0.01	<0.01	0.01	0.01	<0.01	<0.01
858	MTB-14/087	153.00	154.00	1.00	1.00	<0.01	<0.01	<0.01	0.01	0.01	<0.01	<0.01
859	MTB-14/088	177.00	178.00	1.00	1.00	0.11	<0.01	<0.01	0.01	0.01	<0.01	<0.01
860	MTB-14/089	178.00	178.50	0.50	0.50	0.40	<0.01	<0.01	0.02	0.02	<0.01	<0.01
861	MTB-14/090	178.50	179.00	0.50	0.50	0.12	<0.01	<0.01	0.01	0.01	<0.01	<0.01
862	MTB-14/091	179.00	180.00	1.00	1.00	0.01	<0.01	<0.01	<0.01	0.01	<0.01	<0.01
863	MTB-14/092	180.00	181.00	1.00	1.00	0.06	<0.01	<0.01	0.02	0.01	<0.01	<0.01
864	MTB-14/093	181.00	181.50	0.50	0.50	0.47	<0.01	<0.01	0.03	0.01	<0.01	<0.01
865	MTB-14/094	181.50	182.00	0.50	0.50	0.63	<0.01	<0.01	0.03	0.02	<0.01	<0.01
866	MTB-14/095	182.00	182.50	0.50	0.50	0.59	<0.01	<0.01	0.03	0.01	<0.01	<0.01
867	MTB-14/096	182.50	183.00	0.49	0.50	0.07	<0.01	<0.01	0.01	0.01	<0.01	<0.01
868	MTB-14/097	183.00	184.00	0.98	1.00	0.21	<0.01	<0.01	0.01	0.01	<0.01	<0.01
869	MTB-14/098	189.00	190.00	1.00	1.00	0.12	<0.01	<0.01	0.02	0.01	<0.01	<0.01
870	MTB-14/099	190.00	190.50	0.50	0.50	0.20	<0.01	0.01	0.02	0.01	<0.01	<0.01
871	MTB-14/100	190.50	191.00	0.50	0.50	0.64	<0.01	0.01	0.02	0.01	<0.01	<0.01
872	MTB-14/101	191.00	192.00	1.00	1.00	0.01	<0.01	0.01	0.02	0.01	<0.01	<0.01
873	MTB-14/102	192.00	193.00	1.00	1.00	0.08	<0.01	0.01	0.02	0.01	<0.01	<0.01
874	MTB-14/103	193.00	193.50	0.50	0.50	0.14	<0.01	0.01	0.03	0.01	<0.01	<0.01
875	MTB-14/104	193.50	194.00	0.50	0.50	0.15	<0.01	0.01	0.02	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
877	MTB-14/106	194.50	195.00	0.50	0.50	0.11	<0.01	0.01	0.01	0.01	<0.01	<0.01
878	MTB-14/107	195.00	196.00	1.00	1.00	0.16	<0.01	0.01	0.01	0.01	<0.01	<0.01
Borehole No: MTB-15												
879	MTB-15/001	41.50	42.50	1.00	1.00	0.09	<0.01	0.01	0.07	0.02	<0.01	<0.01
880	MTB-15/002	42.50	43.00	0.50	0.50	0.18	<0.01	<0.01	0.02	0.01	<0.01	<0.01
881	MTB-15/003	43.00	43.50	0.50	0.50	0.19	<0.01	0.01	0.03	0.01	<0.01	<0.01
882	MTB-15/004	43.50	44.50	0.98	1.00	0.08	<0.01	<0.01	0.01	<0.01	0.01	<0.01
883	MTB-15/005	51.00	52.00	0.98	1.00	0.06	<0.01	<0.01	0.01	0.01	<0.01	<0.01
884	MTB-15/006	52.00	52.50	0.50	0.50	0.14	<0.01	<0.01	0.01	0.01	<0.01	<0.01
885	MTB-15/007	52.50	53.00	0.50	0.50	0.20	<0.01	0.01	0.02	0.01	<0.01	<0.01
886	MTB-15/008	53.00	53.50	0.50	0.50	0.13	<0.01	0.01	0.02	0.01	<0.01	<0.01
887	MTB-15/009	53.50	53.90	0.40	0.40	0.30	<0.01	<0.01	0.01	0.01	<0.01	<0.01
888	MTB-15/010	53.90	54.30	0.40	0.40	0.28	<0.01	0.01	0.02	0.01	<0.01	<0.01
889	MTB-15/011	54.30	54.70	0.40	0.40	1.44	<0.01	0.01	0.02	0.01	<0.01	<0.01
890	MTB-15/012	54.70	55.40	0.60	0.70	0.28	<0.01	0.01	0.02	0.01	<0.01	<0.01
891	MTB-15/013	55.40	55.85	0.41	0.45	0.03	<0.01	0.01	0.01	0.01	<0.01	<0.01
892	MTB-15/014	55.85	56.30	0.41	0.45	0.36	<0.01	0.01	0.02	0.02	<0.01	<0.01
893	MTB-15/015	56.30	56.80	0.50	0.50	0.09	<0.01	0.01	0.01	0.01	<0.01	<0.01
894	MTB-15/016	56.80	57.30	0.50	0.50	0.29	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
895	MTB-15/017	57.30	57.80	0.50	0.50	0.05	<0.01	<0.01	<0.01	<0.01	<0.01	0.01
896	MTB-15/018	57.80	58.30	0.50	0.50	0.13	<0.01	<0.01	0.01	0.01	0.01	<0.01
897	MTB-15/019	58.30	59.30	1.00	1.00	0.18	<0.01	0.01	0.01	0.01	<0.01	<0.01
898	MTB-15/020	66.50	67.50	1.00	1.00	0.04	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
899	MTB-15/021	67.50	68.50	1.00	1.00	0.13	<0.01	<0.01	0.01	0.01	<0.01	<0.01
900	MTB-15/022	68.50	69.00	0.50	0.50	0.25	<0.01	0.01	0.02	0.01	<0.01	<0.01
901	MTB-15/023	69.00	69.50	0.50	0.50	0.32	<0.01	<0.01	0.02	0.01	<0.01	<0.01
902	MTB-15/024	69.50	70.00	0.47	0.50	0.04	<0.01	<0.01	0.01	0.01	<0.01	<0.01
903	MTB-15/025	70.00	70.50	0.48	0.50	0.03	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
904	MTB-15/026	70.50	71.00	0.47	0.50	0.04	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
905	MTB-15/027	71.00	71.50	0.48	0.50	0.23	<0.01	0.01	0.01	0.01	<0.01	<0.01
906	MTB-15/028	71.50	72.50	0.94	1.00	0.03	<0.01	<0.01	0.01	0.01	<0.01	<0.01
907	MTB-15/029	72.50	73.50	1.00	1.00	0.01	<0.01	0.01	0.01	<0.01	<0.01	<0.01
908	MTB-15/030	73.50	74.50	1.00	1.00	0.01	<0.01	0.01	0.01	0.01	<0.01	<0.01
909	MTB-15/031	74.50	75.50	1.00	1.00	0.06	<0.01	<0.01	0.02	0.01	<0.01	<0.01
910	MTB-15/032	75.50	76.00	0.50	0.50	0.16	<0.01	<0.01	0.02	0.01	<0.01	<0.01
911	MTB-15/033	76.00	76.50	0.50	0.50	0.13	<0.01	<0.01	0.04	0.02	<0.01	<0.01
912	MTB-15/034	76.50	77.00	0.50	0.50	0.15	<0.01	<0.01	0.04	0.02	<0.01	<0.01
913	MTB-15/035	77.00	77.50	0.50	0.50	0.11	<0.01	<0.01	0.04	0.01	<0.01	<0.01
914	MTB-15/036	77.50	78.00	0.50	0.50	0.35	<0.01	<0.01	0.04	0.01	<0.01	<0.01
915	MTB-15/037	78.00	78.50	0.50	0.50	0.93	<0.01	<0.01	0.06	0.01	<0.01	<0.01
916	MTB-15/038	78.50	79.00	0.50	0.50	0.95	0.01	<0.01	0.06	0.02	<0.01	<0.01
917	MTB-15/039	79.00	79.50	0.50	0.50	1.29	<0.01	<0.01	0.06	0.02	<0.01	<0.01
918	MTB-15/040	79.50	80.00	0.50	0.50	0.39	<0.01	<0.01	0.04	0.02	<0.01	<0.01
919	MTB-15/041	80.00	80.50	0.50	0.50	1.21	<0.01	<0.01	0.09	0.02	<0.01	<0.01
920	MTB-15/042	80.50	81.00	0.50	0.50	0.35	<0.01	<0.01	0.04	0.01	<0.01	<0.01
921	MTB-15/043	81.00	81.50	0.50	0.50	0.64	<0.01	<0.01	0.05	0.01	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
923	MTB-15/045	82.00	82.50	0.50	0.50	0.11	<0.01	<0.01	0.02	0.01	<0.01	<0.01
924	MTB-15/046	82.50	83.00	0.50	0.50	0.21	<0.01	<0.01	0.02	0.01	<0.01	<0.01
925	MTB-15/047	83.00	83.50	0.50	0.50	0.37	<0.01	<0.01	0.04	0.01	<0.01	<0.01
926	MTB-15/048	83.50	84.00	0.50	0.50	0.08	<0.01	<0.01	0.02	0.01	<0.01	<0.01
927	MTB-15/049	84.00	84.50	0.50	0.50	0.61	<0.01	<0.01	0.03	0.01	<0.01	<0.01
928	MTB-15/050	84.50	85.00	0.50	0.50	0.05	<0.01	<0.01	0.03	0.01	<0.01	<0.01
929	MTB-15/051	85.00	85.50	0.50	0.50	0.10	<0.01	<0.01	0.02	0.01	<0.01	<0.01
930	MTB-15/052	85.50	86.50	0.98	1.00	0.10	<0.01	0.01	0.02	0.01	<0.01	<0.01
931	MTB-15/053	86.50	87.00	0.49	0.50	0.09	<0.01	0.01	0.02	0.01	<0.01	<0.01
932	MTB-15/054	87.00	87.50	0.49	0.50	0.27	<0.01	<0.01	0.05	0.01	<0.01	<0.01
933	MTB-15/055	87.50	88.00	0.49	0.50	0.48	<0.01	<0.01	0.04	0.01	<0.01	<0.01
934	MTB-15/056	88.00	88.50	0.49	0.50	0.41	<0.01	<0.01	0.03	0.01	<0.01	<0.01
935	MTB-15/057	88.50	89.00	0.50	0.50	1.42	<0.01	<0.01	0.07	0.01	<0.01	<0.01
936	MTB-15/058	89.00	89.50	0.50	0.50	0.26	<0.01	<0.01	0.02	0.01	<0.01	<0.01
937	MTB-15/059	89.50	90.00	0.50	0.50	2.14	<0.01	0.01	0.10	0.02	<0.01	<0.01
938	MTB-15/060	90.00	90.50	0.50	0.50	4.43	<0.01	0.01	0.14	0.03	0.01	<0.01
939	MTB-15/061	90.50	91.00	0.50	0.50	0.14	<0.01	<0.01	0.03	0.01	0.01	<0.01
940	MTB-15/062	91.00	91.50	0.50	0.50	0.26	<0.01	<0.01	0.02	<0.01	0.02	<0.01
941	MTB-15/063	91.50	92.50	1.00	1.00	0.05	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
942	MTB-15/064	92.50	93.50	1.00	1.00	0.11	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
943	MTB-15/065	93.50	94.00	0.50	0.50	0.09	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
944	MTB-15/066	94.00	94.50	0.50	0.50	0.40	<0.01	<0.01	0.03	<0.01	<0.01	<0.01
945	MTB-15/067	94.50	95.00	0.50	0.50	2.87	<0.01	0.01	0.06	0.01	<0.01	<0.01
946	MTB-15/068	95.00	96.00	1.00	1.00	0.06	<0.01	<0.01	0.03	0.01	<0.01	<0.01
947	MTB-15/069	96.00	96.50	0.50	0.50	0.08	<0.01	<0.01	0.03	0.01	<0.01	<0.01
948	MTB-15/070	96.50	97.00	0.50	0.50	0.26	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
949	MTB-15/071	97.00	97.50	0.50	0.50	0.33	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
950	MTB-15/072	97.50	98.50	1.00	1.00	0.10	<0.01	<0.01	0.01	<0.01	<0.01	<0.01
Borehole No: MTB-16												
951	MTB-16/001	61.30	62.30	1.00	1.00	0.13	<0.01	0.25	0.01	0.01	<0.01	<0.01
952	MTB-16/002	62.30	62.80	0.50	0.50	0.13	<0.01	0.28	0.01	0.01	<0.01	<0.01
953	MTB-16/003	62.80	63.30	0.50	0.50	0.17	<0.01	0.21	0.01	0.01	<0.01	<0.01
954	MTB-16/004	63.30	63.80	0.50	0.50	0.52	<0.01	0.18	0.01	0.01	<0.01	<0.01
955	MTB-16/005	63.80	64.30	0.50	0.50	0.35	<0.01	0.18	<0.01	0.01	<0.01	<0.01
956	MTB-16/006	64.30	65.30	1.00	1.00	0.12	<0.01	0.17	0.01	0.01	<0.01	<0.01
957	MTB-16/007	65.30	66.30	1.00	1.00	0.07	<0.01	0.06	0.01	<0.01	<0.01	0.01
958	MTB-16/008	66.30	67.30	1.00	1.00	0.02	<0.01	0.04	0.01	0.01	<0.01	<0.01
959	MTB-16/009	67.30	68.30	1.00	1.00	0.04	<0.01	0.03	0.01	0.01	<0.01	<0.01
960	MTB-16/010	68.30	69.00	0.70	0.70	0.04	<0.01	0.04	0.01	<0.01	<0.01	<0.01
961	MTB-16/011	69.00	69.50	0.50	0.50	0.11	<0.01	0.08	0.01	<0.01	<0.01	<0.01
962	MTB-16/012	69.50	70.00	0.50	0.50	0.15	<0.01	0.09	0.01	0.01	<0.01	<0.01
963	MTB-16/013	70.00	70.50	0.49	0.50	0.17	<0.01	0.11	0.01	0.02	<0.01	<0.01
964	MTB-16/014	70.50	71.00	0.49	0.50	0.06	<0.01	0.08	0.01	0.01	<0.01	<0.01
965	MTB-16/015	71.00	71.50	0.49	0.50	0.08	<0.01	0.08	0.01	0.01	<0.01	<0.01
966	MTB-16/016	71.50	72.00	0.49	0.50	0.04	<0.01	0.07	0.01	0.02	<0.01	0.01
967	MTB-16/017	72.00	72.50	0.49	0.50	0.10	<0.01	0.08	0.01	0.02	<0.01	<0.01

Sl. No.	Sample No.	Depth (m)		Rec. Thickness (m)	Thickness (m)	Grade (%)						
		From	To			Cu	Pb	Zn	Ni	Co	Mo	W
969	MTB-16/019	73.00	73.50	0.48	0.50	0.14	<0.01	0.05	0.01	0.01	<0.01	<0.01
970	MTB-16/020	73.50	74.50	0.98	1.00	0.09	<0.01	0.03	0.01	0.01	<0.01	<0.01
Borehole No: MTB-17												
971	MTB-17/001	89.77	90.77	0.95	1.00	0.17	<0.01	<0.01	0.04	0.01	<0.01	<0.01
972	MTB-17/002	90.77	91.77	0.97	1.00	0.17	<0.01	<0.01	0.03	0.01	<0.01	<0.01
973	MTB-17/003	91.77	92.77	0.97	1.00	0.10	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
974	MTB-17/004	92.77	93.18	0.40	0.41	0.95	<0.01	<0.01	0.03	0.01	<0.01	<0.01
975	MTB-17/005	93.18	93.59	0.40	0.41	0.53	<0.01	0.01	0.03	0.01	<0.01	<0.01
976	MTB-17/006	93.59	94.00	0.40	0.41	0.16	<0.01	<0.01	0.03	0.01	<0.01	<0.01
977	MTB-17/007	94.00	94.50	0.48	0.50	0.21	<0.01	<0.01	0.02	0.01	<0.01	<0.01
978	MTB-17/008	94.50	95.00	0.49	0.50	0.80	<0.01	<0.01	0.03	0.01	<0.01	<0.01
979	MTB-17/009	95.00	95.50	0.48	0.50	0.10	<0.01	<0.01	0.02	0.01	<0.01	<0.01
980	MTB-17/010	95.50	96.00	0.48	0.50	1.01	<0.01	<0.01	0.03	0.01	<0.01	<0.01
981	MTB-17/011	96.00	96.50	0.48	0.50	0.01	<0.01	<0.01	0.02	0.01	<0.01	<0.01
982	MTB-17/012	96.50	97.00	0.49	0.50	0.76	<0.01	<0.01	0.02	0.01	<0.01	<0.01
983	MTB-17/013	97.00	97.75	0.71	0.75	0.13	<0.01	<0.01	0.02	0.01	<0.01	<0.01
984	MTB-17/014	97.75	98.50	0.71	0.75	0.23	<0.01	<0.01	0.02	0.01	<0.01	<0.01
985	MTB-17/015	98.50	99.25	0.71	0.75	0.29	<0.01	0.01	0.03	0.02	<0.01	<0.01
986	MTB-17/016	99.25	100.00	0.72	0.75	0.14	<0.01	<0.01	0.03	0.02	<0.01	<0.01
987	MTB-17/017	100.00	100.50	0.47	0.50	2.04	<0.01	0.01	0.04	0.03	0.01	<0.01
988	MTB-17/018	100.50	101.00	0.48	0.50	0.66	<0.01	<0.01	0.02	0.01	<0.01	<0.01
989	MTB-17/019	101.00	101.50	0.47	0.50	0.06	<0.01	<0.01	0.02	0.01	<0.01	<0.01
990	MTB-17/020	101.50	102.00	0.48	0.50	0.08	<0.01	<0.01	0.02	0.01	<0.01	<0.01
991	MTB-17/021	102.00	102.50	0.47	0.50	0.10	<0.01	<0.01	0.02	0.01	<0.01	<0.01
992	MTB-17/022	102.50	103.00	0.48	0.50	0.01	<0.01	<0.01	0.01	0.01	<0.01	<0.01
993	MTB-17/023	103.00	103.50	0.50	0.50	0.96	<0.01	<0.01	0.01	0.01	0.03	<0.01
994	MTB-17/024	103.50	104.00	0.50	0.50	0.29	<0.01	<0.01	0.02	0.02	0.03	<0.01
995	MTB-17/025	104.00	104.50	0.50	0.50	0.05	<0.01	<0.01	0.01	0.01	<0.01	<0.01
996	MTB-17/026	104.50	105.00	0.50	0.50	0.02	<0.01	<0.01	0.01	0.01	<0.01	<0.01
997	MTB-17/027	105.00	105.50	0.50	0.50	0.05	<0.01	<0.01	0.01	0.01	<0.01	<0.01
998	MTB-17/028	105.50	106.00	0.50	0.50	0.26	<0.01	<0.01	0.11	0.06	0.39	<0.01
999	MTB-17/029	106.00	106.50	0.48	0.50	0.05	<0.01	<0.01	0.02	0.02	0.06	<0.01
1000	MTB-17/030	106.50	107.25	0.72	0.75	0.02	<0.01	<0.01	0.02	0.02	<0.01	<0.01
1001	MTB-17/031	107.25	108.00	0.72	0.75	<0.01	<0.01	0.01	0.03	0.02	0.27	<0.01
1002	MTB-17/032	108.00	109.00	0.96	1.00	0.01	<0.01	<0.01	0.03	0.01	<0.01	<0.01
1003	MTB-17/033	109.00	109.50	0.49	0.50	0.06	<0.01	<0.01	0.03	0.01	<0.01	<0.01
1004	MTB-17/034	109.50	110.00	0.49	0.50	0.04	<0.01	<0.01	0.04	0.01	<0.01	<0.01
1005	MTB-17/035	110.00	110.50	0.49	0.50	0.01	<0.01	<0.01	0.02	<0.01	<0.01	<0.01
1006	MTB-17/036	110.50	111.00	0.49	0.50	0.01	<0.01	<0.01	0.02	0.01	0.02	<0.01
1007	MTB-17/037	111.00	111.50	0.49	0.50	0.02	<0.01	<0.01	0.02	0.01	0.08	<0.01
1008	MTB-17/038	111.50	112.00	0.48	0.50	0.88	<0.01	0.01	0.04	0.02	0.01	<0.01
1009	MTB-17/039	112.00	112.50	0.47	0.50	3.53	<0.01	0.01	0.04	0.03	<0.01	<0.01
1010	MTB-17/040	112.50	113.00	0.47	0.50	0.01	<0.01	0.01	0.04	0.01	<0.01	<0.01
1011	MTB-17/041	113.00	114.00	0.94	1.00	0.02	<0.01	0.01	0.05	0.01	<0.01	<0.01